




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 210/16, 4/645	A1	(11) International Publication Number: WO 98/49211 (43) International Publication Date: 5 November 1998 (05.11.98)
(21) International Application Number: PCT/US98/08859 (22) International Filing Date: 1 May 1998 (01.05.98) (30) Priority Data: 60/045,348 1 May 1997 (01.05.97) US 60/045,410 1 May 1997 (01.05.97) US (71) Applicant (for all designated States except US): THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Midland, MI 48674 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): KALE, Lawrence, T. [CA/US]; 121 Portulaca, Lake Jackson, TX 77566 (US). VANDERLENDE, Daniel, D. [US/US]; 5003 Kingsland Court, Sugar Land, TX 77479 (US). NICKIAS, Peter, N. [US/US]; 2705 Mt. Vernon Drive, Midland, MI 48642 (US). PATTON, Jasson, T. [US/US]; 1302 Whitehall Street, Midland, MI 48642 (US). STEVENS, James, C. [US/US]; 2026 Pecan Trail Drive, Richmond, TX 77469 (US). PARIKH, Deepak, R. [US/US]; 59 Trillium Court, Lake Jackson, TX (US). MANGOLD, Debra, J. [US/US]; 301 Juniper, Lake Jackson, TX 77566 (US).	(74) Agent: WARRICK, Noreen, D.; Patent Dept., B-1211, 2301 Brazosport Boulevard, Freeport, TX 77541 (US). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.	

(54) Title: OLEFIN POLYMERS PREPARED WITH SUBSTITUTED INDENYL CONTAINING METAL COMPLEXES



(57) Abstract

The subject invention is directed to an olefin polymer produced by polymerizing at least one α -olefin in the presence of a Group 4 metal complex comprising an indenyl group substituted in the 2 or 3 position with at least one group selected from hydrocarbyl, perfluoro-substituted hydrocarbyl, silyl, germyl and mixtures thereof, said indenyl group further being covalently bonded to the metal by means of a divalent ligand group, wherein the divalent ligand comprises nitrogen or phosphorus having an aliphatic or alicyclic hydrocarbyl group covalently bonded thereto via a primary or secondary carbon. Preferred olefin polymers of the invention will be characterized as having a high molecular weight, narrow molecular weight distribution, high vinyl content, and a bimodal DSC melting curve or a deconvoluted ATREF or GPC curve which shows at least two distinct narrow peaks. The olefin polymer will have utility in a variety of applications, including but not limited to films, fibers, foams, molded parts, and as components of formulations such as adhesives, sealants, coatings, caulks, and asphalt.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

OLEFIN POLYMERS PREPARED WITH SUBSTITUTED INDENYL CONTAINING METAL COMPLEXES

This invention relates to a class of Group 4 metal complexes and to olefin polymerization catalysts derived therefrom that are particularly suitable for use in a polymerization process for preparing polymers by polymerization of α -olefins and mixtures of α -olefins, and to the α -olefins and mixtures of α -olefins resulting therefrom.

Constrained geometry metal complexes and methods for their preparation are disclosed in EP-A-416,815; EP-A-468,651; EP-A-514,828; EP-A-520,732 and WO93/19104, as well as US-A-5,055,438, US-A-5,057,475, US-A-5,096,867, US-A-5,064,802, US-A-5,132,380, US-A-5,470,993, WO95/00526, and US Provisional Application 60-005913. Various substituted indenyl containing metal complexes have been taught in U.S. Serial No. 592,756, filed January 26, 1996, as well as WO 95/14024.

Constrained geometry catalysts and other single site or metallocene catalysts are useful to prepare homogeneous olefin polymers. The term "homogeneous olefin polymers" refers to homopolymers or interpolymers of one or more α -olefins which are characterized as having a narrow polydispersity, that is, an M_w/M_n of from 1.5 to 3.0, and, in the case of interpolymers, a homogeneous short chain branching distribution, that is, wherein each molecule has substantially the same number of short chain branches. Homogeneous olefin polymers are advantageous over Ziegler Natta produced polymers, in that they lack a low molecular weight tail fraction, which translates to improved strength and toughness. Homogeneous olefin polymers are further advantageous over Ziegler Natta produced polymers, in that the catalysts useful to prepare such polymers, particularly the constrained geometry catalysts, readily and efficiently incorporate comonomer, which permits the cost-effective production of polymers having a density of less than 0.910 g/cm³ which accords good elastomeric properties.

Despite their advantageous features, homogeneous polymers are typically more difficult to process than their Ziegler Natta counterparts, in part due to the absence of the low molecular weight fraction and in part due to the narrowness of the melting region.

One preferred class of homogeneous olefin polymers is the class of substantially linear polymers, which are characterized as having a narrow polydispersity, a homogeneous short chain branching distribution, and the presence of sufficient long chain branching to provide improved rheological properties and resistance to melt fracture. Substantially linear polymers are disclosed and claimed in U.S. Patent Nos. 5,272,236; 5,278,272; 5,380,810; and EP 659,773; EP 676,421; and WO 94/07930.

An alternate approach to utilizing the preferred substantially linear olefin polymers has been to incorporate into homogeneous olefin polymers effective amounts of polymer processing aids prior to fabrication into films or articles. This is disadvantageous, in that it requires an additional processing step and adds cost to the finished product.

5 While homogeneous olefin-based elastomers, and particularly substantially linear olefin polymers, have found significant commercial utility, the low density of the elastomers, coupled with the absence of a higher crystallinity non-short chain branched fraction renders such polymers relatively poor in terms of upper service temperature and susceptible to deformation under heat, such as in a clothes dryer.

10 To improve the upper service temperature of homogeneous olefin polymers which are elastomers, one can blend such polymers with higher crystallinity homogeneous or heterogeneous olefin polymers, either via a physical blend or via an in-reactor mixture produced in a dual reactor system, such as is disclosed in U.S. Serial No. 510,527, filed on August 2, 1995 (WO 94/171112) and U.S. Serial No. 208,068, filed on March 8, 1994 (EP 619827).

15 However, industry would find great advantage in a polymer having elastomeric properties which exhibits a resistance to deformation under heat which is greater than that of a physical or in-reactor blend of the same overall density. Industry would find particular advantage in those of such polymers which have an overall polydispersity of from 1.5 to 3.0, but which have excellent processability, as evidenced by resistance to melt fracture and/or an
20 I_w/I_n of at least 10. Industry would find especially particular advantage in those of such polymers which may be produced in a single reactor using a highly efficient catalyst which is resistant to degradation at elevated temperature.

It is noted that U.S. Patent No. 5,621,126 to Exxon Chemical Patents, Inc., discloses the use of mono(cyclopentadienyl) Group IV B metal compounds to produce ethylene/ α -olefin
25 copolymers. U.S. Patent No. 5,621,126 asserts that catalysts containing an amido group having a hydrocarbyl ligand R' which is aliphatic or alicyclic and which is bonded to the nitrogen atom through a primary or secondary carbon produce copolymers having a greater degree of α -olefin incorporation than catalysts wherein the hydrocarbyl ligand R' is bonded to the nitrogen atom through a tertiary carbon atom or wherein R' bears aromatic carbon atoms. U.S. Patent No.
30 5,621,126 asserts that when the R' ligand is bonded to the nitrogen atom through a secondary carbon atom, the activity of the catalyst is greater when R' is alicyclic than when R' is bonded to the nitrogen through a primary carbon atom of an aliphatic group of identical carbon number. U.S. Patent No. 5,621,126 asserts that as the number of carbon atoms of R' thereof increases, the productivity of the catalyst system and the molecular weight of the ethylene/ α -olefin
35 copolymer increase while the amount of α -olefin comonomer incorporated remains about the

same or increases. U.S. Patent No. 5,621,126 asserts that the more preferred R' ligand is cyclododecyl.

The compositions of U.S. 5,621,126 are disadvantageous, in that they are believed to lack long chain branching, making them susceptible to melt fracture, and thus, less
5 commercially desirable.

Further, while mono(cyclopentadienyl) Group IV B metal compounds may indeed find great commercial advantage in the polymerization of ethylene/ α -olefin interpolymers, those in industry are continually seeking improvements and, in particular, would find advantage in catalysts which withstand higher reaction temperatures than are characteristic of
10 mono(cyclopentadienyl) catalysts. Such higher reaction temperatures would translate to polymers exhibiting a high degree of vinyl unsaturation, making them especially useful as precursors to functionalized polymers, and enhancing long chain branch incorporation when appropriate polymerization conditions are employed.

According to the present invention there is provided a product produced by a process
15 for preparing polymers of olefin monomers comprising contacting one or more such monomers with a catalyst comprising:

1) a metal complex corresponding to the formula:



20 wherein:

M is titanium, zirconium or hafnium in the +2, +3 or +4 formal oxidation state;

A' is a substituted indenyl group substituted in at least the 2 or 3 position with a group selected from hydrocarbyl, fluoro-substituted hydrocarbyl, hydrocarbyloxy-substituted hydrocarbyl, dialkylamino- substituted hydrocarbyl, silyl, germyl and mixtures thereof, said
25 group containing up to 40 nonhydrogen atoms, and said A' further being covalently bonded to M by means of a divalent Z group;

Z is a divalent moiety bound to both A' and M via σ -bonds, said Z comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen, phosphorus, sulfur or oxygen, wherein Z preferably has covalently bonded thereto an aliphatic
30 or cycloaliphatic hydrocarbyl or substituted hydrocarbyl group, such that the hydrocarbyl group is covalently bonded to Z via a primary or secondary carbon;

X is an anionic or dianionic ligand group having up to 60 atoms exclusive of the class of ligands that are cyclic, delocalized, π -bound ligand groups;

X' independently each occurrence is a neutral ligating compound, having up to 20 atoms;

p is 0, 1 or 2, and is two less than the formal oxidation state of M, with the proviso that when X is a dianionic ligand group, p is 1; and

5 q is 0, 1 or 2;


and

2) an activating cocatalyst

the molar ratio of 1) to 2) being from 1:10,000 to 100:1, or

the reaction product formed by converting 1) to an active catalyst by use of an
10 activating technique.

Also disclosed is a product produced by a process comprising reacting one or more α -olefins in the presence of a catalyst which in turn comprises a metal complex corresponding to the formula:



15 where M is titanium, zirconium or hafnium in the +2, +3 or +4 formal oxidation state;

R' and R'' are independently each occurrence hydride, hydrocarbyl, silyl, germyl, halide, hydrocarbyloxy, hydrocarbylsiloxy, hydrocarbylsilylamino, di(hydrocarbyl)amino, hydrocarbyleneamino, di(hydrocarbyl)phosphino, hydrocarbylene-phosphino, hydrocarbylsulfido, halo-substituted hydrocarbyl, hydrocarbyloxy-substituted hydrocarbyl, silyl-
20 substituted hydrocarbyl, hydrocarbylsiloxy-substituted hydrocarbyl, hydrocarbylsilylamino-substituted hydrocarbyl, di(hydrocarbyl)amino-substituted hydrocarbyl, hydrocarbyleneamino-substituted hydrocarbyl, di(hydrocarbyl)phosphino-substituted hydrocarbyl, hydrocarbylene-phosphino-substituted hydrocarbyl, or hydrocarbylsulfido-substituted hydrocarbyl, said R' or R'' group having up to 40 nonhydrogen atoms, and optionally two or more of the foregoing groups
25 may together form a divalent derivative;

R''' is a divalent hydrocarbylene- or substituted hydrocarbylene group forming a fused system with the remainder of the metal complex, said R''' containing from 1 to 30 nonhydrogen atoms;

Z is a divalent moiety, or a moiety comprising one σ -bond and a neutral two electron pair able to form a coordinate-covalent bond to M, said Z comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen, phosphorus, sulfur or oxygen;

- 5 X is a monovalent anionic ligand group having up to 60 atoms exclusive of the class of ligands that are cyclic, delocalized, π -bound ligand groups;

X' independently each occurrence is a neutral ligating compound having up to 20 atoms;

X" is a divalent anionic ligand group having up to 60 atoms;

- 10 p is zero, 1, 2, or 3;

q is zero, 1 or 2, and

r is zero or 1; and

2) an activating cocatalyst

the molar ratio of 1) to 2) being from 1:10,000 to 100:1, or

- 15 the reaction product formed by converting 1) to an active catalyst by use of an activating technique.

- The present catalysts and process employed in the polymerization of the polymers of the invention, preferably by means of a solution polymerization process, result in the highly efficient production of high molecular weight olefin polymers, particularly ethylene/ α -olefin
 20 interpolymers, ethylene/propylene/diene interpolymers (EPDM), wherein the diene is ethylenenorbornene, 1,4-hexadiene, or a similar nonconjugated diene, or is piperylene, over a wide range of polymerization conditions, and especially at elevated temperatures. The use of elevated temperatures dramatically increases the productivity of such process due to the fact that increased polymer solubility at elevated temperatures allows the use of increased
 25 conversions (higher concentration of polymer product) without exceeding solution viscosity limitations of the polymerization equipment as well as reduced energy costs needed to devolatilize the reaction product.

- The subject invention further provides an olefin interpolymers, preferably an interpolymers of ethylene and at least one C_3 - C_{20} α -olefin, characterized as satisfying at least four of the
 30 following criteria, especially all five of the following criteria:

- a) an $I_2 \leq 100$ g/10 min,
- b) an M_w/M_n of from 1.5 to 3.0,
- c) at least 0.03 vinyls/1000 carbons, as determined by FTIR, and
- d) at least two distinct ATREF peaks, each of which satisfies the following inequality:
5 ATREF Shape Factor $\leq 0.90 - 0.00626$ (Average Elution Temperature) .

The use of the indenyl and indenyl catalysts as disclosed herein leads to the production of polymers having a high degree of vinyl termination. The resultant high level of vinyls/1000 carbons makes the polymers of the invention especially useful in applications wherein the polymers are subsequently functionalized. The resultant high level of vinyls/1000
10 carbons further makes the polymers able to achieve higher levels of long chain branching when appropriate polymerization conditions are employed.

Preferably, the polymers of the invention will be characterized as having an I_{10}/I_2 of at least 10, preferably at least 12, and most preferably at least 15.

As further qualitative indicia of long chain branching, the polymers of the invention will
15 preferably further be characterized as exhibiting a critical shear rate at the onset of surface melt fracture which is at least 50 percent greater than the critical shear rate at the onset of surface melt fracture for a linear interpolmer, wherein the substantially linear interpolmer and the linear interpolmer comprise the same comonomer or comonomers, the linear interpolmer has an I_2 , M_w/M_n and density within ten percent of that of the substantially linear interpolmer, and
20 wherein the respective critical shear rates of the substantially linear interpolmer and the linear interpolmer are measured at the same melt temperature using a gas extrusion rheometer.

The olefin interpolymers of the invention are uniquely characterized as being bimodal with respect to the short chain branching distribution and molecular weight, as evidenced by the differential scanning calorimetry and ATREF curves, as well as the deconvoluted gel
25 permeation chromatographs. This effect is particularly true for interpolymers having a density of no more than 0.910 g/cm^3 .

It has been found that interpolymers of the invention having a density less than 0.890 g/cm^3 , particularly having a density of no more than 0.880 g/cm^3 , and more particularly having a density of less than 0.870 g/cm^3 have a particularly superior and highly unique balance of
30 properties. In particular, such polymers have improved elastomeric properties, such as a compression set of less than 90 percent, preferably less than 85 percent, more preferably less than 80 percent, coupled with an upper service temperature which exceeds that of a physical

blend of interpolymers corresponding to the components of the interpolymers of the invention as discerned by the deconvolution of the representative gel permeation chromatograph. The uniqueness of the interpolymers of the invention is evident in micrographs obtained by transmission electron microscopy, which clearly show the presence of lamella in interpolymers whose density would suggest should be wholly amorphous.

The olefin interpolymers of the invention are expected to have great utility in a variety of applications, including but not limited to films, fibers, foams, injection molded parts, rotational molded parts, and as components of formulations such as adhesives, sealants, coatings, caulks, and asphalt.

These and other embodiments are more fully described in the following Detailed Description, wherein:

FIGURE 1 is an illustration of catalysts, cocatalysts, and scavenging compounds practiced in the examples set forth herein.

FIGURE 2 is a DSC endogram of an ethylene/octene interpolymer of Comparative Example C-3a prepared using Catalyst Three.

FIGURE 3 is a DSC endogram of the ethylene/octene interpolymer of Example 1a prepared using Catalyst One.

FIGURE 4 is a DSC endogram of the ethylene/octene interpolymer of Example 2a prepared using Catalyst Two.

FIGURE 5 is a transmission electron micrograph of the ethylene/octene interpolymer of Example 2a prepared using Catalyst Two.

FIGURE 6 is a transmission electron micrograph of the ethylene/octene interpolymer of Comparative Example C-3a prepared using Catalyst Three.

FIGURE 7a are ATREF curves of two ethylene/octene interpolymers of the invention, prepared with Catalyst One (Example 1b) and Catalyst Two (Example 2a), respectively, and of the ethylene/octene interpolymer of Comparative Example C-3a prepared with Catalyst Three.

FIGURE 7b are ATREF curves of an ethylene/octene interpolymer prepared with Catalyst Two, and of a comparative ethylene/octene interpolymer having a density of 0.895 g/cm³ and a melt index (I₂) of 1.6 g/10 minutes prepared with Catalyst Three.

FIGURE 7c are ATREF and differential viscosity curves of the ethylene/octene interpolymer of Example 45(e) prepared with Catalyst Two.

FIGURE 7d is a plot of the ATREF shape factor versus the average ATREF elution temperature.

FIGURE 8a and 8b provide dynamic mechanical data for ethylene/octene interpolymers prepared with Catalyst One (Example 1a) and Catalyst Two (Example 2a), respectively, and for an ethylene/octene interpolymers prepared with Catalyst Three (Comparative Example C-3a).

FIGURE 9a is a plot of the upper service temperature (UST) of ethylene/octene
5 interpolymers prepared with Catalyst Two and of comparative ethylene/octene interpolymers prepared with Catalyst Three, and of a blend of two ethylene/octene interpolymers prepared with Catalyst Three.

FIGURE 9b is a plot of the difference between the UST of various blends of
ethylene/octene interpolymers prepared using Catalyst Three with the UST of interpolymers of
10 the invention set forth in FIGURE 9a.

FIGURE 10 is a deconvoluted gel permeation chromatogram of the ethylene/octene
interpolymer of Example 1b prepared with Catalyst One.

FIGURE 11 is a deconvoluted gel permeation chromatogram of the ethylene/octene
interpolymer of Example 2b prepared with Catalyst Two.

FIGURE 12 is a deconvoluted gel permeation chromatogram of the ethylene/octene
interpolymer of Comparative Example C-2a prepared with Catalyst Two and using a batch
15 polymerization process.

FIGURE 13 are viscosity curves for the ethylene/octene interpolymers of Example 2a
prepared using Catalyst Two in a continuous solution polymerization process and of
20 Comparative Example C-2a prepared using Catalyst Three in a solution batch polymerization process.

FIGURE 14 is a depiction of the compression set of ethylene/octene interpolymers
prepared using Catalysts One and Two, respectively, and of an ethylene/octene interpolymers
prepared using Catalyst Three.

25 FIGURES 15 and 16 are DSC curves for an EPDM of the invention.

All reference to the Periodic Table of the Elements herein shall refer to the Periodic
Table of the Elements, published and copyrighted by CRC Press, Inc., 1989. Also, any
reference to a Group or Groups shall be to the Group or Groups as reflected in this Periodic
Table of the Elements using the IUPAC system for numbering groups.

30 Unless otherwise indicated, the following procedures are employed:

Density is measured in accordance with ASTM D-792. The samples are annealed at
ambient conditions for 24 hours before the measurement is taken.

Melt index (I_2), is measured in accordance with ASTM D-1238, condition 190°C/2.16 kg (formally known as "Condition (E)").

I_{10} , is measured in accordance with ASTM D-1238, Condition 190°C/10 kg (formerly known as "Condition N").

5 Molecular weight is determined using gel permeation chromatography (GPC) on a Waters 150°C high temperature chromatographic unit equipped with three mixed porosity columns (Polymer Laboratories 103, 104, 105, and 106), operating at a system temperature of 140°C. The solvent is 1,2,4-trichlorobenzene, from which 0.3 percent by weight solutions of the samples are prepared for injection. The flow rate is 1.0 mL/min. and the injection size is 100
10 microliters.

The molecular weight determination is deduced by using narrow molecular weight distribution polystyrene standards (from Polymer Laboratories) in conjunction with their elution volumes. The equivalent polyethylene molecular weights are determined by using appropriate Mark-Houwink coefficients for polyethylene and polystyrene (as described by Williams and
15 Word in Journal of Polymer Science, Polymer Letters, Vol. 6, (621) 1968, incorporated herein by reference) to derive the following equation:

$$M_{\text{polyethylene}} = a * (M_{\text{polystyrene}})^b.$$

In this equation, $a = 0.4316$ and $b = 1.0$. Weight average molecular weight, M_w , is calculated in the usual manner according to the following formula: $M_w = \sum w_i * M_i$, where w_i and
20 M_i are the weight fraction and molecular weight, respectively, of the i th fraction eluting from the GPC column.

Percent crystallinity is calculated with the equation:

$$\%C = (A/292 \text{ J/g}) \times 100,$$

in which %C represents the percent crystallinity and A represents the heat of fusion of the
25 ethylene in Joules per gram (J/g) as determined by differential scanning calorimetry (DSC).

Differential scanning calorimetry (DSC) data was generated by placing each sample (5 mg) in an aluminum pan, the sample was heated to 160°C, cooled at 10°C/min and the endotherm was recorded by scanning from -30°C to 140°C at 10°C/min using a Perkin Elmer DSC 7. The DSC exotherm (cooling curve) was also recorded by scanning from 140 to -30 at
30 10°C/min.

The morphology of the copolymers were investigated by transmission electron microscopy (TEM). Samples were stained with ruthenium chloride-hypochlorite and then thin slices were prepared with a glass knife on a microtome at room temperature. Micrographs were
35 recorded at 150000-fold magnification on a JEOL 2000FX microscope.

Analytical temperature rising elution fractionation (ATREF) data were generated using the standard equipment within Polyolefins Research. The polymer sample (dissolved in hot trichlorobenzene) was crystallized in a column containing an inert support (steel shot) by slowly
5 reducing the temperature. An ATREF chromatogram was then generated by eluting the crystallized sample from the column by slowly increasing the temperature of the eluting solvent, trichlorobenzene. The ATREF curve illustrated several key structural features of the resin. For example, the response from the refractive index detector gives the short chain branching distribution; while the response from the differential viscometer detector provides an estimate of
10 the viscosity average molecular weight.

Dynamic mechanical spectroscopy measurements were made on the RMS-800 dynamic mechanical spectrometer using 25 mm diameter parallel plates (gap 2mm) in the oscillatory shear mode. Frequency sweeps were performed over the shear rate ranges of 0.1 to
15 100 rad/s at 15 percent strain in a nitrogen atmosphere at 190°C. Temperature sweeps were also performed on the RDAII dynamic analyzer. In this case 12.5 mm diameter parallel plates (gap 1.5mm) were used over the temperature range from about -100°C to 200°C at a frequency of 1 rad/s in a nitrogen atmosphere. The sample was loaded at room temperature, heated to 60°C to ensure good contact between the sample and the plates and then cooled to -100°C
20 prior to beginning the temperature sweep experiment.

Processability was evaluated using the gas extrusion rheometer (GER). The resin was packed into a capillary rheometer equipped with a 0.0296-in. diameter and 20 L/D cylindrical die operating at 190°C. Using nitrogen gas to pressurize the rheometer, samples of extrudate were
25 collected as the pressure was decreased from 5500 to 1000 psi (38 to 6.9 MPa), in steps of 250 psi (1.7 MPa), generally, 19 copolymer samples were collected. After solidification, the surface of each extrudate was examined visually for surface flow defects, for instance, the point where each resin lost surface gloss (LSG) and the point where each resin became grossly melt fractured (OGMF) was determined.

30

Olefins as used herein are C₂₋₂₀ aliphatic or aromatic compounds containing vinylic unsaturation, as well as cyclic compounds such as cyclobutene, cyclopentene, and norbornene, including norbornene substituted in the 5 and 6 position with C₁₋₂₀ hydrocarbyl groups. Also included are mixtures of such olefins as well as mixtures of such olefins with C₄₋₄₀ diolefin
35 compounds. Examples of the latter compounds include ethylidene norbornene, 1,4-hexadiene, norbornadiene, and the like. The catalysts and process herein are especially suited for use in

preparation of ethylene/propylene, ethylene/1-butene, ethylene/1-pentene, ethylene/4-methyl-1-pentene, ethylene/1-hexene, ethylene/1-octene, and ethylene/styrene interpolymers as well as terpolymers of ethylene, propylene and a nonconjugated diene, that is EPDM terpolymers, with interpolymers of ethylene and a C₃-C₂₀ α-olefin, preferably at C₄-C₂₀ α-olefin, and more preferably a C₆-C₁₀ α-olefin, with ethylene/1-octene polymers being especially preferred.

The interpolymers of the invention will preferably be prepared using catalyst systems derived from a metal complex corresponding to the formula:



wherein:

M is titanium, zirconium or hafnium in the +2, +3 or +4 formal oxidation state;

A' is a substituted indenyl group substituted in at least the 2 or 3 position with a group selected from hydrocarbyl, fluoro-substituted hydrocarbyl, hydrocarbyloxy-substituted hydrocarbyl, dialkylamino-substituted hydrocarbyl, silyl, germyl and mixtures thereof, said group containing up to 40 nonhydrogen atoms, and said A' further being covalently bonded to M by means of a divalent Z group;

Z is a divalent moiety bound to both A' and M via σ-bonds, said Z comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen or phosphorus, wherein an aliphatic or alicyclic hydrocarbyl group is covalently bonded to the nitrogen or phosphorus via a primary or secondary carbon;

X is an anionic or dianionic ligand group having up to 60 atoms exclusive of the class of ligands that are cyclic, delocalized, π-bound ligand groups;

X' independently each occurrence is a neutral ligating compound, having up to 20 atoms;

p is 0, 1 or 2, and is two less than the formal oxidation state of M, with the proviso that when X is a dianionic ligand group, p is 1; and


q is 0, 1 or 2.

Preferred X' groups are carbon monoxide; phosphines, especially trimethylphosphine, triethylphosphine, triphenylphosphine and bis(1,2-dimethylphosphino)ethane; P(OR)₃, wherein R is as previously defined; ethers, especially tetrahydrofuran; amines, especially pyridine, bipyridine, tetramethylethylenediamine (TMEDA), and triethylamine; olefins; and conjugated

dienes having from 4 to 40 carbon atoms. Complexes including the latter X' groups include those wherein the metal is in the +2 formal oxidation state.

In the case of the above metal complexes, as well as in the case of the other metal complexes disclosed herein, M is preferably zirconium or titanium, and is more preferably titanium.

Preferred substituted indenyl coordination complexes used according to the present invention are complexes corresponding to the formula:



wherein:

R_1 and R_2 , independently are groups selected from hydrogen, hydrocarbyl, perfluoro substituted hydrocarbyl, silyl, germyl and mixtures thereof, said group containing up to 20 nonhydrogen atoms, with the proviso that at least one of R_1 or R_2 is not hydrogen;

R_3 , R_4 , R_5 , and R_6 independently are groups selected from hydrogen, hydrocarbyl, perfluoro substituted hydrocarbyl, silyl, germyl and mixtures thereof, said group containing up to 20 nonhydrogen atoms;

M is titanium, zirconium or hafnium;

Z is a divalent moiety comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen or phosphorus, said moiety having up to 60 nonhydrogen atoms, wherein an aliphatic or alicyclic hydrocarbyl group is covalently bonded to the nitrogen or phosphorus via a primary or secondary carbon;

p is 0, 1 or 2;

q is zero or one;

with the proviso that:


when p is 2, q is zero, M is in the +4 formal oxidation state, and X is an anionic ligand selected from the group consisting of halide, hydrocarbyl, hydrocarbyloxy, di(hydrocarbyl)amido, di(hydrocarbyl)phosphido, hydrocarbylsulfido, and silyl groups, as well as

halo-, di(hydrocarbyl)amino-, hydrocarbyloxy- and di(hydrocarbyl)phosphino-substituted derivatives thereof, said X group having up to 20 nonhydrogen atoms,

when p is 1, q is zero, M is in the +3 formal oxidation state, and X is a stabilizing anionic ligand group selected from the group consisting of allyl, 2-(N,N-dimethylaminomethyl)phenyl, and 2-(N,N-dimethyl)-aminobenzyl, or M is in the +4 formal oxidation state, and X is a divalent derivative of a conjugated diene, M and X together forming a metallocyclopentene group, and

when p is 0, q is 1, M is in the +2 formal oxidation state, and X' is a neutral, conjugated or nonconjugated diene, optionally substituted with one or more hydrocarbyl groups, said X' having up to 40 carbon atoms and forming a π -complex with M.

More preferred coordination complexes used according to the present invention are complexes corresponding to the formula:



wherein:

R₁ and R₂ are hydrogen or C₁₋₆ alkyl, with the proviso that at least one of R₁ or R₂ is not hydrogen;

R₃, R₄, R₅, and R₆ independently are hydrogen or C₁₋₆ alkyl;

M is titanium;

Y is -NR^{**}-, -PR^{**}-;

Z^{*} is SiR^{*}₂, CR^{*}₂, SiR^{*}₂SiR^{*}₂, CR^{*}₂CR^{*}₂, CR^{*}=CR^{*}, CR^{*}₂SiR^{*}₂, or GeR^{*}₂;

R^{*} each occurrence is independently hydrogen, or a member selected from hydrocarbyl, hydrocarbyloxy, silyl, halogenated alkyl, halogenated aryl, and combinations thereof, said R^{*} having up to 20 non-hydrogen atoms, and optionally, two R^{*} groups from Z (when R^{*} is not hydrogen), or an R^{*} group from Z and an R^{*} group from Y form a ring system;

R^{**} is a aliphatic or alicyclic hydrocarbyl group covalently bonded to the nitrogen or phosphorus of Y via a primary or secondary carbon;

p is 0, 1 or 2;

q is zero or one;


with the proviso that:

when p is 2, q is zero, M is in the +4 formal oxidation state, and X is independently at each occurrence methyl or benzyl.

when p is 1, q is zero, M is in the +3 formal oxidation state, and X is 2-(N,N-dimethyl)aminobenzyl; or M is in the +4 formal oxidation state and X is 1,4-butadienyl, and

when p is 0, q is 1, M is in the +2 formal oxidation state, and X' is 1,4-diphenyl-1,3-butadiene or 1,3-pentadiene. The latter diene is illustrative of unsymmetrical diene groups that result in production of metal complexes that are actually mixtures of the respective geometrical isomers.

10 Preferred substituted indenecyl metal complexes correspond to the following formula:



wherein:

R' is hydrocarbonyl, di(hydrocarbonylamino), or a hydrocarbonyleneamino group, said R' having up to 20 carbon atoms,

15 R'' is C₁₋₂₀ hydrocarbyl or hydrogen;

M is titanium;

Y is -O-, -S-, -NR^{*}-, -PR^{*}-; -NR₂^{*}, or -PR₂^{*};

Z* is SiR*₂, CR*₂, SiR*₂SiR*₂, CR*₂CR*₂, CR*=CR*, CR*₂SiR*₂, or GeR*₂;

20 R* each occurrence is independently hydrogen, or a member selected from hydrocarbyl, hydrocarbyloxy, silyl, halogenated alkyl, halogenated aryl, and combinations thereof, said R* having up to 20 non-hydrogen atoms, and optionally, two R* groups from Z (when R* is not hydrogen), or an R* group from Z and an R* group from Y form a ring system;

X , X' and X'' are as previously defined:

p is 0, 1 or 2;

25 q is zero or 1; and

r is zero or 1;

The thermoplastic vulcanizates of the invention may include various additives, such as carbon black, silica, titanium dioxide, colored pigments, clay, zinc oxide, stearic acid, accelerators, vulcanizing agents, sulfur, stabilizers, antidegradants, processing aids, adhesives, tackifiers, plasticizers, wax, prevulcanization inhibitors, discontinuous fibers (such as wood cellulose fibers) and extender oils. Such additives may be provided either prior to, during, or subsequent to vulcanization.

As in the case of the thermoset elastomers of the invention, carbon black will preferably be added to the blend of the substantially random/pseudorandom interpolpolymer and polyolefin prior to vulcanization. Carbon black will typically be provided in an amount from 0 to 50 weight percent, typically from 0.5 to 50 weight percent, based on the total formulation weight. When the carbon black is employed to mask a color, it is typically employed in the range of 0.5 to 10 weight percent, based on the total weight of the formulation. When the carbon black is employed to increase toughness and/or decrease cost, it is typically employed in amounts greater than 10 weight percent, based on the total weight of the formulation.

Moreover, as in the case of the thermoset elastomers of the invention, one or more extender oils will preferably be added to the blend of the substantially random/pseudorandom interpolpolymer and polyolefin prior to vulcanization. Suitable extender oils are listed in Rubber World Blue Book 1975 Edition, Materials and Compounding Ingredients for Rubber, pages 145-190. Typical classes of extender oils include aromatic, naphthenic, and paraffinic extender oils. The extender oil(s) will typically be provided in an amount from 0 to 50 weight percent based on the total formulation weight. When employed, the extender oil will typically be provided in an amount of at least 5 weight percent, more typically in an amount of from 15 to 25 weight percent, based on the total weight of the formulation.

In one preferred embodiment, the thermoplastic vulcanizates of the invention will comprise from 30 to 60 weight percent of the substantially random/pseudorandom interpolpolymer, from 15 to 55 weight percent of the thermoplastic polyolefin, and from 15 to 30 weight percent of the extender oil. Such thermoplastic vulcanizates are particularly useful as moldings for automotive applications.

In a particularly preferred embodiment, the thermoplastic vulcanizates of the invention are characterized by an ASTM #2 oil swell of less than 60 percent, as determined by ASTM D-471.

Test Procedures

Monomer contents are determined by carbon-13 NMR spectroscopy.

Stress-strain properties are determined on an Instron model 1122 load frame using 0.870 inch (2.2 cm) micro-tensile samples measured at an extension rate of 5 inch/min (12.7 cm/min). Tensile break, elongation at break, and 100 percent modulus are measured in accordance with ASTM D-412.

Melt index is measured in accordance with ASTM D-1238.

Molecular weight and molecular weight distribution are determined by gel permeation chromatography.

ASTM #2 and #3 oil swells are measured in accordance with ASTM D-471.

Hardness shore "A" is measured in accordance with ASTM D-2240.

Compression set is measured in accordance with ASTM D-395.

Example One: Preparation of Ethylene-Styrene Interpolymers and Thermoset Elastomers

5 Ethylene/styrene copolymers were made using (tert-butylamido)dimethyl(tetramethyl- η 5-cyclopenta-dienyl)silane dimethyltitanium(+4) catalyst and tris(pentafluorophenyl)borane cocatalyst in a one to one ratio according to the following procedure. A two liter reactor was charged with 360 grams (500 mL) of ISOPAR™ E mixed alkane solvent (available from Exxon Chemicals Inc.) and the desired amount of styrene comonomer. Hydrogen was added to the reactor by differential pressure expansion
10 from a 75 mL addition tank. The reactor was heated to the run temperature and was saturated with ethylene at the desired pressure. (Tert-butylamido)dimethyl-(tetramethyl- η 5-cyclopentadienyl)silane dimethyltitanium (IV) catalyst and tris(pentafluorophenyl)borane cocatalyst were mixed in a dry box by pipeting the desired amount of a 0.005 M solution of the tris(pentafluorophenyl)borane cocatalyst in ISOPAR™ E mixed alkane solvent or toluene into a solution of the (tert-butylamido)dimethyl-
15 (tetramethyl- η 5-cyclopentadienyl)silane dimethyl-titanium (IV) catalyst in ISOPAR™ E mixed alkane solvent or toluene. The resulting catalyst solution was transferred to a catalyst addition tank and was injected into the reactor.

The polymerization was allowed to proceed, with ethylene being introduced on demand. Additional charges of catalyst and cocatalyst, if used, were prepared in the same manner and were added
20 to the reactor periodically. The total amount of catalyst employed was set forth in Table One. In each instance, the amount of tris(pentafluorophenyl)borane cocatalyst (on a molar basis) equals the amount of (tert-butylamido)dimethyl-(tetramethyl- η 5-cyclopentadienyl)silane dimethyltitanium (IV) catalyst indicated in Table One. After the run time, the polymer solution was removed from the reactor and quenched with isopropyl alcohol. A hindered phenol antioxidant (IRGANOX™ 1010 (available from
25 Ciba Geigy Corp.) was added to the polymer. Volatiles were removed from the polymer in a reduced pressure vacuum oven at 135°C for 20 hours.

The preparation conditions for the substantially random interpolymers were set forth in Table 1.

Sample	Catalyst amount $\mu(-mol)$	ISOPAR™ -E (mL)	Styrene (mL)	Ethylene (psig)	Hydrogen (Δ psi)	Reaction Temp (°C)	Reaction Time (min)	Yield (g)
ES-1	2.5	250	750	300	0	80	10	32.3
ES-2	3.8	500	500	200	0	80	10	28.8
ES-3	15.0	500	500	200	100	60	30	166

The resultant substantially random interpolymers were characterized as being pseudorandom and linear.

30 The interpolymers were compounded and cured according to the following procedure. The 60 gram bowl of a Brabender PS-2 internal mixer was preheated to 120°F. 100 pph carbon black N550 (available from Cabot Corporation), 50 pph SUNPAR™ 2280 oil (available from Sun Oil), 5 pph

paraffin wax, 1 pph stearic acid, 8 pph Vul-Cup 40KE peroxide (available from Hercules) and 1.5 pph triallyl cyanurate coagent (available from American Cyanamid) were premixed in a plastic or paper container. The resultant blend was loaded into the 60 gram bowl. To the bowl was further added 100 pph of the desired substantially random/pseudorandom interpolymers as prepared above. The ram was lowered on the internal mixer, and the compound was allowed to mix until a temperature of 220°F was reached (approximately five minutes). The compound was removed from the mixer and was optionally roll-milled.

The samples were compression molded at 260°F to obtain uncured (green) test plaques. The uncured (green) test plaques were compression mold cured at 340°F for 20 minutes to obtain crosslinked thermoset elastomer compositions.

The stress-strain properties of the neat interpolymers, of the uncured (green) test plaques, and of the crosslinked thermoset elastomer compositions were set forth in Table Two. Therein, the designation "ND" means that the given property was not determined.

	ES-1	ES-2	ES-3	C1 (Tafmer 680-P)	C2 (V-457)	C3 (V-707)
COMONOMER CONTENT (AS DIRECTED BY NMR)						
wt % ethylene	67.5	56.8	48.0		51.0	70.0
wt % styrene	32.5	43.2	52.0		0	0
wt % propylene	0	0	0		49.0	30.0
STRESS-STRAIN PROPERTIES OF NEAT UNCROSSLINKED POLYMERS						
tensile at break (psi)	3200	2156	1390	668	243	887
100% modulus (psi)	759	445	256	170	75	205
elongation at break (%)	395	420	518	1115	1780	1336
melt index at 190°C (g/10 min)	0.8	0.8	10.2	4.0	7.1	3.9
Mw/Mn	2.07	2.14	3.50	21.8	3.07	4.59
GREEN STRESS-STRAIN PROPERTIES						
tensile at break (psi)	ND	ND	594	460	70	459
100% modulus (psi)	ND	ND	315	264	52	231
elongation at break (%)	ND	ND	453	476	84	685
STRESS-STRAIN PROPERTIES OF CROSSLINKED INTERPOLYMERS						
tensile at break (psi)	3156	ND	1005	1994	1236	1569
100% modulus (psi)	1076	ND	532	506	276	674
elongation at break (%)	300	ND	297	383	409	292

As illustrated in Table Two, the crosslinked thermoset elastomer compositions of the invention exhibit a higher 100 % modulus than the comparative materials C1 (Tafmer™ 680-P (available from

Mitsui Petrochemical)) and C2 (Vistalon™ 457 (available from Exxon Chemical Co.)). This was consistent with the significantly higher 100 % modulus exhibited by the neat interpolymers as compared to the comparative materials.

Example Two: Preparation of Ethylene/Styrene/Ethylidene Norbornene Interpolymers and Thermoset Elastomers

Ethylene/styrene/ethylidene norbornene interpolymers were made using (tert-butylamido)dimethyl(tetramethyl- η 5-cyclopenta-dienyl)silane dimethyltitanium(+4) catalyst and tris(pentafluorophenyl)borane cocatalyst in a one to one ratio according to the following procedure. A two liter reactor was charged with 360 grams (500 mL) of ISOPAR™ E mixed alkane solvent (available from Exxon Chemicals Inc.) and the desired amount of styrene comonomer. Ethylidene norbornene was transferred to the reactor. Hydrogen was added to the reactor by differential pressure expansion from a 75 mL addition tank. The reactor was heated to the run temperature and was saturated with ethylene at the desired pressure. (Tert-butylamido)dimethyl-(tetramethyl- η 5-cyclopentadienyl)silane dimethyltitanium (IV) catalyst and tris(pentafluoro-phenyl)borane cocatalyst were mixed in a dry box by pipeting the desired amount of a 0.005 M solution of the tris(pentafluorophenyl)borane cocatalyst in ISOPAR™ E mixed alkane solvent or toluene into a solution of the (tert-butylamido)dimethyl-(tetramethyl- η 5-cyclopentadienyl)silane dimethyl-titanium (IV) catalyst in ISOPAR™ E mixed alkane solvent or toluene. The resulting catalyst solution was transferred to a catalyst addition tank and was injected into the reactor.

The polymerization was allowed to proceed, with ethylene being introduced on demand. Additional charges of catalyst and cocatalyst, if used, were prepared in the same manner and were added to the reactor periodically. The total amount of catalyst employed was reported in Table Three. In each instance, the amount of tris(pentafluoro-phenyl)borane cocatalyst (on a molar basis) was equal to that of the (tert-butylamido)dimethyl-(tetramethyl- η 5-cyclopentadienyl)silane dimethyltitanium (IV) catalyst as indicated in Table Three. After the run time, the polymer solution was removed from the reactor and quenched with isopropyl alcohol. A hindered phenol antioxidant (IRGANOX™ 1010 (available from Ciba Geigy Corp.) was added to the polymer. Volatiles were removed from the polymer in a reduced pressure vacuum oven at 135°C for 20 hours.

The preparation conditions for the ethylene/styrene/ethylidene norbornene interpolymers were set forth in Table Three.

Sample	Catalyst amount (-mol)	ISOPAR -E (mL)	Styrene (mL)	ENB amount (mL)	Ethylene pressure (psig)	Hydrogen (psi)	Reaction Temp (C)	Reaction Time (min)	Yield (g)
ES-1	15	500	500	50	250	100	65	20	149.9
ES-2	12.5	500	500	75	300	100	65	30	120.7
ES-3	10	500	500	25	200	100	65	30	135.1

The resultant substantially random interpolymers were characterized as being pseudorandom and linear.

The interpolymers were compounded and cured according to the following procedure. The 60 gram bowl of a Brabender PS-2 internal mixer was preheated to 120°F. 100 pph carbon black N550 (available from Cabot), 50 pph SUNPARTM 2280 oil (available from Sun Oil), 5 pph paraffin wax, 1 pph stearic acid, 5 pph zinc oxide, 1.5 pph sulfur, and 0.5 pph Captax 2-mercaptobenzothiazole (available from R. T. Vanderbilt) were premixed in a plastic or paper container. The resultant blend was loaded into the 60 gram bowl. To the bowl was further added 100 pph of the desired interpolymers as prepared above. The ram was lowered on the internal mixer, and the compound was allowed to mix until a temperature of 220°F was reached (approximately five minutes). The compound was removed from the mixer and was optionally roll-milled.

The samples were compression molded at 260°F to obtain uncured (green) test plaques. The uncured (green) test plaques were compression mold cured at 340°F for 20 minutes to obtain crosslinked thermoset elastomer compositions.

As between ESDM1(a)-(d), ESDM1(a) was prepared in accordance with the above formulation. ESDM1(b)-(d) were likewise prepared in accordance with the above formulation, except that in the case of ESDM1(b), 50 pph SUNDEX 750T oil (available from Sun Oil), was used in place of the SUNPAR oil; in the case of ESDM1(c), 50 pph trioctyltrimellitate was used in place of the SUNPAR oil; and in the case of ESDM1(d), 0.75 pph (rather than 1.5 pph) sulfur was employed.

Regarding the comparative materials, C4 was prepared using the formulation provided above, with Vistalon 6505 EPDM (available from Exxon) being used in place of the substantially random/pseudorandom interpolymers. C5 was prepared using the formulation provided above, with EPSyn 70A EPDM (available from DSM Copolymer) being used in place of the substantially random/pseudorandom interpolymers used in the present invention. C6(a) was prepared using the formulation provided above, with SBR 1500 styrene butadiene rubber being used in place of the substantially random/pseudorandom interpolymers and Sundex 750T oil (available from Sun Oil) being used in place of the SUNPAR oil. C6(b) was prepared using the formulation provided above, except that SBR 1500 styrene butadiene rubber was used in place of the substantially random/pseudorandom interpolymers, 50 pph (rather than 100 pph) N550 carbon black was employed, 7 pph Sundex 750T oil (rather than 50 pph SUNPAR 2280 oil) was employed.

The stress-strain properties of the neat interpolymers, of the uncured (green) test plaques, and of the crosslinked thermoset elastomer compositions were set forth in Table Four. Therein, the abbreviation "ND" means that a given property was not determined.

	ESDM-1	ESDM-2	ESDM-3	C4	C5	C6
COMONOMER CONTENT AS DETERMINED BY (C- NMR)						
wt % ethylene	50.9	46.7	49.4	50	50	0
wt % styrene	35.3	43.7	44	0	0	24
wt % diene	13.8	9.6	6.6	12	10	0
wt % propylene		0	0	38	40	0
wt % butadiene		0	0	0	0	76
STRESS-STRAIN PROPERTIES OF NEAT UNCROSSLINKED INTERPOLYMERS						
tensile at break (psi)	1884	1345	1021	83	80	31
100% modulus (psi)	319	212	242	81	75	30
elongation at break (%)	513	566	505	288	300	>400
melt index (g/10min)	1.6	8.0	4.6	<2.0	<0.5	ND
GREEN STRESS- STRAIN PROPERTIES	a b c d	ND	ND	ND	ND	a b
tensile at break (psi)	869 723 859 932	ND	ND	78	80	3 61
100% modulus (psi)	570 457 606 469	ND	ND	32	67	14 51
elongation at break (%)	338 395 276 369	ND	ND	250	130	2129 300
STRESS-STRAIN AND OIL RESISTANCE PROPERTIES COMPOUNDED CROSS-LINKED INTERPOLYMERS	a b c d					a b
tensile at break (%)	2379 2279 2451 2033	ND	ND	2044	2399	1575 1475
100% modulus	1455 1395 1539 1018	ND	ND	598	533	295 386
elongation at break (%)	188 219 183 246	ND	ND	318	401	277 392
ASTM #2 oil swell (70 hours @ 212°F)	54 55 54 62	ND	ND	93	100	57 49
STRESS STRAIN PROPERTIES AFTER AN OVEN AGING FOR 70 HOURS AT 250°F	a b c d					a b
tensile at break (psi)	2697 2907 ND 2507	ND	ND	ND	ND	663 1352
100% modulus (psi)	2143 ND ND 1401	ND	ND	ND	ND	ND 1326
elongation at break (%)	34 84 ND 199.6	ND	ND	ND	ND	93 103
PERCENT CHANGE IN STRESS-STRAIN PROPERTIES AFTER OVEN AGING 70 HOURS AT 250°F	a b c d					a b
tensile at break (%)	+15 +28 ND +24	ND	ND	ND	ND	-58 -8
100% modulus (%)	-47 ND ND +38	ND	ND	ND	ND	ND +378
elongation at break (%)	-29 -62 ND -19	ND	ND	ND	ND	-76 -74

As illustrated in Table Four, the crosslinked thermoset elastomers of the invention typically exhibit a highly improved 100% modulus, as compared to comparative materials C4 (VistalonTM 6505 EPDM (available from Exxon)), C5 (EPSyn 70A EPDM (available from DSM Copolymer)) and C6 (SBR 1500 styrene-butadiene rubber).

5 As further illustrated in Table Four, the crosslinked thermoset elastomers of the invention typically exhibit a resistance to oil swell similar to that of styrene-butadiene-rubber, but superior to that of EPDM materials.

As further illustrated in Table Four, the crosslinked thermoset elastomers of the invention exhibit aging properties superior to those of styrene-butadiene rubber. For instance, upon aging at 250°F
10 for 70 hours in an air oven, the crosslinked ethylene/styrene/ethylidene norbornene interpolymer exhibited increased tensile at break values and moderately decreased elongation at break values. In contrast, upon oven aging under the same conditions, the styrene-butadiene rubbers exhibited decreased tensile at break values and significantly decreased elongation at break values.

Thus, as illustrated in Table Four, the crosslinked ethylene/styrene/diene thermoset elastomers
15 of the invention exhibit a resistance to oil swell characteristic of styrene-butadiene rubber without suffering the concomitant negative effects of heat aging.

Example Three: Preparation of Thermoplastic Vulcanizates

The Brabender PS-2 or Haake internal torque mixer was preheated to 350°C. The desired
20 amount of Pro-fax 6524 isotactic polypropylene (available from Himont Incorporated) was added to the mixer, and was allowed to melt and to homogenize. Over one minute, the desired amount of the noncrosslinked substantially random/pseudorandom interpolymer was added. Thereafter, the process oil, antioxidant, stearic acid, and carbon black were added and mixed for one minute. The zinc oxide, sulfur, benzothiazyl disulfide and methyl tuads were added. Mixing occurs until the torque reaches a maximum and for at least 10 minutes total mix time. The resultant thermoplastic vulcanizate was
25 removed from the mixer.

In executing the above procedure, the formulations set forth in Table Five were employed. Unless otherwise indicated, all amounts were expressed in parts per hundred, based on 100 parts of the elastomer.

BEST AVAILABLE COPY

Elastomer	TPV-1	TPV-2				C-TPV-1	C-TPV-2
	ESDM-2	ESDM-3				C-4	C-5
wt % ethylene	46.7	49.4				50	50
wt % styrene	43.7	44				0	0
wt % diene	9.6	6.6				12	10
wt % propylene	0	0				38	40
TPV formulation (all amounts in ppb)		A	B	C	D		
Substantially random interpolymers	100	100	100	100	100	100	100
isotactic polypropylene	67	67	33	67	100	67	67
process oil	50	50	100	100	100	50	50
IRGANOX 1010 antioxidant (available from Ciba Geigy Corp.)	3	3	3	3	3	3	3
stearic acid	1	1	1	1	1	1	1
N550 carbon black available from Cabot	1	1	1	1	1	1	1
zinc oxide	5	5	5	5	5	5	5
sulfur	1.5	1.5	1.5	1.5	1.5	1.5	1.5
benzothiazyl disulfide (available from Altax)	0.38	0.38	0.38	0.38	0.38	0.38	0.38
methyl tuads	0.75	0.75	0.75	0.75	0.75	0.75	0.75

Except in the case of TPV1(b), SunPar™ 2280 (available from Sun Oil) was employed as the process oil. For TPV1(b), trioctyltrimellitate was employed as the process oil.

- 5 The resultant thermoplastic vulcanizates were compression molded at 380°F. Representative physical properties of the thermoplastic vulcanizates and of comparative thermoplastic vulcanizates C-TPV1 (made with Vistalon 6505 EPDM (available from Exxon)) and C-TPV2 (made with EPSyn 70A EPDM (available from DSM Rubber)) were set forth in Table Six. Therein, the abbreviation "ND" means that a given property was not determined.

	TPV 1		TPV 2				C-TPV-1	C-TPV-2
Stress-Strain properties	A	B	A	B	C	D		
tensile at break (psi)	1507	1589	1621	515	1549	1436	1520	1787
100% modulus (psi)	1375	1307	951	327	691	1008	759	889
elongation at break (%)	132	164	251	192	336	247	322	344
ASTM #2-70 hours at 212°F (% swell)	ND	ND	109.5	133.8	89.3	68.2	ND	ND
Hardness Shore "A"	88	86	86	63	77	83	90	88

- 10 A comparison of TPV1(a) and TPV2(a) with comparative materials C-TPV1 (made with Vistalon 6505 EPDM (available from Exxon)) and C-TPV2 (made with EPSyn 70A EPDM (available from DSM Rubber)) indicates that the thermoplastic vulcanizates of the invention exhibit a much greater resistance to oil swell (under the ASTM #2 test method) than the comparative materials without sacrificing hardness (Hardness Shore "A"). A comparison of these materials further indicates that the

thermoplastic vulcanizates of the invention exhibit improved 100% modulus values and comparable tensile at break values, with respect to the comparative materials.

5 A comparison of TPV-2(b), TPV-2(c), and TPV-2(d) indicates that one can adjust resistance to ASTM #2 oil swell and hardness values by adjusting the ratio between the polypropylene and the substantially random/pseudorandom interpolmer. Namely, as the proportion of the polypropylene increases, the resistance to ASTM #2 oil swell and hardness likewise increase. Moreover, the effect of the added substantially random/pseudorandom interpolmer was evident. In particular, the percent elongation at break of the inventive thermoplastic vulcanizates was many times greater than that of unmodified isotactic polypropylene, which exhibits a percent elongation at break of 13 percent.

10 The thermoset elastomers of the invention were useful in a variety of applications. Exemplary applications include hoses, air ducts, brake cups, roofing materials, as well as use as components in blends as impact modifiers and in general molded goods.

The thermoplastic vulcanizates were likewise useful in a variety of applications, particularly articles made by extrusion, injection molding and compression molding techniques. One principal application for the TPVS of the invention was in automotive under-the-hood components, such as rack-and-pinion boots and ducting, fuel-line covers, hoses, belts, and gaskets. Other expected automotive applications were in interior applications (such as skins, instrument panels, air-bag covers, door trim, control knobs, molded parts, and seat belt covers) and exterior applications (such as tires and molding).

BEST AVAILABLE COPY

CLAIMS

1. A thermoset elastomer comprising either

(1) a crosslinked pseudorandom interpolpolymer of:

- (a) from 15 to 70 weight percent of at least one α -olefin,
- 5 (b) from 30 to 70 weight percent of at least one vinylidene aromatic compound, and
- (c) from 0 to 15 weight percent of at least one diene; or (2) a crosslinked substantially random interpolpolymer of:

- (a) from 15 to 70 weight percent of at least one α -olefin,
- (b) from 30 to 70 weight percent of at least one vinylidene aromatic compound, and
- 10 (c) from 0 to 15 weight percent of at least one diene.

2. The thermoset elastomer of Claim 1 comprising either

(1) a crosslinked pseudorandom interpolpolymer of

- (a) from 25 to 60 weight percent of at least one α -olefin,
- 15 (b) from 35 to 60 weight percent of at least one vinylidene aromatic compound, and
- (c) from 3 to 15 weight percent of at least one diene, or

(2) a crosslinked substantially random interpolpolymer of

- (a) from 25 to 60 weight percent of at least one α -olefin,
- (b) from 35 to 60 weight percent of at least one vinylidene aromatic compound, and
- 20 (c) from 3 to 15 weight percent of at least one diene, or

(2) a crosslinked substantially random interpolpolymer of.

3. The thermoset elastomer of Claim 1 comprising either (1) a crosslinked pseudorandom interpolpolymer of:

- 25 (a) from 40 to 65 weight percent of at least one α -olefin selected from the group consisting of ethylene, propylene, 1-butene, 3-methyl-1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 1-dodecene, 3-phenylpropene, and mixtures thereof; and

- (b) from 35 to 60 weight percent of at least one vinylidene aromatic compound selected from
30 the group consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, and divinylbenzene, and mixtures thereof; or

(2) a crosslinked substantially random interpolpolymer of:

- (a) from 40 to 65 weight percent of at least one α -olefin selected from the group consisting of
35 ethylene, propylene, 1-butene, 3-methyl-1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene,

5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 1-dodecene, 3-phenylpropene, and mixtures thereof; and

- (b) from 35 to 60 weight percent of at least one vinylidene aromatic compound selected from the group consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, and divinylbenzene, and mixtures thereof.

4. The thermoset elastomer of Claim 1, 2, or 3 wherein

- (a) the α -olefin is selected from the group consisting of ethylene, propylene, 1-butene, 3-methyl-1-butene, 1-pentene, 4-methyl-1-pentene, 1-hexene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 1-dodecene, 3-phenylpropene, and mixtures thereof;
- (b) the vinylidene aromatic compound is selected from the group consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, and divinylbenzene, and mixtures thereof; and
- (c) the diene, when present, is selected from the group consisting of butadiene, 1,3-pentadiene, 1,4-pentadiene, isoprene, 1,4-hexadiene, 7-methyl-1,6-octadiene, dicyclopentadiene, methylenenorbornene, ethylenenorbornene, and methyltetrahydroindene, and mixtures thereof.

5. The thermoset elastomer of Claim 4, wherein the α -olefin is ethylene, the vinylidene aromatic compound is styrene, and the diene, when present, is ethylenenorbornene.

6. A process for preparing a thermoset elastomer comprising:

- (a) reacting at least one α -olefin with at least one vinylidene aromatic compound and optionally at least one diene, in the presence of a constrained geometry catalyst, to form a pseudorandom interpolpolymer;
- (b) curing the pseudorandom interpolpolymer to form a thermoset elastomer.

7. The process of Claim 6, wherein the constrained geometry catalyst comprises a metal coordination complex comprising a metal of Group III or IV or the Lanthanide series of the Periodic Table of the Elements and a delocalized Π -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry the metal atom such that the angle at the metal between the centroid of the delocalized, substituted Π -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex containing a similar Π -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted π -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted Π -bonded moiety.

8. The process of Claim 6, wherein the constrained geometry catalyst is selected from the group consisting of (tert-butylamido)(tetramethyl- η 5-cyclopentadienyl)-1,2-ethanediylzirconium dichloride; (tert-butylamido) (tetramethyl- η 5-cyclopentadienyl)-1,2-ethanediyltitanium dichloride; (tert-butylamido)dimethyl(tetramethyl- η 5-cyclopentadienyl) silanetitanium dimethyl; (tert-
 5 butylamido)dimethyl(tetramethyl- η 5-indenyl) silanetitanium dimethyl; (tert-butylamido)dimethyl(tetramethyl- η 5-tetrahydroindenyl) silanetitanium dimethyl; (tert-butylamido)dimethyl(tetramethyl- η 5-fluorenyl) silanetitanium dimethyl; (tert-butylamido)dimethyl(tetramethyl- η 5-tetrahydrofluorenyl) silanetitanium dimethyl; (tert-butylamido)dimethyl(tetramethyl- η 5-octahydrofluorenyl) silanetitanium dimethyl; (tert-
 10 butylamido)dimethyl(tetramethyl- η 5-cyclopentadienyl) silanetitanium dibenzyl; (tert-butylamido)dimethyl (tetramethyl- η 5-cyclopentadienyl)silanezirconium dibenzyl; and mixtures thereof.

9. The process of Claim 7, wherein the constrained geometry catalyst is activated by a cocatalyst selected from the group consisting of polymeric alumoxanes, oligomeric alumoxanes,
 15 polymeric carbylboranes, oligomeric carbylboranes, monomeric carbylboranes, aluminum alkyls, aluminum halides, haloaluminum alkyls, substituted ammonium salts, silver salts, ferrocenium ions, and mixtures thereof.

10. The process of Claim 7, wherein the constrained geometry catalyst is activated by
 20 tris(pentafluorophenyl)borane.

11. The process Claim 6, wherein the curing is effected by a curing agent selected from the group consisting of peroxides, phenols, azides, aldehyde-amine reaction products, substituted ureas, substituted guanidines, substituted xanthates, substituted dithiocarbamates, thiazoles, imidazoles,
 25 sulfenamides, thiuramidisulfides, paraquinonedioxime, dibenzoparaquinonedioxime, and sulfur.

12. The process of Claim 6, wherein the curing is effected by a curing agent selected from the group consisting of peroxides, phenols, substituted dithiocarbamates, thiazoles, imidazoles, sulfenamides, thiuramidisulfides, sulfur and mixtures thereof and sulfur.
 30

13. The process of Claim 6, wherein the curing is effected simultaneously with the compounding of the pseudorandom interpolymers.

14. A process for preparing a thermoset elastomer comprising:

- (a) reacting at least one α -olefin with at least one vinylidene aromatic compound and optionally at least one diene, in the presence of a constrained geometry catalyst, to form a substantially random interpolpolymer;
- (b) curing the substantially random interpolpolymer to form a thermoset elastomer.

5

15. The process of Claim 6,7, 8, 9, 10, 11, 12, 13 or 14, wherein

- (i) the α -olefin is selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 3-phenylpropene, and mixtures thereof;
- 10 (ii) the vinylidene aromatic compound is selected from the groups consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, divinylbenzene, and mixtures thereof; and
- (iii) the diene, when present, is selected from the group consisting of butadiene, 1,3-pentadiene, 1,4-pentadiene, isoprene, 1,4-hexadiene, 7-methyl-1,6-octadiene, dicyclopentadiene,
- 15 methylenenorbornene, ethylenenorbornene, and mixtures thereof.

16. A thermoplastic vulcanizate comprising:

- (a) a crosslinked pseudorandom interpolpolymer of
 - (i) from 15 to 70 weight percent of at least one α -olefin,
 - 20 (ii) from 30 to 70 weight percent of at least one vinylidene aromatic compound, and
 - (iii) from 0 to 15 weight percent of at least one diene; and
- (b) at least one thermoplastic polyolefin.

17. The thermoplastic vulcanizate of Claim 16, comprising from 10 to 90 weight percent of the crosslinked pseudorandom interpolpolymer and from 10 to 90 weight percent of the thermoplastic polyolefin.

18. The thermoplastic vulcanizate of Claim 16, further comprising from 0 to 50 weight percent of an extender oil selected from the group consisting of aromatic oils, naphthenic oils, and paraffinic oils.

19. The thermoplastic vulcanizate of Claim 16, wherein the crosslinked pseudorandom interpolpolymer is an interpolpolymer of (a) from 40 to 65 weight percent of at least one α -olefin, and (b) from 35 to 60 weight percent of at least one vinylidene aromatic compound.

35

20. The thermoplastic vulcanizate of Claim 18, wherein the crosslinked pseudorandom interpolmer is an interpolmer of (a) from 25 to 60 weight percent of at least one α -olefin, (b) from 35 to 60 weight percent of at least one vinylidene aromatic compound, and (c) from 3 to 15 weight percent of at least one diene.

5

21. The thermoplastic vulcanizate of Claim 16, comprising from 30 to 60 weight percent of the crosslinked pseudorandom interpolmer, from 15 to 55 weight percent of the thermoplastic polyolefin, and from 15 to 30 weight percent of the extender oil.

10

22. A thermoplastic vulcanizate comprising:

(a) a crosslinked substantially random interpolmer of

(i) from 15 to 70 weight percent of at least one α -olefin,

(ii) from 30 to 70 weight percent of at least one vinylidene aromatic compound, and

(iii) from 0 to 15 weight percent of at least one diene; and

15 (b) at least one thermoplastic polyolefin.

23. The thermoplastic vulcanizate of Claim 16, 17, 18, 19, 20, 21 or 22, wherein:

(a) the α -olefin is selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 3-phenylpropene, and mixtures thereof;

20

(b) the vinylidene aromatic compound is selected from the group consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, divinylbenzene, and mixtures thereof; and

(c) the optional diene is selected from the group consisting of butadiene, 1,3-pentadiene, 1,4-pentadiene, isoprene, 1,4-hexadiene, 7-methyl-1,6-octadiene, dicyclopentadiene, methylenenorbornene, ethylenenorbornene, methyltetrahydroindene, and mixtures thereof.

25

24. The thermoplastic vulcanizate of Claim 23, wherein the thermoplastic polyolefin is selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 2-methyl-1-propene, 3-methyl-1-pentene, 4-methyl-1-pentene, 5-methyl-1-hexene, and mixtures thereof.

30

25. The thermoplastic vulcanizate of Claim 23, wherein the α -olefin is ethylene, the vinylidene aromatic compound is styrene, and the diene, when present, is ethylenenorbornene.

35

26. The thermoplastic vulcanizate of Claim 24, wherein the α -olefin is ethylene, the vinylidene aromatic compound is styrene, and the diene, when present, is ethylenenorbornene.

27. A thermoplastic vulcanizate comprising a crosslinked substantially random
interpolymer of at least one α -olefin, at least one vinylidene aromatic compound and optionally at least
one diene distributed in a thermoplastic polyolefin matrix, said thermoplastic vulcanizate being
5 characterized by an ASTM #2 oil swell of less than 60 percent, as determined by ASTM D-471.

28. A process for making a thermoplastic vulcanizate comprising:
- (a) reacting at least one α -olefin with at least one vinylidene aromatic compound and optionally at
least one diene in the presence of a constrained geometry catalyst to form a pseudorandom
10 interpolymer;
 - (b) intimately mixing the pseudorandom interpolymer with at least one thermoplastic polyolefin at a
temperature above the melting or softening point of the thermoplastic polyolefin;
 - (c) providing to the intimate mixture an agent for curing the pseudorandom interpolymer;
 - (d) simultaneously curing the pseudorandom interpolymer and compounding the intimate mixture to
15 form a thermoplastic vulcanizate.

29. The process of Claim 28, wherein
- (i) the α -olefin is selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-
hexene, 4-methyl-1-pentene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 3-phenylpropene,
20 and mixtures thereof;
 - (ii) the vinylidene aromatic compound is selected from the group consisting of styrene, α -
methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene,
vinylbenzocyclobutane, divinylbenzene, and mixtures thereof; and
 - (iii) the optional diene is selected from the group consisting of butadiene, 1,3-pentadiene, 1,4
25 pentadiene, isoprene, 1,4-hexadiene, 7-methyl-1,6-octadiene, dicyclopentadiene,
methylenenorbornene, ethylenenorbornene, methyltetrahydroindene, and mixtures thereof.

30. The process of Claim 28, wherein the thermoplastic polyolefin is selected
from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 2-methyl-1-propene, 3-
30 methyl-1-pentene, 4-methyl-1-pentene, 5-methyl-1-hexene, and mixtures thereof.

31. The process of Claim 28, wherein the agent for curing the substantially
random interpolymer is selected from the group consisting of peroxides, phenols, azides, aldehyde-
amine reaction products, substituted ureas, substituted guanidines, substituted xanthates, substituted
35 dithiocarbamates, thiazoles, imidazoles, sulfenamides, thiuramidisulfides, paraquinonedioxime,
dibenzoparaquinonedioxime, sulfur, and mixtures thereof.

32. The process of Claim 28, 29, 30 or 31, wherein the constrained geometry catalyst comprises a metal coordination complex comprising a metal of Group III or IV or the Lanthanide series of the Periodic Table of the Elements and a delocalized Π -bonded moiety substituted with a constrain-inducing moiety, said complex having a constrained geometry the metal atom such that the angle at the metal between the centroid of the delocalized, substituted Π -bonded moiety and the center of at least one remaining substituent is less than such angle in a similar complex containing a similar Π -bonded moiety lacking in such constrain-inducing substituent, and provided further that for such complexes comprising more than one delocalized, substituted π -bonded moiety, only one thereof for each metal atom of the complex is a cyclic, delocalized, substituted Π -bonded moiety.

33. The process of Claim 32, wherein the constrained geometry catalyst is activated by a cocatalyst selected from the group consisting of polymeric alumoxanes, oligomeric alumoxanes, polymeric carbylboranes, oligomeric carbylboranes, monomeric carbylboranes, aluminum alkyls, aluminum halides, haloaluminum alkyls, ammonium salts, silver salts, ferrocenium ions, and mixtures thereof.

34. A process for making a thermoplastic vulcanizate comprising:

- (a) reacting at least one α -olefin with at least one vinylidene aromatic compound and optionally at least one diene in the presence of a constrained geometry catalyst to form a substantially random interpolpolymer;
- (b) intimately mixing the substantially random interpolpolymer with at least one thermoplastic polyolefin at a temperature above the melting or softening point of the thermoplastic polyolefin;
- (c) providing to the intimate mixture an agent for curing the substantially random interpolpolymer;
- (d) simultaneously curing the substantially random interpolpolymer and compounding the intimate mixture to form a thermoplastic vulcanizate.

35. A fabricated part comprising a crosslinked pseudorandom interpolpolymer of:

- (a) from 15 to 70 weight percent of at least one α -olefin selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 3-phenylpropene, and mixtures thereof;
- (b) from 30 to 70 weight percent of at least one vinylidene aromatic compound selected from the groups consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, divinylbenzene, and mixtures thereof;
- (c) from 0 to 15 weight percent of at least one diene selected from the group consisting of butadiene, 1,3-pentadiene, 1,4-pentadiene, isoprene, 1,4-hexadiene, 7-methyl-1,6-octadiene,

dicyclopentadiene, methylenenorbornene, ethylenenorbornene, methyltetrahydroindene, and mixtures thereof.

36. A fabricated part comprising a thermoplastic vulcanizate comprising
- 5 (a) from 10 to 90 weight percent of a crosslinked substantially random interpolmer of
- (i) from 15 to 70 weight percent of at least one α -olefin selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 5-methyl-1-hexene, 4-ethyl-1-hexene, 1-octene, 3-phenylpropene, and mixtures thereof;
- 10 (ii) from 30 to 70 weight percent of at least one vinylidene aromatic compound selected from the groups consisting of styrene, α -methylstyrene, ortho-methylstyrene, meta-methylstyrene, para-methylstyrene, chlorostyrene, vinylbenzocyclobutane, divinylbenzene, and mixtures thereof; and
- (iii) from 0 to 15 weight percent of at least one diene selected from the group consisting of butadiene, 1,3-pentadiene, 1,4-pentadiene, isoprene, 1,4-hexadiene, 7-methyl-1,6-octadiene, 15 dicyclopentadiene, methylenenorbornene, ethylenenorbornene, methyltetrahydroindene, and mixtures thereof; and
- (b) from 10 to 90 weight percent of at least one thermoplastic polyolefin selected from the group consisting of ethylene, propylene, 1-butene, 1-pentene, 1-hexene, 2-methyl-1-propene, 3-methyl-1-pentene, 4-methyl-1-pentene, 5-methyl-1-hexene, and mixtures thereof.

INTERNATIONAL SEARCH REPORT

International application No.

PC1/US 95/09945

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C08F 212/00, C08F 210/00, C08L 23/02, C08L 25/02 // C08F 4/602, 4/74
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, PAJ, WPI, CLAIMS, CAPLUS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP, A1, 0634427 (MITSUI PETROCHEMICAL INDUSTRIES, LTD.), 18 January 1995 (18.01.95), page 3, line 33 - line 37; page 19, line 4 - line 55, claims 1-5, 9	1-36
Y	--	16-34, 36
X	WO, A1, 9406858 (THE DOW CHEMICAL COMPANY), 31 March 1994 (31.03.94), page 5, line 30 - page 6, line 2; page 6, line 19 - line 26; page 11, line 13 - line 27; page 12, line 20; claim 11; abstract	1-15, 35
	--	

☒ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

- * Special categories of cited documents:
- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed
- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- * "&" document member of the same patent family

Date of the actual completion of the international search

21 November 1995

Date of mailing of the international search report

21.12.95

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL-2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

MONIKA BOHLIN

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US 95/09945

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	Dialog Information Services, file 351, DERWENT WPI, Dialog accession no. 009584777, WPI accession no. 93-278323/35, IDEMITSU KOSAN CO LTD: "Olefinic copolymer for elastomers, high tenacity material and complex materials - prepd. by copolymerising styre- nic monomer and olefin in catalyst contg. transition metal and organo metallic cpds., for modified copo- lymers mfr.", & JP, A, 5194666, 930803, 9335 (Basic) abstract --	1-15
X	EP, A2, 0572990 (MITSUI TOATSU CHEMICALS, INC.), 8 December 1993 (08.12.93), page 5, line 3 - line 10, abstract --	1-10, 14-15
Y	US, A, 4130535 (AUBERT Y. CORAN ET AL), 19 December 1978 (19.12.78), column 2, line 1 - line 19; column 2, line 64 - column 3, line 15; column 5, line 48 - line 66; column 6, line 10 - line 16 and line 41 - line 46; abstract --	16-34, 36
A	EP, A2, 0416815 (THE DOW CHEMICAL COMPANY), 13 March 1991 (13.03.91), claim 33, abstract -----	1-36

INTERNATIONAL SEARCH REPORT

Information on patent family members

SA 15721

International application No.

02/10/95

PCT/US 95/09945

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A1- 0634427	18/01/95	NONE	
WO-A1- 9406858	31/03/94	NONE	
EP-A2- 0572990	08/12/93	NONE	
US-A- 4130535	19/12/78	AT-B- 361704	25/03/81
		AU-B,B- 506201	20/12/79
		BE-A,A- 844318	20/01/77
		CA-A- 1101578	19/05/81
		CH-A- 643279	30/05/84
		DE-A,C,C 2632654	10/02/77
		FR-A,B- 2323734	08/04/77
		GB-A- 1524602	13/09/78
		JP-C- 1029735	22/01/81
		JP-A- 52013541	01/02/77
		JP-B- 55018448	19/05/80
		LU-A- 75420	06/04/77
		NL-A- 7607970	25/01/77
		NL-A- 8101416	03/08/81
		NL-A- 8101419	03/08/81
		SE-B,C- 415266	22/09/80
		SE-A- 7608253	22/01/77
EP-A2- 0416815	13/03/91	AU-B- 645519	20/01/94
		AU-A- 6203990	07/03/91
		CA-A- 2024333	01/03/91
		HU-B- 209316	28/04/94
		JP-A- 3163088	15/07/91
		JP-A- 7053618	28/02/95
		JP-A- 7070223	14/03/95
		NO-B,C- 176964	20/03/95
		CN-A- 1049849	13/03/91
		PL-B- 166689	30/06/95

Elastomers suitable for use over a broad range of temperatures and which are also less susceptible to ozone degradation are desired. Thermoset elastomers which are prepared from elastomers having high green strength (which provides greater flexibility in their handling prior to curing) are particularly desired. Also desired, are thermoset elastomers which are resistant to oil, which are useful in fabricated parts which typically contact oil, such as automotive parts and gaskets. Also desired are thermoset elastomers which easily undergo surface modification, to promote surface adhesion of the elastomer and/or to provide ionic sites on the elastomer surface. Also desired is a process for preparing such thermoset elastomers.

Thermoplastic vulcanizates are crystalline polyolefinic matrices through which thermoset elastomers are generally uniformly distributed. Examples of thermoplastic vulcanizates include EPM and EPDM thermoset materials distributed in a crystalline polypropylene matrix. Such thermoplastic vulcanizates are disadvantageous, in that they are susceptible to oil degradation. Thermoplastic vulcanizates which are more resistant to oil are desired. Also desired is a process for preparing such thermoplastic vulcanizates.

Summary of Invention

The subject invention provides a thermoset elastomer comprising a crosslinked substantially random interpolmer of: (a) from 15 to 70 weight percent of at least one α -olefin, (b) from 30 to 70 weight percent of at least one vinylidene aromatic compound, and (c) from 0 to 15 weight percent of at least one diene.

The subject invention further provides a process for making a thermoset elastomer comprising: (a) reacting at least one α -olefin with at least one vinylidene aromatic compound in the presence of a constrained geometry catalyst to form a substantially random interpolmer; and (b) curing the substantially random interpolmer to form a thermoset elastomer.

The subject invention further provides a thermoplastic vulcanizate comprising a blend of: (1) a crosslinked substantially random interpolmer of (a) from 15 to 70 weight percent of at least one α -olefin, (b) from 30 to 70 weight percent of at least one vinylidene aromatic compound, and (c) from 0 to 15 weight percent of at least one diene; and (2) at least one thermoplastic polyolefin.

The subject invention further provides a process for making a thermoplastic vulcanizate comprising:

(a) reacting at least one α -olefin with at least one vinylidene aromatic compound and optionally at least one diene in the presence of a constrained geometry catalyst to form a substantially random interpolmer; (b) intimately mixing the substantially random interpolmer with at least one thermoplastic polyolefin at a temperature above the melting or softening point of the thermoplastic polyolefin; (c) providing to the intimate mixture an agent for curing the substantially random interpolmer;

(d) simultaneously curing the substantially random interpolymers and compounding the intimate mixture to form a thermoplastic vulcanizate.

The subject invention further comprises fabricated parts comprising the thermoset elastomers or thermoplastic vulcanizates of the invention.

5 These and other embodiments are more fully described in the following Detailed Description.

The term "polymer" as used herein refers to a polymeric compound prepared by polymerizing monomers whether of the same or a different type. The generic term polymer thus embraces the term homopolymer, usually employed to refer to polymers prepared from only one type of monomer, and the term interpolymers as defined hereinafter.

10 The term "interpolymer" as used herein refers to polymers prepared by the polymerization of at least two different types of monomers. The generic term interpolymers thus includes copolymers, usually employed to refer to polymers prepared from two different monomers, and polymers prepared from more than two different types of monomers.

15 Statements herein that a polymer or interpolymers comprises or contains certain monomers, mean that such polymer or interpolymers comprises or contains polymerized therein units derived from such a monomer. For example, if a polymer is said to contain ethylene monomer, the polymer will have incorporated in it an ethylene derivative, that is, $-\text{CH}_2-\text{CH}_2-$.

20 The elastomeric thermoset compositions of the invention are preferably substantially random substantially linear or linear interpolymers comprising an olefin and a vinylidene aromatic monomer, which interpolymers have been crosslinked to yield thermoset behavior. As used herein, the term "substantially random" means that the distribution of the monomers of the interpolymers can be described by the Bernoullian statistical model or by a first or second order Markovian statistical model, as described by J. C. Randall in Polymer Sequence Determination, Carbon-13 NMR Method, Academic Press New York, 1977, pp. 71-78. Substantially random interpolymers do not contain more than 15 weight percent of the total amount of vinylidene aromatic monomer in blocks of more than three vinylidene aromatic monomer units.

25 Pseudorandom interpolymers are a subset of substantially random interpolymers. Pseudorandom interpolymers are characterized by an architecture in which all phenyl (or substituted phenyl) groups which are pendant from the polymer backbone are separated by two or more carbon backbone units. In other words, the pseudorandom interpolymers of the invention, in their noncrosslinked state, can be described by the following general formula (using styrene as the vinylidene aromatic monomer and ethylene as the α -olefin for illustration):

30

with the proviso that:

when p is 2, q and r are zero, M is in the +4 formal oxidation state (or M is in the +3 formal oxidation state if Y is $-NR^*_2$ or $-PR^*_2$), and X is an anionic ligand selected from the group consisting of halide, hydrocarbyl, hydrocarbyloxy, di(hydrocarbyl)amido, di(hydrocarbyl)phosphido, hydrocarbylsulfido, and silyl groups, as well as halo-,
 5 di(hydrocarbyl)amino-, hydrocarbyloxy-, and di(hydrocarbyl)phosphino-substituted derivatives thereof, said X group having up to 30 nonhydrogen atoms,

when r is 1, p and q are zero, M is in the +4 formal oxidation state, and X^* is a dianionic ligand selected from the group consisting of hydrocarbadiyl, oxyhydrocarbyl, and
 10 hydrocarbylenedioxy groups, said X group having up to 30 nonhydrogen atoms,

when p is 1, q and r are zero, M is in the +3 formal oxidation state, and X is a stabilizing anionic ligand group selected from the group consisting of allyl, 2-(N,N-dimethylamino)phenyl, 2-(N,N-dimethylaminomethyl)phenyl, and 2-(N,N-dimethylamino)benzyl, and

when p and r are zero, q is 1, M is in the +2 formal oxidation state, and X' is a neutral, conjugated or nonconjugated diene, optionally substituted with one or more hydrocarbyl groups,
 15 said X' having up to 40 carbon atoms and forming a π -complex with M.

Most preferred metal complexes are those according to the previous formula (II) or (III), wherein M, X, X' , X'' , R' , R'' , Z^* , Y, p, q and r are as previously defined, with the proviso that:

when p is 2, q and r are zero, M is in the +4 formal oxidation state, and X is
 20 independently each occurrence methyl, benzyl, or halide;


when p and q are zero, r is one, and M is in the +4 formal oxidation state, X'' is a 1,4-butadienyl group that forms a metallocyclopentene ring with M,

when p is 1, q and r are zero, M is in the +3 formal oxidation state, and X is 2-(N,N-dimethylamino)benzyl; and

25 when p and r are 0, q is 1, M is in the +2 formal oxidation state, and X' is 1,4-diphenyl-1,3-butadiene or 1,3-pentadiene.

Especially preferred coordination complexes corresponding to the previous formulas (II) and (III) are uniquely substituted depending on the particular end use thereof. In particular, highly useful metal complexes for use in catalyst compositions for the copolymerization of
 30 ethylene, one or more monovinyl aromatic monomers, and optionally an α -olefin or diolefin

BEST AVAILABLE COPY



Noncrosslinked pseudorandom interpolymers are described in European Patent Publication 416,815-A, the relevant parts of which are incorporated herein by reference.

While not wishing to be bound by any particular theory, it is believed that during the addition polymerization reaction of, for example, ethylene and styrene, in the presence of a constrained geometry catalyst as described below, if a styrene monomer is inserted into the growing polymer chain, the next monomer inserted will be an ethylene monomer or a styrene monomer inserted in an inverted or "tail-to-tail" fashion. It is believed that after an inverted or "tail-to-tail" styrene monomer is inserted, the next monomer will be ethylene, as the insertion of a second styrene monomer at this point would place it too close to the inverted styrene monomer, that is, less than two carbon backbone units away.

Preferably, the substantially random/pseudorandom interpolymers will be characterized as largely atactic, as indicated by a ^{13}C -NMR spectrum in which the peak areas corresponding to the main chain methylene and methine carbons representing either meso diad sequences or racemic diad sequences does not exceed 75 percent of the total peak area of the main chain methylene and methine carbons.

The substantially random/pseudorandom interpolymers may further be characterized as either linear or substantially linear. As used herein, the term "substantially linear" means that the interpolymers are characterized as having long chain branches. In contrast, the term "linear" means that the interpolymers lack long chain branches.


Substantially linear interpolymers are characterized as having a melt flow ratio, I_{10}/I_2 (as determined by ASTM D-1238) ≥ 5.63 , a molecular weight distribution (as determined by gel permeation chromatography) $M_w/M_n \leq (I_{10}/I_2) - 4.63$, and either a critical shear rate at the onset of surface melt fracture of at least 50 percent greater than the critical shear rate at the onset of surface melt fracture of a linear olefin polymer having about the same I_2 and M_w/M_n or a critical shear rate at the onset of gross melt fracture of greater than about 4×10^6 dynes/cm 2 .

To identify the melt fracture phenomena, an apparent shear stress vs. apparent shear rate plot may be employed. According to Ramamurthy in Journal of Rheology, 30(2),337-357, 1986, above a certain critical flow rate, the observed extrudate irregularities may be broadly classified into two main types: surface melt fracture and gross melt fracture.

Surface melt fracture occurs under apparently steady flow conditions and ranges in detail from loss of specular gloss to the more severe form of "sharkskin". As used herein, the onset of surface melt

comprise the foregoing complexes (II) or (III) wherein R' is C₆₋₂₀ aryl, especially phenyl, biphenyl or naphthyl, and R" is hydrogen or methyl, especially hydrogen.

Highly useful metal complexes for use in catalyst compositions for the homopolymerization of ethylene or the copolymerization of ethylene and one or more α -olefins, especially 1-butene, 1-hexene or 1-octene, comprise the foregoing complexes (II) or (III) wherein R' is C₁₋₄ alkyl, N,N-dimethylamino or 1-pyrrolidinyl, and R" is hydrogen or C₁₋₄ alkyl. Moreover, in such complexes, Y is preferably a cyclohexylamido group, X is methyl, p is two, and both q and r are zero. Most preferably such complexes are 2,3-dimethyl-substituted s-indecenyl complexes corresponding to the formulas:



10

Finally, highly useful metal complexes for use in catalyst compositions for the copolymerization of ethylene, an α -olefin and a diene, especially ethylene, propylene and a nonconjugated diene, such as ethyldenenorbornene or 1,4-hexadiene, or the conjugated diene piperlyene comprise the foregoing complexes (II) or (III) wherein R' is hydrogen, and R" is C₁₋₄ alkyl, especially methyl.

15

Highly preferred metal complexes are:

2-methylindenyl complexes:

- (n-butylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
- 20 (n-butylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (n-butylamido)dimethyl(η^5 -2-methylindenyl) silanetitanium (IV) dimethyl,
- (n-butylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- (cyclohexylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclohexylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,

- (cyclohexylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (cyclohexylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (cyclohexylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- 5 (isopropylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (isopropylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (isopropylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (isopropylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (isopropylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- 10 (cyclopentylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (cyclopentylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (cyclopentylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (cyclopentylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
- 15 (cyclopentylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (cyclododecylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (cyclododecylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-
- 20 dimethylamino)benzyl,
 (cyclododecylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (cyclododecylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- (isobutylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 25 (isobutylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (isobutylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (isobutylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (isobutylamido)dimethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,

- (n-butylamido)diisopropoxy(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (n-butylamido)diisopropoxy(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (n-butylamido)diisopropoxy(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 5 (n-butylamido)diisopropoxy(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (n-butylamido)diisopropoxy(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (n-butylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 10 (n-butylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (n-butylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (n-butylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-
 15 butadiene,
 (cyclododecylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (cyclododecylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-
 dimethylamino)benzyl,
 (cyclododecylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 20 (cyclododecylamido)dimethoxy(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (n-butylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (n-butylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-
 25 dimethylamino)benzyl,
 (n-butylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,
 (n-butylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)ethoxymethyl(η^5 -2-methylindenyl)silanetitanium (IV) dibenzyl,

2,3-dimethylindenyl complexes:

10

(n-butylamido)dimethyl(η^5 -2,3-dimethylindenyl)-silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(n-butylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)dimethyl(η^5 -2,3-dimethylindenyl)-silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,

15 (n-butylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,

(isopropylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

25 (isopropylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,

(isopropylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(isopropylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,

(isopropylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,

- (cyclopentylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclopentylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 5 (cyclopentylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (cyclopentylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,
- (cyclopentylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,
- 10 (cyclododecylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclododecylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 15 (cyclododecylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,
- (cyclododecylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,
- (isobutylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (isobutylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 20 (isobutylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (isobutylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,
- (isobutylamido)dimethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 25 (n-butylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (n-butylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (n-butylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,

- (n-butylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)-silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 5 (cyclododecylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)-silanetitanium (II) 1,3-pentadiene,
 (cyclododecylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)-silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (cyclododecylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)-silanetitanium (IV) dimethyl,
 (cyclododecylamido)diisopropoxy(η^5 -2,3-dimethylindenyl)-silanetitanium (IV) dibenzyl,
- 10 (n-butylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (n-butylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,
 (n-butylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 15 (n-butylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,
 (n-butylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 20 (cyclododecylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,
 (cyclododecylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (cyclododecylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,
 (cyclododecylamido)dimethoxy(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,
- 25 (n-butylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)-silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (n-butylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,

(n-butylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,

5

(cyclododecylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

10

(cyclododecylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)ethoxymethyl(η^5 -2,3-dimethylindenyl)silanetitanium (IV) dibenzyl,

3-methylindenyl complexes:

15 (n-butylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(n-butylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,

(n-butylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,

20

(cyclohexylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclohexylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclohexylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclohexylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,

25 (cyclohexylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,

(isopropylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(isopropylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,

- (isopropylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (isopropylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
 (isopropylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- 5 (cyclopentylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (cyclopentylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (cyclopentylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (cyclopentylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
 (cyclopentylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- 10 (cyclododecylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (cyclododecylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (cyclododecylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 15 (cyclododecylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
 (cyclododecylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- (isobutylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
 (isobutylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
- 20 (isobutylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (isobutylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
 (isobutylamido)dimethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)diisopropoxy(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 25 (n-butylamido)diisopropoxy(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
 (n-butylamido)diisopropoxy(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
 (n-butylamido)diisopropoxy(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
 (n-butylamido)diisopropoxy(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,

- (cyclododecylamido)diisopropoxy(η^5 -3-methylindenyl)-silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclododecylamido)diisopropoxy(η^5 -3-methylindenyl)-silanetitanium (II) 1,3-pentadiene,
- 5 (cyclododecylamido)diisopropoxy(η^5 -3-methylindenyl)-silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (cyclododecylamido)diisopropoxy(η^5 -3-methylindenyl)-silanetitanium (IV) dimethyl,
- (cyclododecylamido)diisopropoxy(η^5 -3-methylindenyl)-silanetitanium (IV) dibenzyl,
- 10 (n-butylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
- (n-butylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (n-butylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
- (n-butylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- 15
- (cyclododecylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclododecylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-
- 20 dimethylamino)benzyl,
- (cyclododecylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
- (cyclododecylamido)dimethoxy(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 25 (n-butylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
- (n-butylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (n-butylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
- (n-butylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,

- (cyclododecylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclododecylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (II) 1,3-pentadiene,
- 5 (cyclododecylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (cyclododecylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (IV) dimethyl,
- (cyclododecylamido)ethoxymethyl(η^5 -3-methylindenyl)silanetitanium (IV) dibenzyl,
- 10 2-methyl-3-ethylindenyl complexes:
- (n-butylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (n-butylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-
- 15 dimethylamino)benzyl,
- (n-butylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,
- (n-butylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- 20 butadiene,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,
- 25 (cyclohexylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,
- (isopropylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (isopropylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,

(isopropylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(isopropylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(isopropylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

5

(cyclopentylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclopentylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclopentylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

10

(cyclopentylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(cyclopentylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

15

(cyclododecylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)dimethyl(-2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

20

(isobutylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(isobutylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,

(isobutylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

25

(isobutylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(isobutylamido)dimethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

- (n-butylamido)diisopropoxy(η^5 -2-methyl-3-ethyl-indenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (n-butylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-
- 5 dimethylamino)benzyl,
- (n-butylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,
- (n-butylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)diisopropoxy(-2-methyl-3-ethyl-indenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- 10 butadiene,
- (cyclododecylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)-silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)-silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (cyclododecylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)-silanetitanium (IV) dimethyl,
- 15 (cyclododecylamido)diisopropoxy(η^5 -2-methyl-3-ethylindenyl)-silanetitanium (IV) dibenzyl,
- (n-butylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- butadiene,
- (n-butylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 20 (n-butylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (n-butylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,
- (n-butylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)dimethoxy(η^5 -2-methyl-3-ethyl-indenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- 25 butadiene,
- (cyclododecylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- 30 (cyclododecylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)dimethoxy(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

(n-butylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

5 (n-butylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(n-butylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

10

(cyclododecylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silane-titanium (II) 1,3-pentadiene,

15 (cyclododecylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silane-titanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)ethoxymethyl(η^5 -2-methyl-3-ethylindenyl)silanetitanium (IV) dibenzyl,

2,3,4,6-tetramethylindenyl complexes:

20

(n-butylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(n-butylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,

25 (n-butylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)-silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,

(n-butylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,

- (cyclohexylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-
- 5 dimethylamino)benzyl,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,
- (isopropylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- 10 butadiene,
- (isopropylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (isopropylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (isopropylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,
- 15 (isopropylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclopentylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- butadiene,
- (cyclopentylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 20 (cyclopentylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (cyclopentylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,
- (cyclopentylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,
- (cyclododecylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-
- 25 butadiene,
- (cyclododecylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (cyclododecylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,
- 30 (cyclododecylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,

- (isobutylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (isobutylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 5 (isobutylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (isobutylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,
- (isobutylamido)dimethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,
- 10 (n-butylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silane-titanium (II) 1,3-pentadiene,
- (n-butylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)-silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 15 (n-butylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silane-titanium (IV) dimethyl,
- (n-butylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silane-titanium (IV) dibenzyl,
- (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)-silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 20 (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)diisopropoxy(-2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,
- 25 (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,

(n-butylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,

5

(cyclododecylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

10

(cyclododecylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)dimethoxy(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,

15

(n-butylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(n-butylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,

20

(n-butylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

25

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6-tetramethylindenyl)silanetitanium (IV) dibenzyl,

30

2,3,4,6,7-pentamethylindenyl complexes:

- (n-butylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 5 (n-butylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)-silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (n-butylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,
- (n-butylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,
- 10 (cyclohexylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 15 (cyclohexylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,
- (cyclohexylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,
- (isopropylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 20 (isopropylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (isopropylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- (isopropylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,
- (isopropylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,
- 25 (cyclopentylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (cyclopentylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclopentylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-
- 30 dimethylamino)benzyl,

- (cyclopentylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dimethyl,
 (cyclopentylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dibenzyl,
- 5 (cyclododecylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
 (cyclododecylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,3-pentadiene,
 (cyclododecylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (III) 2-(N,N-dimethylamino)benzyl,
 (cyclododecylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dimethyl,
 10 (cyclododecylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dibenzyl,
- (isobutylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
 (isobutylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,3-pentadiene,
 15 (isobutylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (III) 2-(N,N-dimethylamino)benzyl,
 (isobutylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dimethyl,
 (isobutylamido)dimethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dibenzyl,
- 20 (n-butylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
 (n-butylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,3-pentadiene,
 (n-butylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (III) 2-(N,N-dimethylamino)benzyl,
 25 (n-butylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dimethyl,
 (n-butylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (IV) dibenzyl,
- (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,

- (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
- (cyclododecylamido)diisopropoxy(-2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 5 (cyclododecylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,
(cyclododecylamido)diisopropoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,
- (n-butylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 10 (n-butylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
(n-butylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
(n-butylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,
(n-butylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,
- 15 (cyclododecylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
(cyclododecylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
- 20 (cyclododecylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
(cyclododecylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,
(cyclododecylamido)dimethoxy(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,
- 25 (n-butylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethyl-indenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
(n-butylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,
(n-butylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,
- 30 (n-butylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,

(n-butylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

- 5 (cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dimethyl,

- 10 (cyclododecylamido)ethoxymethyl(η^5 -2,3,4,6,7-pentamethylindenyl)silanetitanium (IV) dibenzyl,

3-phenyl-s-indacen-1-yl complexes (alternatively referred to as [1,2,3,4,5- η]-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl) complexes)

(i-propylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(IV) dimethyl,

- 15 (cyclohexylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(IV) dimethyl,

(n-butylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(II) 1,4-diphenyl-1,3-butadiene,

(n-butylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(II) 1,3-pentadiene,

(n-butylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(IV) dimethyl,

- 20 (n-butylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(IV) dibenzyl,

(cyclododecylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(II) 1,3-pentadiene,

- 25 (cyclododecylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(IV) dimethyl,

(cyclododecylamido)dimethyl(η^5 -3-phenyl-s-indacenyl)silanetitanium(IV) dibenzyl,

3-naphthyl-s-indacenyl complexes:

5 (i-propylamido)dimethyl(η^5 -3-naphthyl-s-indacenyl)silanetitanium (IV) dimethyl

(cyclohexylamido)dimethyl(η^5 -3-naphthyl-s-indacenyl)silanetitanium (IV) dimethyl

3-biphenyl-s-indacenyl complexes:

(i-propylamido)dimethyl(η^5 -3-biphenyl-s-indacenyl)silanetitanium (IV) dimethyl, and

10 (cyclohexylamido)dimethyl(η^5 -3-biphenyl-s-indacenyl)silanetitanium (IV) dimethyl

2-methyl-3-biphenyl-s-indacenyl complexes:

(i-propylamido)dimethyl(η^5 -2-methyl-3-biphenyl-s-indacenyl)silane-titanium (IV) dimethyl, and

(cyclohexylamido)dimethyl(η^5 -2-methyl-3-biphenyl-s-indacenyl)silane-titanium (IV) dimethyl

15

2-methyl-3-naphthyl-s-indacenyl complexes:

(cyclohexylamido)dimethyl(η^5 -2-methyl-3-naphthyl-s-indacenyl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

20 (cyclohexylamido)dimethyl(η^5 -2-methyl-3-naphthyl-s-indacenyl)silanetitanium (II) 1,3-pentadiene,

(cyclohexylamido)dimethyl(η^5 -2-methyl-3-naphthyl-s-indacenyl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclohexylamido)dimethyl(η^5 -2-methyl-3-naphthyl-s-indacenyl)silanetitanium (IV) dimethyl, and

(cyclohexylamido)dimethyl(η^5 -2-methyl-3-naphthyl-s-indacenyl)silanetitanium (IV) dibenzyl.

3-phenyl-gem-dimethylacenaphthalenyl complexes (also referred to as (1,2,3,4,5- η)(5,6,7,8-tetrahydro-5,5,8,8-tetramethyl-1H-Benz(f)inde-1-yl) complexes)

- 5 (n-butylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(II) 1,3-pentadiene,
- (n-butylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(III) 2-(N,N-dimethylamino)benzyl,
- 10 (n-butylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(IV) dimethyl,
- (n-butylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(IV) dibenzyl,
- (cyclododecylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(II) 1,4-diphenyl-1,3-butadiene,
- 15 (cyclododecylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(II) 1,3-pentadiene,
- (cyclododecylamido)dimethyl(η^5 -3-gem-dimethylacenaphth-alenyl)silanetitanium(III) 2-(N,N-dimethylamino)benzyl,
- 20 (cyclododecylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(IV) dimethyl,
- (cyclododecylamido)dimethyl(η^5 -3-phenyl-gem-dimethylacenaphth-alenyl)silanetitanium(IV) dibenzyl,
- 25 2-methyl-s-indacen-1-yl complexes:

- (n-butylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,3-pentadiene,
- (n-butylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (III) 2-(N,N-
- 5 dimethylamino)benzyl,
- (n-butylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dimethyl,
- (n-butylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dibenzyl,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
- 10 (cyclohexylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,3-pentadiene,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (III) 2-(N,N-dimethylamino)benzyl,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dimethyl,
- (cyclohexylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dibenzyl,
- 15
- (isopropylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,4-diphenyl-1,3-butadiene,
- (isopropylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,3-pentadiene,
- (isopropylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (III) 2-(N,N-
- 20 dimethylamino)benzyl,
- (isopropylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dimethyl,
- (isopropylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dibenzyl,
- (cyclopentylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,4-diphenyl-1,3-
- 25 butadiene,
- (cyclopentylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (II) 1,3-pentadiene,
- (cyclopentylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (III) 2-(N,N-dimethylamino)benzyl,
- (cyclopentylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silane-titanium (IV) dimethyl,

(cyclopentylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

(cyclododecylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

- 5 (cyclododecylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,
(cyclododecylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(cyclododecylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

10

(isobutylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(isobutylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

- 15 (isobutylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(isobutylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(isobutylamido)dimethyl(η^5 -2-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

2,3-dimethyl-s-indacen-1-yl complexes: (n-butylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

20

(n-butylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(n-butylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(n-butylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

- 25 (n-butylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(cyclohexylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

5

(isopropylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(isopropylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(isopropylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

10

(isopropylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(isopropylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

(cyclopentylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

15

(cyclopentylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(cyclopentylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclopentylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(cyclopentylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

20

(cyclododecylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(cyclododecylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

25

(cyclododecylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(cyclododecylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

- (isobutylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (isobutylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,
- (isobutylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-
- 5 dimethylamino)benzyl,
- (isobutylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,
- (isobutylamido)dimethyl(η^5 -2,3-dimethyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

3-methyl-s-indacen-1-yl complexes:

- 10 (n-butylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (n-butylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,
- (n-butylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- 15 (n-butylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,
- (n-butylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,
- (cyclohexylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- 20 (cyclohexylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,
- (cyclohexylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-
- dimethylamino)benzyl,
- (cyclohexylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,
- (cyclohexylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,
- 25 (isopropylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,
- (isopropylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,
- (isopropylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-
- 30 dimethylamino)benzyl,

(isopropylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(isopropylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

5 (cyclopentylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclopentylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(cyclopentylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclopentylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

10 (cyclopentylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

(cyclododecylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(cyclododecylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

15 (cyclododecylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

(cyclododecylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl,

(cyclododecylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl,

20 (isobutylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,4-diphenyl-1,3-butadiene,

(isobutylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (II) 1,3-pentadiene,

(isobutylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (III) 2-(N,N-dimethylamino)benzyl,

25 (isobutylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dimethyl, and

(isobutylamido)dimethyl(η^5 -3-methyl-s-indacen-1-yl)silanetitanium (IV) dibenzyl.

The complexes can be prepared by use of well known synthetic techniques. Optionally a reducing agent can be employed to produce the lower oxidation state complexes. Such a process is disclosed in USSN 8/241,523, filed May 13, 1994, published as WO95-00526. The reactions are conducted in a suitable noninterfering solvent at a temperature from -100 to 300

°C, preferably from -78 to 100 °C, most preferably from 0 to 50 °C. By the term "reducing agent" herein is meant a metal or compound which, under reducing conditions causes the metal, M, to be reduced from a higher to a lower oxidation state. Examples of suitable metal reducing agents are alkali metals, alkaline earth metals, aluminum and zinc, alloys of alkali
5 metals or alkaline earth metals such as sodium/mercury amalgam and sodium/potassium alloy. Examples of suitable reducing agent compounds are sodium naphthalenide, potassium graphite, lithium alkyls, lithium or potassium alkadienyls; and Grignard reagents. Most preferred reducing agents are the alkali metals or alkaline earth metals, especially lithium and magnesium metal.

10 Suitable reaction media for the formation of the complexes include aliphatic and aromatic hydrocarbons, ethers, and cyclic ethers, particularly branched-chain hydrocarbons such as isobutane, butane, pentane, hexane, heptane, octane, and mixtures thereof; cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof; aromatic and hydrocarbyl-substituted aromatic
15 compounds such as benzene, toluene, and xylene, C₁₋₄ dialkyl ethers, C₁₋₄ dialkyl ether derivatives of (poly)alkylene glycols, and tetrahydrofuran. Mixtures of the foregoing are also suitable.


The complexes are rendered catalytically active by combination with an activating cocatalyst or by use of an activating technique. Suitable activating cocatalysts for use herein
20 include polymeric or oligomeric alumoxanes, especially methylalumoxane, triisobutyl aluminum modified methylalumoxane, or isobutylalumoxane; neutral Lewis acids, such as C₁₋₃₀ hydrocarbyl substituted Group 13 compounds, especially tri(hydrocarbyl)aluminum- or tri(hydrocarbyl)boron compounds and halogenated (including perhalogenated) derivatives thereof, having from 1 to 10 carbons in each hydrocarbyl or halogenated hydrocarbyl group,
25 more especially perfluorinated tri(aryl)boron compounds, and most especially tris(pentafluorophenyl)borane; nonpolymeric, compatible, noncoordinating, ion forming compounds (including the use of such compounds under oxidizing conditions), especially the use of ammonium-, phosphonium-, oxonium-, carbonium-, silylium- or sulfonium- salts of compatible, noncoordinating anions, or ferrocenium salts of compatible, noncoordinating anions; bulk
30 electrolysis (explained in more detail hereinafter); and combinations of the foregoing activating cocatalysts and techniques. The foregoing activating cocatalysts and activating techniques have been previously taught with respect to different metal complexes in the following references: EP-A-277,003, US-A-5,153,157, US-A-5,064,802, EP-A-468,651 (equivalent to U. S. Serial No. 07/547,718), EP-A-520,732 (equivalent to U. S. Serial No. 07/876,268), and EP-A-
35 520,732 (equivalent to U. S. Serial Nos. 07/884,966 filed May 1, 1992).

Combinations of neutral Lewis acids, especially the combination of a trialkyl aluminum compound having from 1 to 4 carbons in each alkyl group and a halogenated tri(hydrocarbyl)boron compound having from 1 to 20 carbons in each hydrocarbyl group, especially tris(pentafluorophenyl)borane, further combinations of such neutral Lewis acid mixtures with a polymeric or oligomeric alumoxane, and combinations of a single neutral Lewis acid, especially tris(pentafluorophenyl)borane with a polymeric or oligomeric alumoxane are especially desirable activating cocatalysts. A benefit according to the present invention is the discovery that the most efficient catalyst activation using such a combination of tris(pentafluorophenyl)borane/alumoxane mixture occurs at reduced levels of alumoxane. Preferred molar ratios of Group 4 metal complex:tris(pentafluoro-phenyl)borane:alumoxane are from 1:1:1 to 1:5:5, more preferably from 1:1:1.5 to 1:5:3. The surprising efficient use of lower levels of alumoxane with the present invention allows for the production of olefin polymers with high catalytic efficiencies using less of the expensive alumoxane cocatalyst. Additionally, polymers with lower levels of aluminum residue, and hence greater clarity, are obtained.

Suitable ion forming compounds useful as cocatalysts in one embodiment of the present invention comprise a cation which is a Bronsted acid capable of donating a proton, and a compatible, noncoordinating anion, A⁻. As used herein, the term "noncoordinating" means an anion or substance which either does not coordinate to the Group 4 metal containing precursor complex and the catalytic derivative derived therefrom, or which is only weakly coordinated to such complexes thereby remaining sufficiently labile to be displaced by a neutral Lewis base. A noncoordinating anion specifically refers to an anion which when functioning as a charge balancing anion in a cationic metal complex does not transfer an anionic substituent or fragment thereof to said cation thereby forming neutral complexes. "Compatible anions" are anions which are not degraded to neutrality when the initially formed complex decomposes and are noninterfering with desired subsequent polymerization or other uses of the complex.

Preferred anions are those containing a single coordination complex comprising a charge-bearing metal or metalloid core which anion is capable of balancing the charge of the active catalyst species (the metal cation) which may be formed when the two components are combined. Also, said anion should be sufficiently labile to be displaced by olefinic, diolefinic and acetylenically unsaturated compounds or a neutral Lewis base such as an ether or nitrile. Suitable metals include, but are not limited to, aluminum, gold and platinum. Suitable metalloids include, but are not limited to, boron, phosphorus, and silicon. Compounds containing anions which comprise coordination complexes containing a single metal or metalloid atom are, of course, well known and many, particularly such compounds containing a single boron atom in the anion portion, are available commercially.

Preferably such cocatalysts may be represented by the following general formula:



wherein:

L^* is a neutral Lewis base;

5 $(L^*-H)^+$ is a Bronsted acid;

A^{d-} is a noncoordinating, compatible anion having a charge of d^- , and

d is an integer from 1 to 3.


More preferably A^{d-} corresponds to the formula: $[M'Q_d]^-$;

wherein:

10 M' is boron or aluminum in the +3 formal oxidation state; and

Q independently each occurrence is selected from hydride, dialkylamido, halide, hydrocarbyl, hydrocarbyloxy, halosubstituted-hydrocarbyl, halosubstituted hydrocarbyloxy, and halo-substituted silylhydrocarbyl radicals (including perhalogenated hydrocarbyl-perhalogenated hydrocarbyloxy- and perhalogenated silylhydrocarbyl radicals), said Q having
15 up to 20 carbons with the proviso that in not more than one occurrence is Q halide. Examples of suitable hydrocarbyloxy Q groups are disclosed in U. S. Patent 5,296,433.

In a more preferred embodiment, d is one, that is, the counter ion has a single negative charge and is A^- . Activating cocatalysts comprising boron which are particularly useful in the preparation of catalysts of this invention may be represented by the following general formula:



wherein:

L^* is as previously defined;

B is boron in a formal oxidation state of 3; and

Q is a hydrocarbyl-, hydrocarbyloxy-, fluorinated hydrocarbyl-, fluorinated
25 hydrocarbyloxy-, or fluorinated silylhydrocarbyl- group of up to 20 nonhydrogen atoms, with the proviso that in not more than one occasion is Q hydrocarbyl.

Most preferably, Q is each occurrence a fluorinated aryl group, especially, a pentafluorophenyl group.

30 Illustrative, but not limiting, examples of boron compounds which may be used as an activating cocatalyst in the preparation of the improved catalysts of this invention are tri-substituted ammonium salts such as:

- trimethylammonium tetrakis(pentafluorophenyl) borate,
triethylammonium tetrakis(pentafluorophenyl) borate,
tripropylammonium tetrakis(pentafluorophenyl) borate,
tri(n-butyl)ammonium tetrakis(pentafluorophenyl) borate, tri(sec-butyl)ammonium
5 tetrakis(pentafluorophenyl) borate,
N,N-dimethylanilinium tetrakis(pentafluorophenyl) borate,
N,N-dimethylanilinium n-butyltris(pentafluorophenyl) borate,
N,N-dimethylanilinium benzyltris(pentafluorophenyl) borate,
N,N-dimethylanilinium tetrakis(4-(t-butyl)dimethylsilyl)-2, 3, 5, 6-tetrafluorophenyl) borate,
10 N,N-dimethylanilinium tetrakis(4-(triisopropylsilyl)-2, 3, 5, 6-tetrafluorophenyl) borate,
N,N-dimethylanilinium pentafluorophenoxytris(pentafluorophenyl) borate,
N,N-diethylanilinium tetrakis(pentafluorophenyl) borate,
N,N-dimethyl-2,4,6-trimethylanilinium tetrakis(pentafluorophenyl) borate,
trimethylammonium tetrakis(2,3,4,6-tetrafluorophenyl) borate,
15 triethylammonium tetrakis(2,3,4,6-tetrafluorophenyl) borate,
tripropylammonium tetrakis(2,3,4,6-tetrafluorophenyl) borate,
tri(n-butyl)ammonium tetrakis(2,3,4,6-tetrafluorophenyl) borate,
dimethyl(t-butyl)ammonium tetrakis(2,3,4,6-tetrafluorophenyl) borate,
N,N-dimethylanilinium tetrakis(2,3,4,6-tetrafluorophenyl) borate,
20 N,N-diethylanilinium tetrakis(2,3,4,6-tetrafluorophenyl) borate, and
N,N-dimethyl-2,4,6-trimethylanilinium tetrakis(2,3,4,6-tetrafluorophenyl) borate;
dialkyl ammonium salts such as:
di-(i-propyl)ammonium tetrakis(pentafluorophenyl) borate, and
dicyclohexylammonium tetrakis(pentafluorophenyl) borate;
25 tri-substituted phosphonium salts such as:
triphenylphosphonium tetrakis(pentafluorophenyl) borate,
tri(o-tolyl)phosphonium tetrakis(pentafluorophenyl) borate, and
tri(2,6-dimethylphenyl)phosphonium tetrakis(pentafluorophenyl) borate;

di-substituted oxonium salts such as:

diphenyloxonium tetrakis(pentafluorophenyl) borate,

di(o-tolyl)oxonium tetrakis(pentafluorophenyl) borate, and

di(2,6-dimethylphenyl)oxonium tetrakis(pentafluorophenyl) borate;

5 di-substituted sulfonium salts such as:


diphenylsulfonium tetrakis(pentafluorophenyl) borate,

di(o-tolyl)sulfonium tetrakis(pentafluorophenyl) borate, and

bis(2,6-dimethylphenyl)sulfonium tetrakis(pentafluorophenyl) borate.

Preferred $(L^*-H)^+$ cations are N,N-dimethylanilinium and tributylammonium.

10 Another suitable ion forming, activating cocatalyst comprises a salt of a cationic oxidizing agent and a noncoordinating, compatible anion represented by the formula:



wherein:

Ox^{e+} is a cationic oxidizing agent having a charge of $e+$;

15 e is an integer from 1 to 3; and

A^{d-} and d are as previously defined.

Examples of cationic oxidizing agents include: ferrocenium, hydrocarbyl-substituted ferrocenium, Ag^+ , or Pb^{+2} . Preferred embodiments of A^{d-} are those anions previously defined with respect to the Bronsted acid containing activating cocatalysts, especially

20 tetrakis(pentafluorophenyl)borate.

Another suitable ion forming, activating cocatalyst comprises a compound which is a salt of a carbenium ion and a noncoordinating, compatible anion represented by the formula:




wherein:

25 C^+ is a C_{1-20} carbenium ion; and

A^- is as previously defined. A preferred carbenium ion is the trityl cation, that is triphenylmethyl cation.

A further suitable ion forming, activating cocatalyst comprises a compound which is a salt of a silylium ion and a noncoordinating, compatible anion represented by the formula:



wherein:

R is C₁₋₁₀ hydrocarbyl, and X', q and A⁻ are as previously defined.

Preferred silylium salt activating cocatalysts are trimethylsilylium tetrakis(pentafluorophenyl)borate, triethylsilylium tetrakis(pentafluorophenyl)borate and ether substituted adducts thereof. Silylium salts have been previously generically disclosed in J. Chem Soc. Chem. Comm., 1993, 383-384, as well as Lambert, J. B., et al., Organometallics, 1994, 13, 2430-2443. The use of the above silylium salts as activating cocatalysts for addition polymerization catalysts is claimed in USP 5,625,087.

Certain complexes of alcohols, mercaptans, silanols, and oximes with tris(pentafluorophenyl)borane are also effective catalyst activators and may be used according to the present invention. Such cocatalysts are disclosed in USP 5,296,433.

Especially preferred cocatalysts will comprise a cation which is a Bronsted acid capable of donating a proton, and an inert, compatible, noncoordinating, anion, characterized by a solubility at 25 °C in hexane, cyclohexane or methylcyclohexane of at least 5 weight percent, preferably at least 7.5 weight percent. By the use of the foregoing catalyst activator, improved catalyst activation is provided. More particularly, increased catalyst efficiency and rate of polymerization are obtained, especially under solution polymerization conditions, most especially continuous, solution polymerization conditions.

Preferred embodiments of such cocatalysts may be represented by the following general formula: (L⁺-H)_d⁺(A^{d-}), wherein:


L⁺ is a neutral Lewis base;

(L⁺-H)⁺ is a Bronsted acid;

A^{d-} is a noncoordinating, compatible anion having charge d-, and

d is an integer from 1 to 3.

Examples of suitable anions of the formula A^{d-} include sterically shielded diboron anions corresponding to the formula:



wherein:

S is alkyl, fluoroalkyl, aryl, or fluoroaryl (and where two S groups are present additionally hydrogen),

Ar^{F} is fluoroaryl, and

X^1 is either hydrogen or halide.

5 Such diboron anions are disclosed in US-A-5,447,895.

Additional examples of $\text{A}^{\text{d-}}$ anions are those anions corresponding to the formula: $[\text{M}^{\text{k+}}\text{Q}_{\text{n}}]^{\text{d-}}$, wherein:

k is an integer from 1 to 3;

n' is an integer from 2 to 6;

10 $\text{n}' - \text{k} = \text{d}$;

M' is an element selected from Group 13 of the Periodic Table of the Elements; and

Q independently each occurrence is selected from hydride, dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, and halosubstituted-hydrocarbyl radicals, said Q having up to 20 carbons with the proviso that in not more than one occurrence is Q halide.

15 In a more preferred embodiment, d is one, that is, the counter ion has a single negative charge and corresponds to the formula, A^- . Activating cocatalysts comprising boron which are particularly useful in this invention may be represented by the following general formula: $[\text{L}^* - \text{H}]^+ [\text{BQ}'_4]^-$, wherein:

L^* is a nitrogen, sulfur or phosphorus containing neutral Lewis base;

20 B is boron in an oxidation state of 3; and

Q' is a fluorinated C_{1-20} hydrocarbyl group.

Most preferably, Q' is in each occurrence a fluorinated aryl group, especially a pentafluorophenyl group.

Generally, solubility of the catalyst activators of the invention in aliphatic compounds is
 25 increased by incorporation of one or more oleophilic groups such as long chain alkyl groups; long chain alkenyl groups; or halo-, alkoxy-, amino-, silyl-, or germlyl- substituted long chain alkyl groups or long chain alkenyl groups into the Bronsted acid, L. By the term "long chain" are meant groups having from 10 to 50 non-hydrogen atoms in such group, preferably in a non-branched form. Preferably such L groups contain from 1 to 3 C_{10-40} n-alkyl groups with a total of
 30 from 12 to 100 carbons, more preferably 2 C_{10-40} alkyl groups and from 21 to 90 total carbons. The presence of such oleophilic groups is believed to render the activator more soluble in aliphatic liquids thereby improving the effectiveness in catalyst activation. It is understood that the catalyst activator may comprise a mixture of oleophilic groups of differing lengths. For

example, one suitable activator is the protonated ammonium salt derived from the commercially available long chain amine comprising a mixture of two C₁₄, C₁₆ or C₁₈ alkyl groups and one methyl group. Such amines are available from Witco Corp., under the trade name Kemamine™ T9701, and from Akzo-Nobel under the trade name Armeen™ M2HT. The present cocatalysts
 5 may be used in reduced concentrations based on amount of metal complex compared to the amounts of prior known cocatalysts previously required, while retaining equivalent or improved catalyst efficiencies.

Illustrative, but not limiting examples of boron compounds which may be used as ionic activating cocatalysts useful in the preparation of the polymers of this invention are tri-
 10 substituted ammonium salts such as:
 decyldi(methyl)ammonium tetrakis(pentafluorophenyl) borate, dodecyldi(methyl)ammonium tetrakis(pentafluorophenyl) borate, tetradecyldi(methyl)ammonium tetrakis(pentafluorophenyl) borate, hexadecyldi(methyl)ammonium tetrakis(pentafluorophenyl) borate, octadecyldi(methyl)ammonium tetrakis(pentafluorophenyl) borate, eicosyldi(methyl)ammonium
 15 tetrakis(pentafluorophenyl) borate, methyldi(decyl)ammonium tetrakis(pentafluorophenyl) borate, methyldi(dodecyl)ammonium tetrakis(pentafluorophenyl) borate, methyldi(tetradecyl)ammonium tetrakis(pentafluorophenyl) borate, methyldi(hexadecyl)ammonium tetrakis(pentafluorophenyl) borate, methyldi(octadecyl)ammonium tetrakis(pentafluorophenyl) borate, methyldi(eicosyl)ammonium
 20 tetrakis(pentafluorophenyl) borate, tridecylammonium tetrakis(pentafluorophenyl) borate, tridodecylammonium tetrakis(pentafluorophenyl) borate, tritetradecylammonium tetrakis(pentafluorophenyl) borate, trihexadecylammonium tetrakis(pentafluorophenyl) borate, trioctadecylammonium tetrakis(pentafluorophenyl) borate, trieicosylammonium tetrakis(pentafluorophenyl) borate, decyldi(n-butyl)ammonium tetrakis(pentafluorophenyl) borate, dodecyldi(n-butyl)ammonium tetrakis(pentafluorophenyl) borate, octadecyldi(n-butyl)ammonium tetrakis(pentafluorophenyl) borate,
 25 N,N-didodecylanilinium tetrakis(pentafluorophenyl) borate, N-methyl-N-dodecylanilinium tetrakis(pentafluorophenyl) borate, N,N-di(octadecyl)(2,4,6-trimethylanilinium) tetrakis(pentafluorophenyl) borate, cyclohexyldi(dodecyl)ammonium tetrakis(pentafluorophenyl) borate, and methyldi(dodecyl)ammonium tetrakis-(2,3,4,6-tetrafluorophenyl) borate.
 30
 35 Suitable similarly substituted sulfonium or phosphonium salts such as, di(decyl)sulfonium tetrakis(pentafluorophenyl) borate,

(n-butyl)dodecylsulfonium tetrakis(pentafluorophenyl) borate, tridecylphosphonium tetrakis(pentafluorophenyl) borate, di(octadecyl)methylphosphonium tetrakis(pentafluorophenyl) borate, and tri(tetradecyl)phosphonium tetrakis(pentafluorophenyl) borate, may also be named.

- 5 Preferred activators are di(octadecyl)methylammonium tetrakis(pentafluorophenyl)borate and di(octadecyl)(n-butyl)ammonium tetrakis(pentafluorophenyl)borate.

The cocatalysts may also be used in combination with a tri(hydrocarbyl)aluminum compound having from 1 to 10 carbons in each hydrocarbyl group, an oligomeric or polymeric
10 alumoxane compound, a di(hydrocarbyl)(hydrocarbyloxy)aluminum compound having from 1 to 20 carbons in each hydrocarbyl or hydrocarbyloxy group, or a mixture of the foregoing compounds, if desired. These aluminum compounds are usefully employed for their beneficial ability to scavenge impurities such as oxygen, water, and aldehydes from the polymerization mixture.

- 15 Suitable di(hydrocarbyl)(hydrocarbyloxy)aluminum compounds correspond to the formula $T^1_2AlOT^2$ wherein T^1 is C_{3-6} secondary or tertiary alkyl, most preferably isopropyl, isobutyl or tert-butyl; and T^2 is a C_{12-30} alkaryl radical or aralkyl radical, most preferably, 2,6-di(t-butyl)-4-methylphenyl, 2,6-di(t-butyl)-4-methyltolyl, 2,6-di(i-butyl)-4-methylphenyl, or 4-(3',5'-ditertiarybutyltolyl)-2,6-ditertiarybutylphenyl.

- 20 Preferred aluminum compounds include C_{2-6} trialkyl aluminum compounds, especially those wherein the alkyl groups are ethyl, propyl, isopropyl, n-butyl, isobutyl, pentyl, neopentyl, or isopentyl, dialkyl(aryloxy)aluminum compounds containing from 1-6 carbons in the alkyl group and from 6 to 18 carbons in the aryl group (especially (3,5-di(t-butyl)-4-methylphenoxy)diisobutylaluminum), methylalumoxane, modified methylalumoxane and
25 diisobutylalumoxane. The molar ratio of aluminum compound to metal complex is preferably from 1:10,000 to 1000:1, more preferably from 1:5000 to 100:1, most preferably from 1:100 to 100:1.

- The technique of bulk electrolysis involves the electrochemical oxidation of the metal complex under electrolysis conditions in the presence of a supporting electrolyte comprising a
30 noncoordinating, inert anion. In the technique, solvents, supporting electrolytes and electrolytic potentials for the electrolysis are used such that electrolysis byproducts that would render the metal complex catalytically inactive are not substantially formed during the reaction. More particularly, suitable solvents are materials that are: liquids under the conditions of the electrolysis (generally temperatures from 0 to 100 °C), capable of dissolving the supporting
35 electrolyte, and inert. "Inert solvents" are those that are not reduced or oxidized under the

reaction conditions employed for the electrolysis. It is generally possible in view of the desired electrolysis reaction to choose a solvent and a supporting electrolyte that are unaffected by the electrical potential used for the desired electrolysis. Preferred solvents include difluorobenzene (all isomers), dimethoxyethane (DME), and mixtures thereof.

5 The electrolysis may be conducted in a standard electrolytic cell containing an anode and cathode (also referred to as the working electrode and counter electrode respectively). Suitable materials of construction for the cell are glass, plastic, ceramic and glass coated metal. The electrodes are prepared from inert conductive materials, by which are meant conductive materials that are unaffected by the reaction mixture or reaction conditions. Platinum or
10 palladium are preferred inert conductive materials. Normally an ion permeable membrane such as a fine glass frit separates the cell into separate compartments, the working electrode compartment and counter electrode compartment. The working electrode is immersed in a reaction medium comprising the metal complex to be activated, solvent, supporting electrolyte, and any other materials desired for moderating the electrolysis or stabilizing the resulting
15 complex. The counter electrode is immersed in a mixture of the solvent and supporting electrolyte. The desired voltage may be determined by theoretical calculations or experimentally by sweeping the cell using a reference electrode such as a silver electrode immersed in the cell electrolyte. The background cell current, the current draw in the absence of the desired electrolysis, is also determined. The electrolysis is completed when the current
20 drops from the desired level to the background level. In this manner, complete conversion of the initial metal complex can be easily detected.

Suitable supporting electrolytes are salts comprising a cation and a compatible, noncoordinating anion, A^- . Preferred supporting electrolytes are salts corresponding to the formula G^+A^- ; wherein:

25 G^+ is a cation which is nonreactive towards the starting and resulting complex, and
 A^- is as previously defined.

Examples of cations, G^+ , include tetrahydrocarbyl substituted ammonium or phosphonium cations having up to 40 nonhydrogen atoms. Preferred cations are the tetra(n-butylammonium)- and tetraethylammonium- cations.

30 During activation of the complexes of the present invention by bulk electrolysis the cation of the supporting electrolyte passes to the counter electrode and A^- migrates to the working electrode to become the anion of the resulting oxidized product. Either the solvent or the cation of the supporting electrolyte is reduced at the counter electrode in equal molar quantity with the amount of oxidized metal complex formed at the working electrode. Preferred
35 supporting electrolytes are tetrahydrocarbylammonium salts of tetrakis(perfluoroaryl) borates

having from 1 to 10 carbons in each hydrocarbyl or perfluoroaryl group, especially tetra(n-butylammonium)tetrakis(pentafluorophenyl) borate.

A further recently discovered electrochemical technique for generation of activating cocatalysts is the electrolysis of a disilane compound in the presence of a source of a noncoordinating compatible anion. This technique is more fully disclosed and claimed in the previously mentioned USP 5,625,087.

The foregoing electrochemical activating technique and activating cocatalysts may also be used in combination. An especially preferred combination is a mixture of a tri(hydrocarbyl)aluminum or tri(hydrocarbyl)borane compound having from 1 to 4 carbons in each hydrocarbyl group with an oligomeric or polymeric alumoxane compound.

The molar ratio of catalyst/cocatalyst employed preferably ranges from 1:10,000 to 100:1, more preferably from 1:5000 to 10:1, most preferably from 1:1000 to 1:1. Alumoxane, when used by itself as an activating cocatalyst, is employed in large quantity, generally at least 100 times the quantity of metal complex on a molar basis. Tris(pentafluorophenyl)borane, where used as an activating cocatalyst is employed in a molar ratio to the metal complex of form 0.5:1 to 10:1, more preferably from 1:1 to 6:1 most preferably from 1:1 to 5:1. The remaining activating cocatalysts are generally employed in approximately equimolar quantity with the metal complex.

The process may be used to polymerize ethylenically unsaturated monomers having from 3 to 20 carbon atoms either alone or in combination. Preferred monomers include monovinylidene aromatic monomers, 4-vinylcyclohexene, vinylcyclohexane, norbornadiene and C₃₋₁₀ aliphatic α -olefins (especially ethylene, propylene, isobutylene, 1-butene, 1-hexene, 3-methyl-1-pentene, 4-methyl-1-pentene, and 1-octene), C₄₋₄₀ dienes, and mixtures thereof. Most preferred monomers are ethylene, and mixtures of ethylene, propylene and a nonconjugated diene, especially ethylenenorbornene.

In general, the polymerization may be accomplished at conditions well known in the prior art for Ziegler-Natta or Kaminsky-Sinn type polymerization reactions, that is, temperatures from 0 to 250 °C, preferably 30 to 200 °C and pressures from atmospheric to 10,000 atmospheres (1000 MPa). Suspension, solution, slurry, gas phase, solid state powder polymerization or other process condition may be employed if desired. A support, especially silica, alumina, or a polymer (especially poly(tetrafluoroethylene) or a polyolefin) may be employed, and desirably is employed when the catalysts are used in a gas phase polymerization process. The support is preferably employed in an amount to provide a weight ratio of catalyst (based on metal):support from 1:100,000 to 1:10, more preferably from 1:50,000 to 1:20, and most preferably from 1:10,000 to 1:30.

In most polymerization reactions the molar ratio of catalyst:polymerizable compounds employed is from 10^{-12} :1 to 10^{-1} :1, more preferably from 10^{-9} :1 to 10^{-5} :1.

Suitable solvents for polymerization are inert liquids. Examples include straight and branched-chain hydrocarbons such as isobutane, butane, pentane, hexane, heptane, octane, 5 and mixtures thereof; cyclic and alicyclic hydrocarbons such as cyclohexane, cycloheptane, methylcyclohexane, methylcycloheptane, and mixtures thereof; perfluorinated hydrocarbons such as perfluorinated C_{4-10} alkanes, and aromatic and alkyl-substituted aromatic compounds such as benzene, toluene, xylene, and ethylbenzene and the like. Suitable solvents also include liquid olefins which may act as monomers or comonomers including ethylene, 10 propylene, butadiene, cyclopentene, 1-hexene, 1-hexane, 4-vinylcyclohexene, vinylcyclohexane, 3-methyl-1-pentene, 4-methyl-1-pentene, 1,4-hexadiene, 1-octene, 1-decene, styrene, divinylbenzene, allylbenzene, and vinyltoluene (including all isomers alone or in admixture), and the like. Mixtures of the foregoing are also suitable.

The catalysts may be utilized in combination with at least one additional homogeneous 15 or heterogeneous polymerization catalyst in separate reactors connected in series or in parallel to prepare polymer blends having desirable properties. An example of such a process is disclosed in WO 94/00500, equivalent to U. S. Serial Number 07/904,770, as well as WO 94/17112, equivalent to U. S. Serial Number 08/10958, filed January 29, 1993.

Utilizing the catalysts of the present invention copolymers having high comonomer 20 incorporation and correspondingly low density, yet having a low melt index may be readily prepared. That is, high molecular weight polymers are readily attained by use of the present catalysts even at elevated reactor temperatures. This result is highly desirable because the molecular weight of α -olefin copolymers can be readily reduced by the use of hydrogen or similar chain transfer agent, however increasing the molecular weight of α -olefin copolymers is 25 usually only attainable by reducing the polymerization temperature of the reactor.

Disadvantageously, operation of a polymerization reactor at reduced temperatures significantly increases the cost of operation since heat must be removed from the reactor to maintain the reduced reaction temperature, while at the same time heat must be added to the reactor effluent to vaporize the solvent. In addition, productivity is increased due to improved polymer solubility, 30 decreased solution viscosity, and a higher polymer concentration. Utilizing the present catalysts, α -olefin homopolymers and copolymers having densities from 0.85 g/cm^3 to 0.96 g/cm^3 , and melt flow rates from 0.001 to 10.0 dg/min are readily attained in a high temperature process.

The polymers of the present invention will preferably have high levels of long chain 35 branching. The use of the catalysts described herein in the production of the polymers of the

present invention in continuous polymerization processes, especially continuous, solution polymerization processes, allows for elevated reactor temperatures which favor the formation of vinyl terminated polymer chains that may be incorporated into a growing polymer, thereby giving a long chain branch. The use of the catalysts described herein in the production of the polymers of the present invention advantageously allows for the economical production of ethylene/ α -olefin copolymers having processability similar to high pressure, free radical produced low density polyethylene.

The polymers of the present invention will preferably have at least 0.03 , more preferably at least 0.04 vinyls/1000 carbons, as determined by FTIR .

The polymers of the invention will preferably be characterized as having long chain branching, preferably from 0.01 to 3 long chain branches/1000 carbons. Methods for determining the amount of long chain branching present, both qualitatively and quantitatively, are known in the art.

For qualitative methods for determination, see, for instance, U.S. Patent Nos. 5,272,236 and 5,278,272, which disclose the use of an apparent shear stress versus apparent shear rate plot to identify melt fracture phenomena. Preferred polymers of the present invention will possess a gas extrusion rheology such that: (a) the critical shear rate at the onset of surface melt fracture for the inventive polymer is at least 50 percent greater than the critical shear rate at the onset of surface melt fracture for a linear polymer having the same comonomer or comonomers and having an I_2 , M_w/M_n and density within ten percent of that of the inventive polymer, and wherein the respective critical shear rates of the inventive polymer and the linear polymer are measured at the same melt temperature using a gas extrusion rheometer; or (b) the critical shear rate at the onset of gross melt fracture is greater than 4×10^6 dynes/cm², as determined by gas extrusion rheometry.

For quantitative methods for determination, see, for instance, U.S. Patent Nos. 5,272,236 and 5,278,272; Randall (Rev. Macromol. Chem. Phys., C29 (2&3), p. 285-297), which discusses the measurement of long chain branching using ¹³C nuclear magnetic resonance spectroscopy, Zimm, G.H. and Stockmayer, W.H., J. Chem. Phys., 17, 1301 (1949); and Rudin, A., Modern Methods of Polymer Characterization, John Wiley & Sons, New York (1991) pp. 103-112, which discuss the use of gel permeation chromatography coupled with a low angle laser light scattering detector (GPC-LALLS) and gel permeation chromatography coupled with a differential viscometer detector (GPC-DV).

The inventive polymers are further characterized as having a melt flow ratio (I_{10}/I_2) which may be varied independently of the polydispersity index, that is, the molecular weight distribution M_w/M_n . This feature accords the inventive polymers with a high degree of processability despite a narrow molecular weight distribution. Preferably, the polymers of the invention will have an I_{10}/I_2 which is at least 10, preferably at least 15, with I_{10}/I_2 values exceeding 20 being possible.

ATREF/DV may be further used to illustrate the fact that the preferred copolymers of the invention are characterized as having a bimodal molecular weight distribution. It is significant to note that the ATREF peaks are quite sharp, and are distinguishable from copolymers which are produced using supported catalyst systems. Specifically, (i) the maximum ATREF peak height is measured, (ii) the width of the total ATREF peak at $\frac{1}{2}$ the maximum peak height is measured, the ATREF shape factor is calculated, that is, the ratio (ii)/(i), and the average ATREF elution temperature is determined, that is, (minimum ATREF elution temp + maximum ATREF elution temp)/2. The polymers of the invention will be characterized as having an ATREF curve which satisfies the following inequality:

$$\text{ATREF Shape Factor} \leq 0.90 - 0.00626 (\text{Average Elution Temperature})$$

which preferably satisfies the following inequality:

$$\text{ATREF Shape Factor} \leq 0.75 - 0.00626 (\text{Average Elution Temperature}).$$

and which most preferably satisfies the following inequality:

$$\text{ATREF Shape Factor} \leq 0.70 - 0.00626 (\text{Average Elution Temperature}).$$

The polymer compositions of the invention are characterized as having a fraction which has a higher crystallinity than the other fraction. The presence of the higher crystallinity fraction translates to an enhancement in the upper service temperature of the polymer compositions of the invention, with respect to the comparative compositions. The upper service temperature may be defined as the intersection of a line drawn across the upper non-melted plateau region and the descending melting transition region of the log G1 versus temperature plot. Preferably the upper service temperature of the olefin interpolmer (UST (interpolymer)) is greater than the upper service temperature of a physical blend (UST (blend)) of a first homogeneous olefin polymer having a density equal to the first density, an I_2 equal to the first I_2 , and which is provided in the first weight percent, and a second homogeneous olefin polymer having a density equal to the second density, an I_2 equal to the second I_2 , and which is provided in the second weight percent, in accordance with the following inequality:

UST (interpolymer) - UST (blend) $\geq 256 - 275$ (density of olefin interpolymer).

The polymers of the present invention will preferably have improved processing properties, whether they result from polymerizing ethylene alone or ethylene/ α -olefin mixtures with low levels of a "H" branch inducing diene, such as norbornadiene, 1,7-octadiene, or 1,9-decadiene. The unique combination of elevated reactor temperatures, high molecular weight (or low melt indices) at high reactor temperatures and high comonomer reactivity advantageously allows for the economical production of polymers having excellent physical properties and processability. Preferably such polymers comprise ethylene, a C_{3-20} α -olefin and a "H"-branching comonomer. Preferably, such polymers are produced in a solution process, most preferably a continuous solution process.

As previously mentioned, the polymers of the present invention may be prepared via a solution or slurry process both of which are previously known in the art. Kaminsky, J. Poly. Sci., Vol. 23, pp. 2151-64 (1985) reported the use of a soluble bis(cyclopentadienyl) zirconium dimethyl-alumoxane catalyst system for solution polymerization of EP and EPDM elastomers. USP 5,229,478 disclosed a slurry polymerization process utilizing similar bis(cyclopentadienyl) zirconium based catalyst systems.

In general terms, it is desirable to produce such EP and EPDM elastomers under conditions of increased reactivity of the diene monomer component. The reason for this was explained in USP 5,229,478 in the following manner, which still remains true despite the advances attained in such reference. A major factor affecting production costs and hence the utility of an EPDM is the diene monomer cost. The diene is a more expensive monomer material than ethylene or propylene. Further, the reactivity of diene monomers with previously known metallocene catalysts is lower than that of ethylene and propylene. Consequently, to achieve the requisite degree of diene incorporation to produce an EPDM with an acceptably fast cure rate, it has been necessary to use a diene monomer concentration which, expressed as a percentage of the total concentration of monomers present, is in substantial excess compared to the percentage of diene desired to be incorporated into the final EPDM product. Since substantial amounts of unreacted diene monomer must be recovered from the polymerization reactor effluent for recycle, the cost of production is increased unnecessarily.

Further adding to the cost of producing an EPDM is the fact that, generally, the exposure of an olefin polymerization catalyst to a diene, especially the high concentrations of diene monomer required to produce the requisite level of diene incorporation in the final EPDM product, often reduces the rate or activity at which the catalyst will cause polymerization of ethylene and propylene monomers to proceed. Correspondingly, lower throughputs and longer

reaction times have been required, compared to the production of an ethylene-propylene copolymer elastomer or other α -olefin copolymer elastomer.

The present catalyst system advantageously allows for increased diene reactivity thereby preparing EPDM polymers in high yield and productivity. Additionally, the catalyst
5 system of the present invention achieves the economical production of EPDM polymers with diene contents of up to 20 weight percent or higher, which polymers possess highly desirable fast cure rates.

The non-conjugated diene monomer can be a straight chain, branched chain or cyclic hydrocarbon diene having from 6 to 15 carbon atoms. Examples of suitable non-conjugated
10 dienes are straight chain acyclic dienes such as 1,4-hexadiene and 1,6-octadiene; branched chain acyclic dienes such as 5-methyl-1,4-hexadiene; 3,7-dimethyl-1,6-octadiene; 3,7-dimethyl-1,7-octadiene and mixed isomers of dihydromyricene and dihydroocinene; single ring alicyclic dienes such as 1,3-cyclopentadiene; 1,4-cyclohexadiene; 1,5-cyclooctadiene and 1,5-cyclododecadiene; and multi-ring alicyclic fused and bridged ring dienes such as
15 tetrahydroindene, methyl tetrahydroindene, dicyclopentadiene; bicyclo-(2,2,1)-hepta-2, 5-diene; alkenyl, alkylidene, cycloalkenyl and cycloalkylidene norbornenes such as 5-methylene-2-norbornene (MNB); 5-propenyl-2-norbornene, 5-isopropylidene-2-norbornene, 5-(4-cyclopentenyl)-2-norbornene, 5-cyclohexylidene-2-norbornene, 5-vinyl-2-norbornene and norbornadiene. Another preferred diene is piperylene.

20 Of the dienes typically used to prepare EPDMs, the particularly preferred dienes are 1,4-hexadiene (HD), 5-ethylidene-2-norbornene (ENB), 5-vinylidene-2-norbornene (VNB), 5-methylene-2-norbornene (MNB), and dicyclopentadiene (DCPD). The especially preferred dienes are 5-ethylidene-2-norbornene (ENB) and 1,4-hexadiene (HD). Another preferred diene is piperylene.

25 The preferred EPDM elastomers may contain 20 up to 90 weight percent ethylene, more preferably 30 to 85 weight percent ethylene, most preferably 35 to 80 weight percent ethylene.

The α -olefins suitable for use in the preparation of elastomers with ethylene and dienes are preferably C_{3-18} α -olefins. Illustrative non-limiting examples of such α -olefins
30 are propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, 1-decene, and 1-dodecene. The α -olefin is generally incorporated into the EPDM polymer at 10 to 80 weight percent, more preferably at 20 to 65 weight percent. The non-conjugated dienes are generally incorporated into the EPDM at 0.5 to 20 weight percent; more, preferably at 1 to 15 weight percent, and most preferably at 3 to 12 weight percent. If desired, more than one diene may be incorporated

simultaneously, for example HD and ENB, with total diene incorporation within the limits specified above.

The catalyst system may be prepared as a homogeneous catalyst by addition of the requisite components to a solvent in which polymerization will be carried out by solution polymerization procedures. The catalyst system may also be prepared and employed as a heterogeneous catalyst by adsorbing the requisite components on a catalyst support material such as silica gel, alumina or other suitable inorganic support material. When prepared in heterogeneous or supported form, it is preferred to use silica as the support material. The heterogeneous form of the catalyst system is employed in a slurry polymerization. As a practical limitation, slurry polymerization takes place in liquid diluents in which the polymer product is substantially insoluble. Preferably, the diluent for slurry polymerization is one or more hydrocarbons with less than 5 carbon atoms. If desired, saturated hydrocarbons such as ethane, propane or butane may be used in whole or part as the diluent. Likewise the α -olefin monomer or a mixture of different α -olefin monomers may be used in whole or part as the diluent. Most preferably the diluent comprises in at least major part the α -olefin monomer or monomers to be polymerized.

In contrast, solution polymerization conditions utilize a solvent for the respective components of the reaction, particularly the EP or EPDM polymer. Preferred solvents include mineral oils and the various hydrocarbons which are liquid at reaction temperatures. Illustrative examples of useful solvents include alkanes such as pentane, iso-pentane, hexane, heptane, octane and nonane, as well as mixtures of alkanes including kerosene and Isopar ETM, available from Exxon Chemicals Inc.; cycloalkanes such as cyclopentane and cyclohexane; and aromatics such as benzene, toluene, xylenes, ethylbenzene and diethylbenzene.

At all times, the individual ingredients as well as the recovered catalyst components must be protected from oxygen and moisture. Therefore, the catalyst components and catalysts must be prepared and recovered in an oxygen and moisture free atmosphere. Preferably, therefore, the reactions are performed in the presence of an dry, inert gas such as, for example, nitrogen.

Ethylene is added to the reaction vessel in an amount to maintain a differential pressure in excess of the combined vapor pressure of the α -olefin and diene monomers. The ethylene content of the polymer is determined by the ratio of ethylene differential pressure to the total reactor pressure. Generally the polymerization process is carried out with a differential pressure of ethylene of from 10 to 1000 psi (70 to 7000 kPa), most preferably from 40 to 400 psi (30 to 300 kPa). The polymerization is generally conducted at a temperature of from 25 to 200 °C, preferably from 75 to 170 °C, and most preferably from greater than 95 to 140 °C.

The polymerization may be carried out as a batchwise or a continuous polymerization process. A continuous process is preferred, in which event catalyst, ethylene, α -olefin, and optionally solvent and diene are continuously supplied to the reaction zone and polymer product continuously removed therefrom.

5 Without limiting in any way the scope of the invention, one means for carrying out such a polymerization process is as follows. In a stirred-tank reactor propylene monomer is introduced continuously together with solvent, diene monomer and ethylene monomer. The reactor contains a liquid phase composed substantially of ethylene, propylene and diene monomers together with any solvent or additional diluent. If desired, a small amount of a "H"-
10 branch inducing diene such as norbornadiene, 1,7-octadiene or 1,9-decadiene may also be added. Catalyst and cocatalyst are continuously introduced in the reactor liquid phase. The reactor temperature and pressure may be controlled by adjusting the solvent/monomer ratio, the catalyst addition rate, as well as by cooling or heating coils, jackets or both. The polymerization rate is controlled by the rate of catalyst addition. The ethylene content of the polymer product is
15 determined by the ratio of ethylene to propylene in the reactor, which is controlled by manipulating the respective feed rates of these components to the reactor. The polymer product molecular weight is controlled, optionally, by controlling other polymerization variables such as the temperature, monomer concentration, or by a stream of hydrogen introduced to the reactor, as is well known in the art. The reactor effluent is contacted with a catalyst kill agent
20 such as water. The polymer solution is optionally heated, and the polymer product is recovered by flashing off gaseous ethylene and propylene as well as residual solvent or diluent at reduced pressure, and, if necessary, conducting further devolatilization in equipment such as a devolatilizing extruder. In a continuous process, the mean residence time of the catalyst and polymer in the reactor generally is from 5 minutes to 8 hours, and preferably from 10 minutes to
25 6 hours.

In a preferred manner of operation, the polymerization is conducted in a continuous solution polymerization system comprising two reactors connected in series or parallel. In one reactor, a product having a molecular weight (M_w) of from 300,000 to 600,000, more preferably 400,000 to 500,000, is formed while in the second reactor a product of a second molecular
30 weight (M_w) of 50,000 to 300,000 is formed. The final product is a blend of the two reactor effluents which are combined prior to devolatilization to result in a uniform blend of the two polymer products. Such a dual reactor process allows for the preparation of products having improved properties. In a preferred embodiment the reactors are connected in series, that is effluent from the first reactor is charged to the second reactor and fresh monomer, solvent and
35 hydrogen is added to the second reactor. Reactor conditions are adjusted such that the weight ratio of polymer produced in the first reactor to that produced in the second reactor is from

20:80 to 80:20. In addition the temperature of the second reactor is controlled to produce the lower molecular weight product. This system beneficially allow for production of EPDM products having a large range of Mooney viscosities, as well as excellent strength and processability. Preferably the Mooney viscosity (ASTM D1646-94, ML1+4 at 125 °C) of the resulting product is
5 adjusted to fall in the range from 1 to 200, preferably from 5 to 150, and most preferably from 10 to 110.

Examples

The skilled artisan will appreciate that the invention disclosed herein may be practiced in the absence of any component which has not been specifically disclosed. The following
10 examples are provided as further illustration of the invention and are not to be construed as limiting. Unless stated to the contrary all parts and percentages are expressed on a weight basis.

¹H and ¹³C NMR spectra were recorded on a Varian XL (300 MHz) spectrometer. Chemical shifts were determined relative to TMS or through the residual CHCl₃ in CDCl₃ or the
15 residual C₆HD₅ in C₆D₆, relative to TMS. Tetrahydrofuran (THF), diethylether, toluene, and hexane were used following passage through double columns charged with activated alumina and alumina supported mixed metal oxide catalyst (Q-5[®] catalyst, available from Engelhard Corp.) The compounds n-BuLi, KH, all Grignard reagents, and 1,4-diphenyl-1,3-butadiene were
20 all used as purchased from Aldrich Chemical Company. All syntheses were performed under dry nitrogen atmosphere using a combination of glove box and high vacuum techniques.

Preparation of Catalyst One: [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] Titanium Dimethyl

Preparation of Dimethylsilyl(2,3,4,6-tetramethylindenyl)(isopropylamine):

Dimethylsilyl(2,3,4,6-tetramethylindenyl)Cl (22.29 grams, 84.17 mmol) was stirred in
25 THF as i-PrNH₂ (28.68 mL, 336.7 mmol) was added. The mixture was stirred for 16 hours. The volatiles were removed under reduced pressure. The residue was extracted with hexane and filtered through a diatomaceous earth filter aid on a 10-15 mm glass frit. The hexane was removed under reduced pressure to afford the product as a yellow oil. Yield; 17.23 grams, 71 percent.

Preparation of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] titanium Dichloride:

In the drybox, 17.23 grams (59.93 mmol) of dimethylsilyl(2,3,4,6-tetramethylindenyl)(isopropylamine) was dissolved in 350 mL of hexane in a 500 mL round-

bottom schlenk flask. Two equivalents of n-BuLi (47.94 mL, 2.5 M in hexanes) were then added via syringe. The reaction was stirred for twelve hours. The solvent was removed under reduced pressure to afford a orange powder. The powder was dissolved in 250 mL of THF. $\text{TiCl}_3(\text{THF})_3$ (22.2 grams, 59.93 mmol) was added as a solid. After 15 minutes, CH_2Cl_2 (2.48 mL, 29.97 mmol) was added. After two hours, the solvent was removed under reduced pressure. The residue was extracted with toluene and filtered through a diatomaceous earth filter aid on a 10-15 mm glass frit. The toluene was removed under reduced pressure. The residue was slurried in hexane and filtered over a 10 to 15 mm glass frit. The residue was dried under reduced pressure to afford a red powder. Yield; 12.3 grams, 51 percent.

10 Preparation of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] titanium Dimethyl:

In the drybox, [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium dichloride (6.92 grams, 17.12 mmol) was suspended in 150 mL of Et_2O in a 250 mL round bottom flask. Two equivalents of a 3.0 M THF solution of MeMgCl (11.41 mL, 34.23 mmol) were added. The mixture was stirred for one hour. The volatiles were removed under reduced pressure. The residue was extracted with hexane and filtered through a diatomaceous earth filter aid on a 10 to 15 mm glass frit. The hexane was removed under reduced pressure to afford a orange powder. Yield; 5.8 grams, 93 percent.

20 Preparation of Catalyst Composition Two [(N-cyclohexylamido)(dimethyl) (2,3,4,6-tetramethylindenyl)silane] titanium dimethyl:

Preparation of dimethylsilyl(2,3,4,6-tetramethylindenyl)(cyclohexylamine):

Dimethylsilyl(2,3,4,6-tetramethylindenyl)Cl (9.95g, 37.8 mmol) was stirred in hexane (200 mL) as NEt_3 (4.1 g, 40.6 mmol) was added followed by cyclohexylamine (4.05g, 40.8 mmol). This mixture was allowed to stir for 24 hours at 20°C. After the reaction period the mixture was filtered and the desired product isolated as a pale yellow oil following the removal of the volatiles (10.98 g, 89.3 percent yield).

Preparation of Dilithium (N-cyclohexylamido)(dimethyl) (2,3,4,6-tetramethylindenyl)silane:

In the drybox 4.0 g (12.6 mmol) of (N-cyclohexylamino)(dimethyl) (2,3,4,6-tetramethylindenyl) silane was dissolved in 300 ml of hexane. To this solution 12.6 ml (25.2 mmol) of nBuLi (2.00 M) was added dropwise at 20°C. Upon complete addition of the nBuLi the solution was stirred for 12 hours after which the solvent was removed under reduced pressure to give, 4.12 g (96 percent yield) of a yellow-orange powder.

Preparation of [(N-cyclohexylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] Titanium Dichloride:

In the drybox 4.63 g (12.5 mmol) of $\text{TiCl}_3(\text{THF})_3$ was dissolved in 75 ml of THF. To this solution, 4.12 g (12.5 mmol) of dilithium (N-cyclohexylamido) (dimethyl)(2,3,4,6-tetramethylindenyl)silane was added as a solid while stirring at 20°C. The solution was then stirred for 45 minutes. After this time period 1.73 g of PbCl_2 (6.25 mmol) was added and the solution stirred for 45 minutes. The THF was then removed under reduced pressure. The residue was then extracted with toluene, the solution filtered, and the toluene removed under reduced pressure. The residue was then triturated with hexane and the solution volume reduced whereupon a red precipitate was formed and collected via filtration and washed with cold (0°C) hexane. The solid product was dried under vacuum to yield 1.70g (31 percent yield) of product.

Preparation of [(N-cyclohexylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] titanium Dimethyl:

In the drybox 0.300 g of [(N-t-cyclohexylamino)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium dichloride (0.675 mmol) was suspended in 50 ml of Et_2O at 20°C. To this suspension, 0.45 ml of MeMgI (3.0 M) was added dropwise while stirring over a 20 minute period. After the addition MeMgI was completed, the solution was stirred for 40 minutes. Then the Et_2O was removed under reduced pressure and the residue extracted with hexane, the solution filtered, the filtrate evaporated to dryness under reduced pressure to give 0.27 g (100 percent yield) of product.

Preparation of Catalyst Composition Three [(tetramethylcyclopentadienyl) dimethyl(t-butylamido)silane] titanium 1,3-pentadiene

25 Preparation of $\text{TiCl}_3(\text{DME})_{1.5}$

The apparatus (referred to as R-1) was set-up in the hood and purged with nitrogen; it consisted of a 10 L glass kettle with flush mounted bottom valve, 5-neck head, polytetrafluoroethylene gasket, clamp, and stirrer components (bearing, shaft, and paddle). The necks were equipped as follows: stirrer components were put on the center neck, and the outer necks had a reflux condenser topped with gas inlet/outlet, an inlet for solvent, a thermocouple, and a stopper. Dry, deoxygenated dimethoxyethane (DME) was added to the flask (approx. 5.2 L). In the drybox, 300 g of TiCl_3 was weighed into an equalizing powder addition funnel; the funnel was capped, removed from the drybox, and put on the reaction kettle in place of the

stopper. The TiCl_3 was added over about 10 minutes with stirring. After the addition was completed, additional DME was used to wash the rest of the TiCl_3 into the flask. This process was then repeated with 325 g of additional TiCl_3 , giving a total of 625 g. The addition funnel was replaced with a stopper, and the mixture heated to reflux. The color changed from purple to
 5 pale blue. The mixture was heated for about 5 hours, cooled to room temperature, the solid was allowed to settle, and the supernatant was decanted from the solid. The $\text{TiCl}_3(\text{DME})_{1.5}$ was left in R-1 as a pale blue solid.

Preparation of $[(\text{Me}_4\text{C}_5)\text{SiMe}_2\text{NtBu}][\text{MgCl}]_2$

The apparatus (referred to as R-2) was set-up as described for R-1, except that flask
 10 size was 30 L. The head was equipped with seven necks; stirrer in the center neck, and the outer necks containing condenser topped with nitrogen inlet/outlet, vacuum adapter, reagent addition tube, thermocouple, and stoppers. The flask was loaded with 7 L of toluene, 3.09 kg of 2.17 M iPrMgCl in Et_2O , 250 mL of THF, and 1.03 kg of $(\text{Me}_4\text{C}_5\text{H})\text{SiMe}_2\text{NtBu}$. The mixture was then heated, and the ether allowed to boil off into a trap cooled to -78°C . After three hours,
 15 the temperature of the mixture had reached 80°C , at which time a white precipitate formed. The temperature was then increased to 90°C over 30 minutes and held at this temperature for 2 hours. At the end of this time, the heater was turned off, and 2 L of DME was added to the hot, stirring solution, resulting in the formation of additional precipitate. The solution was allowed to cool to room temperature, the material was allowed to settle, and the supernatant
 20 was decanted from the solid. An additional wash was done by adding toluene, stirring for several minutes, allowing the solids to settle, and decanting the toluene solution. The $[(\text{Me}_4\text{C}_5)\text{SiMe}_2\text{NtBu}][\text{MgCl}]_2$ was left in R-2 as an off-white solid.

Preparation of $[(\eta_5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{NtBu}]\text{Ti}(\eta_4\text{-1,3-pentadiene})$

The materials in R-1 and R-2 were slurried in DME (the total volumes of the mixtures
 25 were approx. 5 L in R-1 and 12 L in R-2). The contents of R-1 were transferred to R-2 using a transfer tube connected to the bottom valve of the 10 L flask and one of the head openings in the 30 L flask. The remaining material in R-1 was washed over using additional DME. The mixture darkened quickly to a deep red/brown color. After 15 minutes, 1050 mL of 1,3-pentadiene and 2.60 kg of 2.03 M nBuMgCl in THF were added simultaneously. The maximum
 30 temperature reached in the flask during this addition was 53°C . The mixture was stirred for 2 hours, then approx. 11 L of solvent was removed under vacuum. Hexane was then added to the flask to a total volume of 22 L. The material was allowed to settle, and the liquid layer (12 L) was decanted into another 30 L glass kettle (R-3). An additional 15 liters of product solution was collected by adding hexane to R-2, stirring for 50 minutes, again allowing to settle, and

decanting. This material was combined with the first extract in R-3. The solvent in R-3 was removed under vacuum to leave a red/black solid, which was then extracted with toluene. This material was transferred into a storage cylinder. Analysis indicated that the solution (11.75 L) was 0.255 M in titanium; this is equal to 3.0 moles of $[(\eta^5\text{-Me}_4\text{C}_5)\text{SiMe}_2\text{NtBu}]\text{Ti}(\eta^4\text{-1,3-pentadiene})$ or 1095 g. This is a 74 percent yield based on the titanium added as TiCl_3 .

Preparation of the Soluble Borate Cocatalyst ((bis(hydrogenated-tallowalkyl)methylamine) (B-FABA)

Methylcyclohexane (1200 mL) was placed in a 2L cylindrical flask. While stirring, bis(hydrogenated-tallowalkyl)methylamine (ARMEEN® M2HT, 104 g, ground to a granular form) was added to the flask and stirred until completely dissolved. Aqueous HCl (1M, 200 mL) was added to the flask, and the mixture was stirred for 30 minutes. A white precipitate formed immediately. At the end of this time, $\text{LiB}(\text{C}_6\text{F}_5)_4 \cdot \text{Et}_2\text{O} \cdot 3 \text{ LiCl}$ (MW = 887.3; 177.4 g) was added to the flask. The solution began to turn milky white. The flask was equipped with a 6 inch (15 cm) Vigreux column topped with a distillation apparatus and the mixture was heated (140°C external wall temperature). A mixture of ether and methylcyclohexane was distilled from the flask. The two-phase solution was now only slightly hazy. The mixture was allowed to cool to room temperature, and the contents were placed in a 4 L separatory funnel. The aqueous layer was removed and discarded, and the organic layer was washed twice with H_2O , and the aqueous layers again discarded. The product solution was divided into two equal portions for the evaluation of two workup procedures. These H_2O saturated methylcyclohexane solutions were measured to contain 0.48 weight percent diethylether (Et_2O).

The solution (600 mL) was transferred into a 1 L flask, sparged thoroughly with nitrogen, and transferred into the drybox. The solution was passed through a column (1 inch (2.5 cm) diameter, 6 inch (15 cm) height) containing 13 times molecular sieves. This reduced the level of Et_2O from 0.48 weight percent to 0.28 weight percent. The material was then stirred over fresh 13 times sieves (20 g) for four hours. The Et_2O level was then measured to be 0.19 weight percent. The mixture was then stirred overnight, resulting in a further reduction in Et_2O level to approximately 40 ppm. The mixture was filtered using a funnel equipped with a glass frit having a pore size of 10 to 15 μm to give a clear solution (the molecular sieves were rinsed with additional dry methylcyclohexane). The concentration was measured by gravimetric analysis yielding a value of 16.7 weight percent.

Polymerization of Polymers of the Examples of the Invention and of the Comparative Examples:

The polymer products of the Examples were produced in a solution polymerization process using a well-mixed recirculating loop reactor. In the case of polymers produced with

Catalyst One, the additive package was 1500 ppm calcium stearate, 600 ppm Irganox™ 1076 hindered phenolic antioxidant, and 950 ppm PEPQ (tetrakis(2,4-di-t-butylphenyl)-4,4'-biphenylene diphosphonite) (available from Clariant Corporation). In the case of polymers produced with Catalyst Two, the additive package was 1450 ppm calcium stearate, 600 ppm Irganox™ 1076, and 930 ppm PEPQ. In the case of polymers produced with Catalyst Three, the additive package was 640 ppm calcium stearate, 260 ppm Irganox™ 1076, and 400 ppm PEPQ.

The ethylene and the hydrogen (as well as any ethylene and hydrogen which were recycled from the separator, were combined into one stream before being introduced into the diluent mixture, a mixture of C₈-C₁₀ saturated hydrocarbons, for example, ISOPAR™-E (available from Exxon Chemical Company) and the comonomer 1-octene.

The metal complex and cocatalysts were combined into a single stream and were also continuously injected into the reactor. In the case of Examples 1a, 1b, and 1c, the catalyst was as prepared in Catalyst Preparation One. In the case of Examples 2a, 2b, 2c, and 2d, the catalyst was as prepared in Catalyst Preparation Two. In the case of the Comparative Examples C-3a and C-3b, the catalyst was as prepared in Catalyst Preparation Three. In each of the Examples and Comparative Examples, the Primary and Secondary cocatalysts were as prepared in Cocatalyst Example One and Cocatalyst Example Two.

Sufficient residence time was allowed for the metal complex and cocatalyst to react prior to introduction into the polymerization reactor. The reactor pressure was held constant at about 450 to 475 psig (3.1 to 3.3 MPa).

After polymerization, the reactor exit stream was introduced into a separator where the molten polymer was separated from the unreacted comonomer(s), unreacted ethylene, unreacted hydrogen, and diluent mixture stream, which was in turn recycled for combination with fresh comonomer, ethylene, hydrogen, and diluent, for introduction into the reactor. The molten polymer was subsequently strand chopped or pelletized, and, after being cooled in a water bath or pelletizer, the solid pellets were collected. Table One describes the polymerization conditions and the resultant polymer properties.

Table 1. Run Conditions

Example Number	Catalyst	solvent feed (kg/hr)	ethylene feed (kg/hr)	octene feed (kg/hr)	Feed temp (°C)	solvent /ethylene ratio	R1 temp (°C)	Oil temp (°C)	ethylene conversion percent	Catalyst concentration (ppm Ti)	Catalyst timer percent	B-FABA timer percent	DIBAL-BOT timer percent	B/Ti (molar)	Al/Ti (molar)
C-3a	Three	21.0	2.17	2.20	0.0	10.69	88.0	77	84.0	37					
1a	One	21.0	2.17	2.00	-0.4	10.60	122.0	119	85.0	47	25	20	25	10.4	26.0
1b	One	21.0	2.17	2.20	-0.4	10.69	122.0	119	85.6	47	60	175	25	4.9	0.2
1c	One	21.0	2.17	2.20	-0.4	10.69	122.0	119	85.6	47	60	175	25	4.9	0.2
2a	Two	21.0	2.17	1.98	0.3	10.59	129.4	136	84.4	46	60	175	25	4.9	0.2
2b	Two	21.0	2.17	1.98	0.3	10.59	129.4	134	84.1	46	71	120	50	3.0	4.9
2c	Two	21.0	2.17	1.98	0.3	10.59	129.5	132	83.5	46	71	120	50	2.2	3.3
2d	Two	21.0	2.17	1.98	0.3	10.59	129.0	136	85.1	48	74	120	50	1.9	0.5
C-3b	Three	21.0	2.17	2.40	0.0	10.78	122.0	118	85.0		26	45	100	0.9	2.5

The following Table Two compares the melt index (I_2), density and melt flow ratio (I_{10}/I_2) of the ethylene/octene copolymers produced using Catalyst Composition Three with the polymers of the invention prepared using Catalyst Compositions One and Two. Significantly higher molecular weight copolymers were produced using Catalyst Compositions One and Two than were produced using Catalyst Composition Three. For example, at a reactor temperature of 122°C, Catalyst One produced a polymer having an I_2 of 0.7 dg/min, while Catalyst Three produced a polymer having an I_2 of 116 dg/min copolymer. The use of Catalysts One and Two is advantageous, in that they permit one to produce a copolymer of a specific molecular weight at a higher reactor temperature, thus reducing solution viscosity, reactor pressure drop, reactor fouling and improving the overall process economics.

As further illustrated in Table Two, the copolymers produced using Catalysts One and Two had higher melt flow ratios. Such higher melt flow ratios are desirable, in that copolymers with higher melt flow ratios are easier to process, for instance, significantly lower pressures and amps are observed during the conversion of such copolymers into plastic parts.

Table Two: Characterization Information for Polymers of the Examples and Comparative Examples

Example	Catalyst	Reaction temperature (°C)	I ₂ (g/10 min.)	I ₁₀	I ₁₀ /I ₂	Annealed Density (g/cm ³)
C-3a	Three	88.0	0.48	4.5	9.38	0.8667
1a	One	122.0	0.71	8.22	11.58	0.8710
1b	One	122.0	0.63	7.74	12.29	0.8700
1c	One	122.0	0.82	8.95	10.91	0.8703
2a	Two	129.4	0.5	7.61	15.22	0.8606
2b	Two	129.4	0.43	5.84	13.58	0.8612
2c	Two	129.5	0.38	5.47	14.39	0.8612
2d	Two	129.0	0.38	3.84	10.11	0.8615
C-3b	Three	122.0	116	650	6.00	0.8612
C-2a *	Two		0.49		6.53	0.8635

5 * Sample prepared in a batch reactor.

Batch polymerization experiments were performed using a 1 gallon stirred Autoclave Engineers reactor. The reactor was charged with 1440 g of Isopar E, the designated amounts of 1-octene, and hydrogen, and then heated to the desired temperature and saturated with ethylene to 450 psig (3.1MPa). The catalyst was prepared in a drybox by syringing together the catalyst, cocatalyst, and scavenger solutions with additional solvent to give a total volume of 17 mL. The catalyst solution was then transferred by syringe to a catalyst addition loop and injected into the reactor over approximately 4 minutes using a flow of high pressure solvent. The polymerization was allowed to proceed for 10 minutes while feeding ethylene on demand to maintain a pressure of 445 psig (3.07 MPa). The amount of ethylene consumed during the reaction was monitored using a mass flow meter. The polymer solution was dumped from the reactor into a nitrogen-purged glass kettle containing 10 to 20 mL of isopropanol. An aliquot of the additive solution described below was added to this kettle and the solution stirred thoroughly (the amount of additive used was chosen based on the total ethylene consumed during the polymerization). The polymer solution was dumped into a tray, air dried overnight, then thoroughly dried in a vacuum oven for two days. The weights of the polymers were recorded and the efficiency calculated as grams of polymer per gram of transition metal.

Differential scanning calorimeter (DSC) data for the polymers of the Examples and the Comparative Examples are set forth in the following Table Three:

Table Three: Differential scanning calorimetry (DSC) data for the polymer compositions of the invention and of the Comparative Examples

	Catalyst	DSC				Calculated		ASTM Annealed Density (g/cc)
		Tm1 (°C)	Tm2 (°C)	Tc1 (°C)	Tc2 (°C)	Tm1 Density (g/cc)	Tm2 Density (g/cc)	
C-3a	Three	46.32		30.79		0.866		0.8667
1a	One	74.73		63.39		0.884		0.8710
1b	One	74.33		63.79		0.884		0.8700
1c	One	77.99		65.93		0.886		0.8703
2a	Two	24.26	91.19	10.33	67.53	0.854	0.897	0.8606
2b	Two	26.85	91.19	11.66	67.59	0.855	0.897	0.8612
2c	Two	26.86	91.73	11.79	67.39	0.855	0.898	0.8612
2d	Two	29.06	91.79	13	67.6	0.856	0.898	0.8615
C-3b	Three	61.92		49.8		0.875		0.8712
C-2a*	Two	41.07	91.86	24.11	75.48	0.863	0.898	0.8635

5 Given the overall ASTM densities of the copolymers produced using Catalysts One and Two, the melting points (Tm's) and crystallization points (Tc's) were very different from those of the copolymers of the Comparative Examples prepared using Catalyst Three. This distinction is further exemplified in the DSC endograms of copolymers C-3a (Catalyst Three) and 1a (Catalyst One) are shown in Figures 2 and 3.

10 First, the copolymers of the invention prepared with Catalyst One had a Tm which is at least 10°C greater than that of the polymers of the Comparative Examples produced using Catalyst Three, which is expected to translate to an enhanced upper service temperature. Such higher upper service temperatures are clearly demonstrated by the dynamic mechanical data discussed below.

15 Moreover, as shown Figure 4 and Table Three, the DSC thermograms of copolymers produced using Catalyst Two have a distinct bimodal character. In fact, the DSC thermogram for such polymer of Example 1a corresponds to a DSC thermogram of a blend of two copolymers having densities of 0.855 and 0.897 g/cm³, respectively.

20 The bimodal characteristic of the polymers of the invention prepared using Catalyst Two is further exemplified in a micrograph of polymer 2a produced by transmission electron microscopy (TEM), wherein one can clearly see the lamellae produced by the higher density copolymer fraction. For example, as shown in Figure 5, well defined lamella were present in the polymer of Example 2a. These ribbon-like structures, with an aspect ratio of about 16 (1120Å x 70Å), appear relatively isolated in a matrix of granule-like fringed micelle structures, with an
25 aspect ratio close to unity (70Å). In contrast, well defined lamellae were not present in TEM

micrograph prepared for the copolymer of Comparative Example C-3a prepared using Catalyst Three, as shown in Figure 6 (although it did have some structures having an aspect ratio of about 6). The lack of lamellae existed despite the fact that the copolymer of Comparative Example C-3a had a higher density than that of the copolymer of Example 2a.

- 5 Assuming that octene is randomly incorporated into the copolymers of the invention and comparative examples, one can calculate the final density in accordance with the following equation:

$$1/\rho_f = w_1/\rho_1 + w_2/\rho_2$$

- 10 wherein ρ_f is the final density, ρ_1 and ρ_2 are the densities of the first and second component fractions, respectively, and w_1 and w_2 are the weight fractions of the component fractions.

The polymers of Examples 1b and 2a and Comparative Examples C-3a and C-2a* were analyzed for short chain branching distribution by ATREF. The results are set forth in the following Table Four:

Table 4: Measurement of Comonomer Incorporation by ATREF

Example	Catalyst	ATREF			Calculated		ASTM Annealed Density (g/cc)
		percent Purge	Elution Temp. (°C)	Calc'd Density (g/cc)	Tm1 Density (g/cc)	Tm2 Density (g/cc)	
C-3a	Three	100			0.866		0.8667
1b	One	63.8	53.00	0.8855	0.884		0.8700
2a	Two	92.3	62.45	0.8950	0.854	0.897	0.8606
C-2a *	Two	90.1	60.85	0.8934	0.863	0.898	0.8635

5 * Comparative Example C-2a was produced in a batch reactor.

The ATREF curves for Examples 1b and 2a and for Comparative Example C-3a are set forth in Figure 7a. Because the overall densities of these copolymers were relatively low, most of the copolymer eluted with the purge, that is, the copolymer did not crystallize from the solvent (trichlorobenzene). In fact, 100 percent of the copolymer of Comparative Example C-3a eluted with the purge. The ATREF data showed that both Catalysts One and Two produced copolymers which were bimodal in short chain branching distribution. More specifically, the bulk of the copolymer produced from these catalysts was a low density copolymer which eluted with the purge, but there was also a higher density copolymer which produced a peak in the ATREF chromatograms shown in Figure 7a. Comparing the copolymers of Catalyst One with that of Catalyst Two, Catalyst Two produced a smaller amount of the higher density copolymer. As shown in Table Four, the copolymer densities calculated from ATREF were similar to the DSC estimate. For example, although the copolymer of Example 2a had a density of 0.861 g/cm³, the ATREF peak corresponded to what one would typically see for a substantially linear ethylene/1-octene copolymer prepared using Catalyst Three and having a density of 0.895 g/cm³. This is consistent with the finding above that the copolymer of Example 1a, having a density of 0.871 g/cm³ exhibited a DSC endotherm which corresponded to what one would typically see for a substantially linear ethylene/1-octene copolymer prepared using Catalyst Three having a density of 0.897 g/cm³. See, for example, Figure 7b, which compares the ATREF of a copolymer produced with Catalyst Three having a density of 0.895 g/cm³, and I₂ of 1.6 g/10 min. and an I₁₀/I₂ of 9.9 with the copolymer of Example 2a.

Similarly, although the copolymer of Example 1b had a density of 0.870 g/cm³, the ATREF peak corresponded to what one would typically see for a substantially linear ethylene/1-octene copolymer prepared using Catalyst Three and having a density of 0.886 g/cm³, which is consistent with the finding above that the copolymer of Example 1b exhibited a DSC endotherm

which corresponded to what one would typically see for a substantially linear ethylene/1-octene copolymer prepared using Catalyst Three having a density of 0.884 g/cm³.

ATREF/DV may be further used to illustrate the fact that the copolymers of the invention are characterized as having a bimodal molecular weight distribution. For instance, as set forth in Figure 7c, the ATREF refractive index detector shows the unique short chain branching distribution of the copolymer of Example 45e produced by Catalyst Two. In addition, the ATREF differential viscometer detector (right hand vertical axis) shows that the copolymer comprises 92 weight percent of a lower density component which elutes at about 71°C and has a weight average molecular weight of 417000 daltons, and about 8 weight percent of a higher density component which elutes at about 85°C and has a weight average molecular weight of 174000 daltons. Thus the ATREF M_{w1}/M_{n2} ratio was 2.40, which was similar to the value determined by GPC deconvolution, shown in Table Six, i.e., 2.41.

The following Figure 7d is a plot of the ATREF shape factor versus the average ATREF elution temperature. This data in this plot was generated from ATREF curves. Specifically, (i) the maximum ATREF peak height was measured, (ii) the width of the total ATREF peak at ½ the maximum peak height was measured, the ATREF shape factor was calculated, that is, the ratio (ii)/(i), and the average ATREF elution temperature was determined, that is, (minimum ATREF elution temp + maximum ATREF elution temp)/2. In the case of the copolymers of the invention produced with Catalyst Two, the ATREF shape factor was described by the line ATREF shape factor = 0.64 - 0.00626 (average ATREF elution temperature), which indicates an ATREF shape factor of 0.165 at an average elution temperature of 75.94°C.

As the above DSC and ATREF information illustrates, the polymer compositions of the invention are characterized as having a fraction which has a higher crystallinity than the other fraction. The presence of the higher crystallinity fraction translates to an enhancement in the upper service temperature of the polymer compositions of the invention, with respect to the comparative compositions prepared with Catalyst Three. In particular, dynamic mechanical data for the copolymers of Examples 1a and 2a, and for Comparative Example C-3c are compared in Figure 8. Figure 8a compares the storage modulus (G') and $\tan \delta$ (G''/G') as a function of temperature. At high temperatures, the copolymers of Examples 1a and 2a, produced with Catalyst One and Two, respectively, were more elastic, relative to the copolymer of Comparative Example C-3c, produced with Catalyst Three. Higher elasticity is a desirable attribute in applications such as thermoforming. The upper service temperature may be defined as the intersection of a line drawn across the upper non-melted plateau region and the descending melting transition region of the log $G1$ versus temperature plot, as indicated by the intersecting lines on Figure 8b. The upper service temperature of the copolymer of Example 1a

was 75°C, which was 21°C higher than that of the Comparative Example C-3a which had an upper service temperature of 54°C. The upper service temperatures of the copolymer of Example 2a was 76°C, which was about 22°C higher than that of the copolymer of Comparative Example C-3c, which was especially surprising in view of the fact that the copolymer of Example 2a had a lower density than that of copolymer C-3c.

Moreover, it is important to note that the enhancement in upper service temperature exceeds that which is achieved by blending discreet substantially linear ethylene/1-octene copolymers having densities corresponding to each of the fractions of the copolymers of the invention. Figure 9a compares the upper service temperatures of the copolymers produced using Catalyst Two with copolymers produced using Catalyst Three, as a function of density. The curves in Figure 9a were simple polynomial fits through the data. The copolymers prepared with Catalyst Two which are used in Figure 9a include Example 2a, and examples prepared using a batch polymerization process set forth above utilizing Catalyst Two and the following reactor conditions:

Example	Catalyst ¹ (μmoles)	Octene (g)	Ethylene (g)	H ₂ (mmole)	Temp (°C)	Efficiency	Melt Index I ₂ (dg/min)	Melt Flow Ratio I ₁₀ /I ₂	ASTM Density (g/cc)
45a	15	37.5	117	20	170	0.042	0.31	6.56	0.9131
45j	7.5	253.7	132.7	5	155	0.168	1.36	6.94	0.8655
45n	7.5	140.5	125	20	155	0.181	0.36	22.87	0.8823

¹ (2,3,4,6-tetramethyl-indenyl)dimethyl(cyclohexylamido)silane titanium dimethyl

For copolymers having a density of 0.87 g/cm³, the upper service temperature of copolymers produced using Catalyst Two was 33°C higher than that of comparative polymers prepared using Catalyst Three.

Figure 9b compares the increase in upper service temperature (UST) which can be achieved via blending copolymers prepared with Catalyst Three with the increase in UST achievable with the copolymers of the invention prepared with Catalyst Two. Studies show that approximately 20 wt% of the higher density component produced the maximum increase in UST in the case of blends. More specifically, when the blend comprised below 20 wt% of the higher density component, the UST decreased due to the decreasing concentration of the higher melting material, while when the blend comprised more than 20 wt% of the higher melting material, the UST decreased because it was necessary to decrease the density of the higher melting material (to keep the overall density of the blend constant at 0.875 g/cm³). In sharp contrast with the behavior of blends, the copolymers of the invention exhibited unique behavior.

For example, relative to a blend containing about 10 wt% of a higher density copolymer (which corresponds to the relative proportion of the high density component in the copolymer produced by Catalyst Two, as illustrated in Figure 9a, the copolymer produced using Catalyst Two exhibited a 24°C higher upper service temperature than the copolymer of the comparative
5 blend.

The molecular weight (M_w and M_n) and the polydispersity (M_w/M_n) for the copolymers of Examples 1a - 1c, and 2a - 2d, as well as for Comparative Examples C-3a and C-2a were determined, and are set forth in the following Table Five:

Table Five: Gel permeation chromatography (GPC) data

Example	Catalyst	GPC			Fit		
		M _w	M _n	M _w /M _n	M _w	M _n	M _w /M _n
C-3a	Three	146500	68700	2.132	142748	60643	2.354
1a	One	122400	43100	2.840	121075	43348	2.793
1b	One	132500	52900	2.505	127299	47828	2.662
1c	One	125300	51100	2.452	119533	44934	2.660
2a	Two	143400	65400	2.193	139869	56994	2.454
2b	Two	136300	54100	2.519	136096	53206	2.558
2c	Two	142900	64300	2.222	138895	55961	2.482
2d	Two	146200	62400	2.343	143378	57570	2.491
C-3b	Three	37300	17000	2.194	36878	15846	2.327
C-2a *	Two	159700	77000	2.074	155539	67900	2.291

5 * Comparative Example C-2a was produced in a batch reactor.

As illustrated in Table Five, the copolymers of the Comparative Examples C-3a and C-3b had GPC polydispersities (M_w/M_n's) of 2.16, while copolymers produced with Catalysts One and Two had polydispersities of 2.60 (Catalyst One) and 2.32 (Catalyst Two).

10 The raw GPC chromatograms were also fit to the Bamford-Tompa distribution from which one can calculate an overall M_n, M_w and M_w/M_n. This fitting procedure assumed a unimodal molecular weight distribution where the level of long chain branching was varied to fit raw GPC chromatograms.

The Bamford-Tompa molecular weight distribution is calculated via Eq.[2],

$$15 \quad w_i(M_i) = \ln(10) \frac{M_i}{M_n} \exp\left(-\frac{M_i(1+\zeta)}{M_n}\right) \times \left(\frac{2+\zeta}{\zeta}\right)^{1/2} \times I_1\left(\frac{M_i \zeta^{1/2} (2+\zeta)^{1/2}}{M_n}\right) \quad [2]$$

where I₁(x) is the modified Bessel function of the first kind of order one, defined by

$$I_1(x) = \sum_b \frac{x^{2b+1}}{2^{2b+1} b!(b+1)!} \quad [3]$$

and ζ is an adjustable parameter which broadens the molecular weight distribution, as shown in Eq.[4].

$$\frac{M_w}{M_n} = 2 + \zeta \quad [4]$$

As defined by Bamford and Tompa, ζ is related to the level of long chain branching via,

$$LCB / 10000C = \frac{10000M\zeta}{M_n} \quad [5]$$

where M is the average molecular weight of the repeating unit. The b individual terms of the expanded Bessel function represent the molecular weight distributions of the polymer chains carrying b long chain branches per molecule. Bamford and Tompa also provide equations to calculate the average number of branch points in a molecule as a function of chain length. See, for instance, C.H. Bamford and H. Tompa "The Calculation of Molecular Weight Distributions from Kinetic Schemes" Trans. Faraday Soc., 50, 1097(1954).

10 The "fit" M_w/M_n 's provided a more consistent polydispersity estimate. The "fit" polydispersities for the copolymers of Comparative Examples C-3a and C-3b, Examples 1a - 1C, and Examples 2a - 2d, were 2.34, 2.50 and 2.71, respectively.

15 In the case of the copolymers of Examples 2a - 2d, which were produced in a continuous solution polymerization process and Comparative Example C-2a, which was produced in a batch solution polymerization process, the former have an increased polydispersity over the latter. In particular, Comparative Example C-2a exhibited a polydispersity of 2.07, while Examples 2a - 2d exhibited a mean polydispersity of 2.32 ± 0.15 ; similarly, "fit" polydispersities of 2.29 and 2.50 ± 0.04 , respectively, were observed for copolymers of Comparative Example C-2a and Examples 2a - 2d, respectively.

20 The increased polydispersity, as one moves from the batch to the continuous process, correlates with the increase in melt flow ratio. For example, the average I_{10}/I_2 of the copolymers of Examples 2a - 2d was 13.3, while the copolymer of Comparative Example C-2a exhibited an I_{10}/I_2 of 6.5. Both of these observations, that is, the higher M_w/M_n and I_{10}/I_2 , suggest that the continuous process copolymers contained a higher concentration of long chain branches than
25 the corresponding batch polymerized polymers. It is well known that long chain branching dramatically increases the shear thinning behavior of a copolymer.

Deconvolution of Bimodal Molecular Weight Distributions

The molecular weight distributions of copolymers produced by Catalyst One and Two were assumed bimodal. In addition it was assumed the M_w/M_n of each component could be

described by Eq.[2]. Thus, the GPC deconvolution procedure involved a five parameter fit, that is, M_{n1} , z_1 , M_{n2} , z_2 and split (S); where the subscripts 1 and 2 refer to the primary and secondary copolymer components, respectively, and split was defined as the weight fraction of the higher molecular weight copolymer. The non-linear curve-fitting subroutine within SigmaPlot+ (v2.01) was used to estimate the parameters. This subroutine used the Marquardt-Levenberg algorithm to determine parameter values that minimized the sum of squares of differences between the distribution defined by the dependent variable values and the observed GPC data. The non-linear curve fitting algorithm required initial parameter values, which were determined following a visual inspection of the experimental GPC chromatogram. Converged parameter estimates were remarkably insensitive to the initial parameter values.

Assuming that the copolymers produced by the Catalysts One and Two were bimodal in molecular weight distribution, Table Six summarizes GPC deconvolution results. In this procedure, as described above, the molecular weight distributions of the two components were assumed to follow a Bamford-Tompa distribution. Thus, GPC deconvolution involved a five parameter fit; M_{n1} , ζ_1 , M_{n2} , ζ_2 and the weight fraction of the higher molecular weight copolymer (M_{n1}). The GPC deconvolution data are set forth in the following Table Six:

Table Six: GPC deconvolution results for the ethylene/octene copolymers produced using Catalysts One and Two

5

Example	Catalyst	High Mw Low Density Component				Low Mw High Density Component			Mn Ratio Mn1/Mn2
		Mw1	Mn1	Mw/Mn	wt %	Mw2	Mn2	Mw/Mn	
1a	One	165383	72285	2.2879	62.6	56827	28272	2.0100	2.56
1b	One	176274	78776	2.2377	60.0	64304	32152	2.0000	2.45
1c	One	166456	72573	2.2936	60.3	61713	30855	2.0001	2.35
Average TMInd-N-Pr →		169371	74545	2.2731	61.0	60948	30426	2.0034	2.45
2a	Two	155074	65311	2.3744	84.1	79312	39654	2.0001	1.65
2b	Two	155959	65455	2.3827	81.5	62924	31459	2.0002	2.08
2c	Two	155235	65205	2.3807	83.0	76699	38348	2.0001	1.70
2d	Two	168193	73727	2.2813	77.1	67357	33678	2.0000	2.19
Average TMInd-N-CHEX →		158615	67425	2.3548	81.4	71573	35785	2.0001	1.88
5r ¹	Two	296460	68670	2.3172	95.5	95134	47558	2.0004	1.44
10a ^{1,2}	TMCP-N-CHEX	77124	36015	2.1414	85.5	48108	24054	2.0000	1.50
10c ^{1,2}	2-Me-5,6,5-Ind-N-CHEX	164432	71648	2.2950	84.2	60634	30316	2.0001	2.36
10e ^{1,2}	3-Pyrol-Ind-N-CHEX	258038	114543	2.2528	89.1	142678	71339	2.0000	1.61
10j ^{1,2}	One	220854	98430	2.2438	68.5	105325	52662	2.0000	1.87
45e ^{1,3}	Two	321517	143333	2.2432	89.7	118855	59424	2.0001	2.41
45f ^{1,3}	Two	133488	58611	2.2775	86.6	64027	32009	2.0003	1.83
45h ^{1,3}	Two	121666	53434	2.2769	89.6	57857	28926	2.0002	1.85
45i ^{1,3}	Two	72715	32997	2.2037	89.9	39552	19776	2.0000	1.67

¹ Batch reactor

As shown in Table Six, 61 percent of the copolymer produced by Catalyst One was of 169,000 daltons, with the remainder 61000 daltons. Similarly, approximately 81.4 percent of the copolymer produced by Catalyst Two was of 159,000 daltons, with the balance 72000 daltons.

5 Figures 10 and 11 illustrate these deconvolution results in a graphical format. GPC deconvolution results for batch reactor samples were also summarized in Table Six.

The copolymers of this invention were analyzed for indicia of long chain branching. In particular, rheological data were generated using a Rheometrics RMS-800 dynamic mechanical spectrometer with 25 mm diameter parallel plates in the oscillatory shear mode. Frequency
10 sweeps were performed over the shear rate range of 0.1-100 rad/s at 15 percent strain in a nitrogen atmosphere. Rheological data are set forth in the following Table Seven.

Table Seven: Viscosity data for Copolymers of the Invention and for Comparative Examples

Example	Catalyst	Melt Index (dg/min)	Melt Flow Ratio I_{10}/I_2	h, viscosity (poise)			tan δ at 0.1 Hz
				$h_{0.1\text{Hz}}$	$h_{100\text{Hz}}$	$h_{0.1\text{Hz}}/h_{100\text{Hz}}$	
C-3a	Three	0.48	9.38	186030	20889	8.91	4.83
1a	One	0.71	11.58	216860	15510	13.98	2.72
1b	One	0.63	12.29	195830	14486	13.52	2.83
1c	One	0.82	10.91	164620	14097	11.68	3.24
2a	Two	0.5	15.22	293030	17363	16.88	2.37
2b	Two	0.43	13.58	344890	18370	18.77	2.13
2c	Two	0.38	14.39	346910	18053	19.22	2.10
2d	Two	0.38	10.11	400840	18965	21.14	1.91
C-3b	Three	116	6.00	854	696	1.23	102.8 ¹
C-2a *	Two	0.49	6.53	171940	22021	7.81	6.06

5 ¹ at 0.631 Hz (rather than 0.1 Hz)

² could not measure

* Copolymer C-2a was produced in a batch reactor.

Figure 13 provides a plot of the log viscosity versus log frequency for the copolymers of in the invention and of the comparative examples as determined by RMS 800 rheometer in accordance with the procedure set forth above. As illustrated in Figure 13, the copolymer of Examples 2a exhibited enhanced shear thinning behavior over the copolymer of Comparative Example C-2a, both of which were produced with Catalyst Two. In addition, Figure 13 illustrates that the copolymer of Example 2a, prepared by a continuous process, was more elastic than the copolymer of Comparative Example C-2a, which was produced in a batch reactor, as indicated by the lower tan δ value of the former. These behaviors are indicative of the higher level of long chain branching characteristic of copolymers produced in a continuous solution polymerization process.

20 The melt fracture behavior of selected resins were also evaluated on the gas extrusion rheometer (GER). The shear stress (MPa) and shear rate (s⁻¹) values where each resin lost surface gloss (LSG) and at the onset of gross melt fracture (OGMF) are set forth in the following Table Eight:

Table Eight: Gas extrusion rheometer (GER) data for Copolymers of the Examples and of the Comparative Examples

Example	Catalyst	Density (g/cc)	Melt Index (dg/min)	Melt Flow Ratio I_{10}/I_2	LSG ¹		OGMF ²	
					Shear Stress (MPa)	Shear Rate (s ⁻¹)	Shear Stress (MPa)	Shear Rate (s ⁻¹)
2a	Two	0.8606	0.50	15.22	0.151	56	0.302	432
C-3c ³	Three	0.8680	0.51	8.01	<0.086	<24	0.237	280
1c	One	0.8703	0.82	10.91	<0.086	<35	0.259	479
C-2a	Two Batch Reactor	0.8635	0.49	6.53	0.129	19	0.237	89

¹ LSG = loss of surface gloss

5 ² OGMF = onset of gross melt fracture

³ Substantially linear ethylene/1-octene interpolmer prepared with Catalyst Three in a continuous solution polymerization process

* Comparative Example C-2a was produced in a batch reactor

10 As demonstrated by the shear rate at the onset of gross melt fracture (OGMF), the copolymers produced with Catalyst One and Two were more resistant to melt fracture than the copolymer of Comparative Example C-2a, which was produced using Catalyst Three in a continuous reactor. Since shear rate is directly proportional to output (that is., lb/hr or parts/hr), the copolymer of Example 2a, prepared with Catalyst Two, can be processed at higher rates
15 relative to copolymer C-3c, prepared with Catalyst Three.

The advantage in using a continuous solution polymerization process over a batch solution polymerization process is illustrated in a comparison of the copolymer of Example 2a, prepared in a continuous solution polymerization reaction, with that of Comparative Example C-2a, prepared in a batch solution polymerization reaction. Although the copolymers had a similar
20 melt index, the copolymer of Comparative Example C-2a exhibited a lower OGMF shear rate (89 s⁻¹) than the copolymer of Example 2a (432 s⁻¹).

Infrared analysis (FTIR) was performed on representative copolymers of the Examples and of the Comparative Examples, the results of which is set forth in the following Table Nine:

Table Nine: Fourier transform infrared (FTIR) data for Copolymers of the Examples and of the Comparative Examples

Example	Catalyst	Density (g/cc)	Melt Index (dg/min)	Melt Flow Ratio I_{10}/I_2	FTIR Data			
					Vinyls	Trans + Vinylidene	Vinyl Ratio ¹	Trans + Vinylidene Ratio
C-3a	Three	0.8667	0.48	9.38	0.025	0.220	1.000	1.000
1a	One	0.8710	0.71	11.58	0.042	0.293	1.680	1.332
1b	One	0.8700	0.63	12.29	0.046	0.298	1.840	1.355
1c	One	0.8703	0.82	10.91	0.080	0.320	3.200	1.455
2a	Two	0.8606	0.50	15.22	0.052	0.602	2.080	2.736
2b	Two	0.8612	0.43	13.58	0.037	0.580	1.480	2.636
2c	Two	0.8612	0.38	14.39	0.051	0.556	2.040	2.527
2d	Two	0.8615	0.38	10.11	0.043	0.566	1.720	2.573
C-3b	Three	0.8712	116	6.00	0.130	0.311	5.200	1.414

¹ normalized vinyl concentration (relative to the vinyl concentration of sample 4a)

5

The data set forth in Table Nine illustrates that the copolymers of Examples 1a - 1c and 2a - 2d exhibited higher vinyl concentrations than the copolymer of Comparative Examples C-3a. Given the higher level of vinyl termination characteristic of the copolymers of the invention, it is believed that they exhibit higher levels of long chain branching, due to the re-incorporation of vinyl-terminated macromolecules into propagating polymer chains. While not wishing to be bound by theory, it is believed that the higher levels of vinyl termination characteristic of the polymers of the invention are due to the higher reaction temperatures made possible by use of catalysts such as Catalysts One and Two described herein. For instance, a comparison of Comparative Examples C-3b and C-3a indicates that as the reaction temperature increases, the amount of vinyl termination likewise increases. It is noted that the copolymers of the Examples were produced at reaction temperatures of about 120°C, as compared to 80°C for the copolymer of Comparative Example C-3a.

Copolymers of the Examples and Comparative Examples were further tested for compression set in accordance with the following procedure. Compression set buttons were prepared for each sample by cutting 2.86 cm diameter (1.125-in.) disks from 1.52 mm thick compression molded plaques. Disks were stacked (total stack height approximately 1.37 cm (0.54-in.)) in a compression set mold (at room temperature) and the disks were fused at 176.7°C (350°F) and 10,000 psi (69 MPa) over 10 minutes. The buttons were removed from the mold, equilibrated at ASTM conditions for 24 hours, and the thickness of each button was measured with a micrometer. The 1.27 cm thick (0.5-in.) buttons were placed in a compression set clamp and compressed to 0.953 cm (0.375-in.) by tightening the nuts until the top platten made contact with the 0.953 cm spacers. The cold compression set clamp was placed in an

oven at 70°C (158°F) for 24 hours. The buttons were removed from the compression set clamp and equilibrated at ASTM conditions for 24 hours prior to the measurement of button thickness. Compression set was expressed as the percentage of the deformation which was not recovered. Additional information on the compression set test can be found in ASTM D-395-89 method B.

The compression set of copolymers of the invention produced with Catalyst One and Catalyst Two, and a comparative copolymer produced with Catalyst Three are summarized in Figure 14. Relative to the copolymer C-3c produced with Catalyst Three, the compression set at 70°C was lower for copolymers produced by Catalyst One and Catalyst Two, in spite of the similar crystallinity of the copolymers. Lower compression sets are desirable, in that, compression set represents the percentage of the deformation which was not recovered. Ideally, the compression set of perfect elastomers would be 0 percent, that is, the deformation would be completely recovered. The lower compression set of the copolymers of the invention produced via Catalyst One and Catalyst Two was attributed to the bimodal short chain branching distribution.

Polymerization of Ethylene/Propylene Interpolymers and Ethylene/Propylene/Diene Interpolymers

Ethylene/propylene interpolymers are prepared in accordance with the following procedure utilizing the reactor conditions set forth in the following Table.

Terpolymerization of ethylene, propylene, and ethylidene norbornene was carried out using a 3.8 L stainless steel reactor charged with 1450/g Isopar E* (mixed alkanes, available from Exxon Chemicals, Inc.), 207.3 g of propylene, 17.6 g of ethylidene norbornene, and 13.8 mMol of hydrogen. The reactor was heated to 100°C and then saturated with ethylene to 460 psig (3.2 MPa). The catalyst was prepared in a dry box by syringing together 5.0 micromol (0.005 M solution) of the metal complex (isopropylamido)dimethyl(η⁵-2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl, 5 micromol (0.0075 M solution) of the cocatalyst di(hydrogenated-tallowalkyl)methylammonium tetrakis(pentafluorophenyl)borate, 50.0 micromol (0.050 M solution) of the scavenger (diisopropylamido)diethylaluminum, and additional Isopar E* to give a total volume of 18 mL. The catalyst solution was then transferred via syringe to a catalyst addition loop and injected into the reactor over approximately 4 minutes using a flow of high pressure solvent. The polymerization was allowed to proceed for 10 minutes while feeding ethylene on demand to maintain a pressure of 460 psig (3.2 MPa). The amount of ethylene consumed during the reaction was monitored using a mass flow meter. The polymer solution was then poured from the reactor into a nitrogen-purged glass kettle and stabilizer (Irganox™

1076) were added and mixed well with the solution. The polymer solution was poured into a tray, air dried overnight, then thoroughly dried in a vacuum oven for one day. The yield of polymer was 37.0 g, and the catalyst efficiency calculated as grams of polymer per gram of transition metal was 0.15 million. The obtained terpolymer had a composition of 54.7 wt percent ethylene, 42.7 wt percent propylene, 2.6 wt percent ethylidene norbornene. The molecular weight was 147,200 with a molecular weight distribution of 2.18. The elastomer had a measured glass transition temperature of -53.9°C and was 0.9 percent crystalline.

Using the apparatus and procedure above, with the exception of omitting the addition of ethylidene norbornene, sixteen ethylene/ propylene copolymers are prepared using the ingredient amounts shown in Table below. The polymer physical properties are shown in the subsequent table. The catalyst of Examples 1a - 1e is (cyclohexylamido)dimethyl(η 5-2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl. The catalyst of Examples 2a - 2f is (isopropylamido)dimethyl(η 5-2,3,4,6-tetramethylindenyl)silanetitanium (IV) dimethyl. The catalyst of the comparative examples is (tetramethylcyclopentadienyl)dimethyl(t-butylamido)silanetitanium 1,3-pentadiene. The cocatalyst of all Examples is di(hydrogenated-tallowalkyl)methylammonium tetrakis(pentafluorophenyl)borate. The scavenger of all Examples is a derivative of diisobutyl aluminum.

Example No.	Ti (μmole)	Co-cat (μmole)	Al / Ti Ratio	Temp (°C)	Exotherm, (°C)	C ₃ grams loaded	Isopar™ E mass	H ₂ delta pressure	H ₂ (mmol)	C ₁ load, (grams)	C ₁ partial pressure	Length of Run (Min)	C ₁ Consumed, g	Total Pressure, psig (MPa)	Dry Weight, g	Efficiency MM g polymer/g Ti
Comp. EP 3a	1.5	2.25	10	100	1.6	357	1462.9	30	2.7	128.3	250.9	10	100.3	467.2 (3.221)	227	3.16
EP 2a	1.25	1.88	10	70	0.6	355	1482	40.2	3.6	222.5	320.2	13.6	30	463.2 (3.194)	43	0.72
EP 2b	1.25	1.88	10	80	0.6	331	1475.9	40.4	3.7	186	302.5	12.1	45.1	461.9 (3.185)	75	1.25
EP 2c	1.5	2.25	10	90	1.1	376	1446.4	30	2.7	152	265.5	5.2	45.5	464.8 (3.205)	113	1.57
EP 2d	1.25	1.88	10	90	2	306	1441.2	40.7	3.7	159.8	293	5.1	45.3	464.7 (3.204)	88	1.47
EP 2e	1.5	2.25	10	100	2	280	1441	40.7	3.7	141.6	286.2	3.9	45.5	463.5 (3.196)	94	1.31
EP 2f	1.5	1.5	25	100	0.6	135.3	1461	292	27.6	153.6	351.5	10	37	458 (3.158)	59	1.2
Comp. EP 3b	1	1.5	10	100	7	303	1441.6	30.8	2.82	133.8	271.6	10	90.4	463.3 (3.194)	266	5.55
Comp. EP 3c	1.25	1.88	10	100	1.2	356	1449.5	41.2	3.8	125.5	253.9	6.8	55.2	463.5 (3.196)	102.2	1.71

Example No.	Ti (μ mole)	Co-cat (μ mole)	Al/Ti Ratio	Temp ($^{\circ}$ C)	Exotherm, ($^{\circ}$ C)	C ₃ grams loaded	Isopar™ E mass	H ₂ delta pressure	H ₂ (mmol)	C ₃ grams loaded	C ₃ partial pressure	Length of Run (Min)	C ₂ Consumed, g	Total Pressure, psig (MPa)	Dry Weight, g	Efficiency MM g polymer/g Ti
Comp. EP 3d	1.25	1.88	10	90	1.6	376	1451.5	40.4	3.68	147.53	269.3	5.3	50.4	462.6 (3.190)	123	2.05
Comp. EP 3e	1.5	2.25	10	80	1.6	389	1451.1	40.4	3.7	174.5	275.3	4.5	42.3	462.7 (3.190)	112	1.56
Comp. EP 3f	1.5	2.25	10	70	3.4	407	1443	45.3	4.1	215.1	305.9	3.6	32.3	464.7 (3.204)	131.5	1.83
Comp. EP 3g	1	1.5	10	100	0.9	305	1454.2	30.3	2.8	130	273.9	10	79.2	465.1 (3.207)	147.4	3.08
EP 1a	1	1.5	10	100	1.3	306	1457.8	40.7	3.76	133	274.2	7.8	55.2	464.1 (3.200)	104	2.17
EP 1b	1	1.5	10	90	1.5	325.1	1455.2	40.2	3.7	155.44	287	8.1	55.2	464.3 (3.201)	99	2.07
EP 1c	1.5	2.25	10	80	2.8	340.6	1430.9	40.7	3.74	184.8	299.3	2.4	43	463.6 (3.196)	99.8	1.39
EP 1d	1.5	2.25	10	70	2.5	356.6	1436.3	50.9	4.7	221.8	322.5	3.5	29.9	464.1 (3.200)	92.7	1.29
EP 1e	2.5	2.5	25	100	0.5	137	1450.4	291	27.5	152.8	350.5	10	24.8	458.3 (3.160)	39.2	

Example No.	Temp. (°C)	Wt. Percent C ₁ H ₄	Wt. Percent C ₃ H ₆	M _w GPC-dv	M _n GPC- dv	M _w /M _n	Mooney ML 1+4 at 125C	DSC T _c °C	DSC Cool Peak °C	DSC Tg °C	DSC Heat of Fusion (J/g)	DSC Melt Peak°C	DSC % Cryst (HF/292) +100
Comp. EP 3a	100	45.8	54.2	141,800	80,100	1.77	39.3	-11.9	-22.6	-48.7	5.0	-21.3	1.7
EP 2a	70	45.4	54.6	313,300	135,500	2.31	144.6	-	-	-52.8	0.0	-	0.0
EP 2b	80	45.2	54.8	286,600	131,200	2.18	137.3	-	-	-53.2	0.0	-	0.0
EP 2c	90	40.9	59.1	258,400	130,400	1.98	115.3	-	-	-52.7	0.0	-	0.0
EP 2d	90	44.2	55.8	263,800	136,300	1.94	125.7	-	-	-55.4	0.0	-	0.0
EP 2e	100	44.6	55.4	231,300	120,200	1.92	107.4	-	-	-54.0	0.0	0.0	0.0
EP 2f	100	67.4	32.6	142,700	74,700	1.91		51.28		-49.17	13.88	2.38	4.75
								14.24					
Comp. EP 3b	100	50.8	49.2	140,700	64,000	2.20	30.2	-2.4	-11.2	-53.1	10.8	-16.2	3.7
Comp. EP 3c	100	44.1	55.9	123,700	64,100	1.93	25.9	-16.9	-23.4	-52.1	3.0	-24.0	1.0
Comp. EP 3d	90	44.3	55.6	154,000	81,500	1.89	43.3	-18.7	-27.2	-52.9	3.5	-26.3	1.2
Comp. EP 3e	80	41.9	58.2	198,900	97,300	2.04	78.3	-	-	-53.5	0.8	-25.6	0.3
Comp. EP 3f	70	44.0	56.1	214,300	113,200	1.89	90.6	-	-	-51.5	2.7	-24.5	0.9
Comp. EP 3g	100	51.6	48.4	146,400	76,700	1.91	44.8	-2.5	-11.72	-54.15	14.52	-17.03	5.0
EP 1a	100	45.5	54.5	221,800	108,500	2.04	87.2	3.4	-16.22	-55.88	1.713	-18.65	0.6
EP 1b	90	44.7	55.3	253,000	116,600	2.17	116.5	5.01	-16.59	-55.49	0.9782	-19.07	0.3
EP 1c	80	43.5	56.5	297,000	151,500	1.96	137.3	12.16	-19.49	-56.49	0	0	0.0
EP 1d	70	45.2	54.8	333,400	178,600	1.87	137.6	10.28	-16.36	-56.41	0	0	0.0
Ep 1e	100	67.5	32.5	149,200	78,500	1.90		83.56		-49.1	8.44	2.1	2.89
								55.37			3.13	62.9	1.07
								8.19					

Polymerization of Ethylene/Propylene/Diene Interpolymer

An ethylene/propylene/diene interpolymer is prepared using the general polymerization procedure set forth above using the reactor conditions set forth below.

Al/Ti ratio: 10

5 Temp: 101.6°C

C₃ grams loaded: 207.3

H₂ delta pressure: 150.6

Isopar™ mass, grams: 1455.9

Octene mass, grams: 0

10 Diene mass, grams: 17.6

C₂ load, grams: 141.54

Total pressure (psi (MPa)): 460.4 (3.174)

C₂ partial pressure (psi (MPa)): 309.4 (2.133)

Ethylene rate max: 8.8

15 Ethylene consumed: 27.5

Length of run: 10

Ti umole: 5

Dry weight: 37

Efficiency: 0.15

20 The resultant polymer had 54.7 weight percent ethylene, 42.7 weight percent propylene, 2.6 weight percent ENB. GPC-dv results indicate that the polymer had an Mw of 147200, an Mn of 67500, an M_w/M_n of 2.18. Differential scanning calorimetry indicated a Tc of 14.09°C, a DSC cooling peak at -22.8°C, a DSC heat of fusion of 2.685 J/g, a DSC melting peak at -30.58°C, and a percent crystallinity of 0.9 percent.

With respect to the ethylene/propylene and the ethylene/propylene/diene copolymer examples, the examples show that semi-crystalline EP and EPDM interpolymers with ethylene content greater than 45 weight percent (EP 2f and EP 1e) display the DSC characteristics observed for other copolymers. Further, amorphous materials with less than 45 weight percent ethylene prepared with the catalysts of this invention have lower Tg and higher molecular weight than polymers prepared under the same conditions with (tetramethylcyclopentadienyl)dimethyl(t-butylamido)silane titanium 1,3-pentadiene.

The following sets forth procedures for preparing additional catalysts useful in the preparation of the polymers of the invention, as well as details of polymerizations made employing such catalysts.

Example A Preparation of (2,3-dimethylindenyl)dimethyl(cyclo-dodecylamido)silane titanium dichloride

Preparation of $\text{Li}_2[(2,3\text{-dimethylindenyl})(\text{cyclododecylamido})\text{dimethyl-silane}] \cdot 0.75 \text{ Et}_2\text{O}$

(2,3-dimethylindenyl)(cyclododecylamido)dimethylsilane (5.47 g, 0.0142 moles) was stirred in diethylether (25 mL) as n-BuLi (0.030 moles, 11.94 mL of 2.5 M solution in hexane) was added slowly. This mixture was then allowed to stir for 16 hours. After the reaction period the volatiles were removed and the residue washed with hexane and then collected as a solid via filtration which was used without further purification or analysis (5.47 g, 85.2 percent).

Preparation of (2,3-dimethylindenyl)dimethyl(cyclododecylamido)-silane titanium dichloride

$\text{Li}_2[(2,3\text{-dimethylindenyl})(\text{cyclododecylamido})\text{dimethyl-silane}] \cdot 3/4 \text{ Et}_2\text{O}$ (5.47 g, 0.0121 moles) was slowly added as a solid to a slurry of $\text{TiCl}_3(\text{THF})_3$ (4.48 g, 0.0121 moles) in THF (75 mL). This mixture was allowed to stir for 45 minutes. PbCl_2 (1.68 g, 0.00604 moles) was then added to the mixture which was then allowed to stir for an additional 45 minutes. After the reaction period the volatiles were removed and the residue extracted and filtered using toluene. The toluene was then removed and the residue slurried in hexane and then collected as a red-brown crystalline solid by filtration. A second crop was obtained by concentrating and cooling the filtrate followed by a second filtration. The crops were then combined and determined to be the desired product (0.457 g, 7.6 percent).

$^1\text{H NMR}$ (300 MHz, C_6D_6): δ 0.52 (s, 3 H), 0.63 (s, 3 H), 1.15-1.91 (m, 23 H), 2.11 (s, 3 H), 2.23 (s, 3 H), 5.31 (m, 1 H), 6.83-7.12 (m, 2 H), 7.29 (d, 1 H), 7.63 (d, 3 H).

Example B Preparation of (2,3-dimethylindenyl)dimethyl(cyclo-dodecylamido)silane titanium dimethyl

(2,3-dimethylindenyl)dimethyl(cyclododecylamido)silane TiCl_2 (0.200 g, 0.000400 moles) was stirred in diethylether (50 mL) as methylMgI (0.00084 moles, 0.28 mL 3.0 M solution in diethylether) was added dropwise. This mixture was then allowed to stir for 30 minutes. After the reaction period the volatiles were removed and the residue extracted and filtered using
 5 hexane. Removal of the volatiles followed by a repeat of the filtration again using hexane resulted in the isolation of the desired product as an orange crystalline solid after the removal of the hexane (0.134 g, 73.2 percent).

^1H NMR (300 MHz, C_6D_6): δ -0.11 (s, 3 H), 0.53 (s, 3 H), 0.61 (s, 3 H), 0.65 (s, 3 H), 1.10-1.90 (m, 23 H), 1.98 (s, 3 H), 2.26 (s, 3 H), 5.12-5.25 (m, 1 H), 6.91 (t, 1 H), 7.09 (t, 1 H),
 10 7.45 (d, 1 H), 7.58 (d, 1 H).

Example C. Preparation of [(N-cyclohexylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium Dimethyl

Preparation of dimethylsilyl(2,3,4,6-tetramethylindenyl)(cyclohexylamine)

Dimethylsilyl(2,3,4,6-tetramethylindenyl)Cl (9.95g, 37.8 mmol) was stirred in hexane
 15 (200 mL) as NEt_3 (4.1 g, 40.6 mmol) was added followed by cyclohexylamine (4.05g, 40.8 mmol). This mixture was allowed to stir for 24 hours at 20 °C. After the reaction period the mixture was filtered and the desired product isolated as a pale yellow oil following the removal of the volatiles (10.98 g, 89.3 percent yield).

Preparation of Dilithium (N-cyclohexylamido)(dimethyl) (2,3,4,6-tetramethylindenyl)silane

20 In the drybox 4.0 g (12.6 mmol) of (N-cyclohexylamino)(dimethyl) (2,3,4,6-tetramethylindenyl) silane was dissolved in 300 ml of hexane. To this solution 12.6 ml (25.2 mmol) of nBuLi (2.00 M) was added dropwise at 20 °C. Upon complete addition of the nBuLi the solution was stirred for 12 hours after which the solvent was removed under reduced pressure to give 4.12 g (96 percent yield) of a yellow-orange powder.

25 Preparation of [(N-cyclohexylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] Titanium Dichloride

In the drybox 4.63 g (12.5 mmol) of $\text{TiCl}_3(\text{THF})_3$ was dissolved in 75 ml of THF. To this solution 4.12 g (12.5 mmol) of dilithium (N-cyclohexylamido) (dimethyl)(2,3,4,6-tetramethylindenyl)silane was added as a solid while stirring at 20 °C. The solution was then
 30 stirred for 45 minutes. After this time period 1.73 g of PbCl_2 (6.25 mmol) was added and the solution stirred for 45 minutes. The THF was then removed under reduced pressure. The residue was then extracted with toluene, the solution filtered, and the toluene removed under

reduced pressure. The residue was then triturated with hexane and the solution volume reduced whereupon a red precipitate was formed and collected via filtration and washed with cold (0 °C) hexane. The solid product was dried under vacuum to yield 1.70g (31 percent yield) of product.

5 Example D Preparation of [(N-cyclohexylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium Dimethyl

In the drybox 0.300 g of [(N-t-cyclohexylamino)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium dichloride (0.675 mmol) was suspended in 50 ml of Et₂O at 20 °C. To this suspension 0.45 ml of MeMgI (3.0 M) was added dropwise while stirring over a 20 minute
10 period. After the addition MeMgI was completed, the solution was stirred for 40 minutes. Then the Et₂O was removed under reduced pressure and the residue extracted with hexane, the solution filtered, the filtrate evaporated to dryness under reduced pressure to give 0.27 g (100 percent yield) of product.

15 Example E Preparation of [(N-cyclohexylamido)(dimethyl)(2,3-methylindenyl)silane]-titanium(II)(1,4-diphenyl-1,3-butadiene)

In a 100ml flask 0.300g of (N-cyclohexylamido)(dimethyl)(2,3-methylindenyl)silane]titanium dichloride (.720 mmol, from Example 23) was stirred with 0.149g of 1,4-diphenyl-1,3-butadiene (0.720 mmol) in 70ml of hexane at 0° C. To this solution 0.577ml of 2.5M nBuLi (in hexane) was added and the mixture refluxed for 2h. After cooling the solution
20 to 20° C, the solution was filtered. The filter residue was then washed with hexane. The hexane was then removed from the filtrate under reduced pressure to give 0.109g (27 percent yield) of product.

Polymerization Runs

A two-liter Parr reactor was charged with 740 g of mixed alkanes solvent (Isopar™-E) and 118 g of 1-octene comonomer. Hydrogen was added as a molecular weight control agent
25 by differential pressure expansion from an ~75 ml addition tank at 25 psi (2070 Kpa). The reactor was heated to the polymerization temperature of 140°C and saturated with ethylene at 500 psig (3.4 Mpa). 2.0 mmol each of catalyst and cocatalyst at 0.005M solutions in toluene were premixed in the drybox. After the desired premix time, the solution was transferred to a
30 catalyst addition tank and injected into the reactor. The polymerization conditions were maintained for 15 minutes with ethylene on demand. The resulting solution was removed from the reactor, and a hindered phenol anti-oxidant (Irganox™ 1010 from Ciba Geigy Corp.) was

added to the resulting solution. Polymers formed were dried in a vacuum oven set at 120°C for about 20 hours.

Example F: Preparation of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]

5 Titanium Dimethyl

Preparation of Dimethylsilyl(2,3,4,6-tetramethylindenyl)(isopropylamine)

Dimethylsilyl(2,3,4,6-tetramethylindenyl)Cl (22.29 grams, 84.17 mmol) was stirred in THF as i-PrNH₂ (28.68 mL, 336.7 mmol) was added. The mixture was stirred for 16 hours. The volatiles were removed under reduced pressure. The residue was extracted with hexane and
10 filtered through a diatomaceous earth filter aid on a 10 to 15 mm glass frit. The hexane was removed under reduced pressure to afford the product as a yellow oil. Yield; 17.23 grams, 71 percent.

Preparation of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium Dichloride

15 In the drybox, 17.23 grams (59.93 mmol) of dimethylsilyl(2,3,4,6-tetramethylindenyl)(isopropylamine) was dissolved in 350 mL of hexane in a 500 mL round-bottom schlenk flask. Two equivalents of n-BuLi (47.94 mL, 2.5 M in hexanes) were then added via syringe. The reaction was stirred for twelve hours. The solvent was removed under reduced pressure to afford an orange powder. The powder was dissolved in 250 mL of THF.
20 TiCl₃(THF)₃ (22.2 grams, 59.93 mmol) was added as a solid. After 15 minutes, CH₂Cl₂ (2.48 mL, 29.97 mmol) was added. After two hours, the solvent was removed under reduced pressure. The residue was extracted with toluene and filtered through a diatomaceous earth filter aid on a 10 to 15 mm glass frit. The toluene was removed under reduced pressure. The residue was slurried in hexane and filtered over a 10 to 15 mm glass frit. The residue was dried
25 under reduced pressure to afford a red powder. Yield; 12.3 grams, 51 percent.

Preparation of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium Dimethyl

In the drybox, [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]titanium dichloride (6.92 grams, 17.12 mmol) was suspended in 150 mL of Et₂O in a 250 mL round bottom flask. Two equivalents of a 3.0 M THF solution of MeMgCl (11.41 mL, 34.23 mmol)
30 were added. The mixture was stirred for one hour. The volatiles were removed under reduced pressure. The residue was extracted with hexane and filtered through a diatomaceous earth

filter aid on a 10-15 mm glass frit. The hexane was removed under reduced pressure to afford an orange powder. Yield; 5.8 grams, 93 percent.


Example G Preparation of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane]-titanium (1,4-diphenyl-1,3-butadiene)

- 5 In the drybox, 0.50 grams (1.24 mmol) of [(N-isopropylamido)(dimethyl)(2,3,4,6-tetramethylindenyl)silane] titanium dichloride was slurried in 60 mL of cyclohexane in a 100 mL round-bottom schlenk flask. 1,4-Diphenyl-1,3-butadiene (.255 grams, 1.24 mmol) was added as a solid. Two equivalents of n-BuLi (.989 mL, 2.5 M in hexanes) were then added via syringe. The flask was fitted with a condenser and heated to reflux for one hour. Upon cooling, the
10 reaction was filtered through a diatomaceous earth filter aid (Celite TM) on a 10-15 mm glass frit. The salts and filter aid were washed with 50 mL of pentane. The solvent was removed under reduced pressure to afford a red/brown powder. Yield; 300 mg, 45 percent.

- Polymerization experiments were performed using a 3.8 liter stirred reactor charged with 1440 g of Isopar E TM (mixed alkanes; available from Exxon Chemicals Inc.), 132 g of
15 1-octene, and 10 mMol of hydrogen. The reactor was heated to 130 °C and saturated with ethylene to 450 psig (4.5 Mpa). The catalyst was prepared in a drybox by syringing together 5.0 mmol (1.0 mL, .005 M) of the metal complex, 15.0 mmol (1.0 mL, .015 M) of cocatalyst, trispentafluorophenylborane (TPFPB), and 50.0 mmol (1.0 mL, .05 M) of scavenger, modified methylaluminoxane (from Akzo-Nobel), with additional Isopar E TM to give a total volume of 17
20 mL. The catalyst solution was then transferred by syringe to a catalyst addition loop and injected into the reactor over approximately 4 minutes using a flow of high pressure solvent. The polymerization was allowed to proceed for 10 minutes while feeding ethylene on demand to maintain a pressure of 445 psig (4.5 Mpa). The polymer solution was then poured from the reactor into a nitrogen-purged glass kettle containing approximately 15 mL of isopropanol. A 20
25 mL aliquot of a stabilizer solution prepared by dissolving 6.66 g of Irgaphos TM 168 and 3.33 g of Irganox TM 1010 in 500 mL of toluene was added. The polymer solution was poured into a tray, air dried overnight, then thoroughly dried in a vacuum oven for two days.

Example H

Synthesis of: dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl]silanaminto(2-)-N] titanium (also referred to as dimethylsilyl(2-methyl-s-indacenyl)(cyclohexyl-amido)TiCl₂

Preparation of chlorodimethyl(1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl)silane

1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl)lithium (1c)) (24.369 g, 0.13831 moles) in THF (100 mL) was added dropwise to a solution of Me₂SiCl₂ (89.252 g, 0.69155 moles) in THF (150 mL). This mixture was then allowed to stir at 20 to 25 °C for 5 hours. After the reaction period the volatiles were removed and the residue extracted and filtered using hexane. The removal of the hexane resulted in the isolation of the desired product as an off-white crystalline solid (31.1451 g, 85.7 percent).

Preparation of N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl)silanamine

Chlorodimethyl(1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl) silane (5.67 g, 0.0216 moles) was stirred in hexane (50 mL) as NEt₃ (2.18 g, 0.0216 moles) and cyclohexylamine (2.13 g, 0.0216 moles) were added. This mixture was allowed to stir 16 hours. After the reaction period the mixture was filtered and the volatiles removed resulting in the isolation of the desired product as a yellow oil (6.62 g, 94.3 percent).

Preparation of [N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl]silanaminto(2-)-N] dilithium

N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl)silanamine (6.67 g, 0.02048 moles) was stirred in hexane (100 mL) as nBuLi (0.04302 moles, 21.51 mL of 2.0 M solution in cyclohexane) was added slowly. This mixture was then allowed to stir 16

hours. After the reaction period the desired product was isolated as a solid which was used without further purification or analysis (7.23 g, product still contained residual hexane).

Preparation of dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl]silanaminto(2-)-N] titanium

- 5 [N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl]silanaminto(2-)-N] dilithium (7.23 g, 0.0214 moles) was slowly added as a solid to a slurry of $\text{TiCl}_3(\text{THF})_3$ (7.93 g, 0.0214 moles) in THF (50 mL). This mixture was allowed to stir for 30 minutes. PbCl_2 (3.80 g, 0.0136 moles) was then added and the mixture allowed to stir for an additional hour. After the reaction period the volatiles were removed and the residue extracted and filtered using toluene. Removal of the toluene resulted in the isolation of a dark residue. This residue was then slurried in hexane and the desired product isolated via filtration as a solid (3.71 g, 39.2 percent).


Example H

- 15 Synthesis of: dimethyl[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (also referred to as dimethylsilyl(2-methyl-s-indacenyl)(cyclohexyl-amido) TiMe_2

- Dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2-methyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (0.400 g, 0.00904 moles) was stirred in diethylether (50 mL) as MeMgBr (0.0181 moles, 0.60 mL of 3.0 M solution in diethylether) was added slowly. 20 This mixture was then stirred for 1 hour. After the reaction period the volatiles were removed and the residue extracted and filtered using hexane. Removal of the hexane resulted in the isolation of the desired product as a solid (0.309 g, 85.1 percent).

Example I

- 25 Synthesis of: dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (also referred to as dimethylsilyl(2,3-dimethyl-s-indacenyl)(cyclohexylamido) TiCl_2



Preparation of N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl) silanamine

Chlorodimethyl(1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl)silane (5.00 g, 0.01806 moles) was stirred in hexane (80 mL) as NEt_3 (3.29 g, 0.03251 moles) and t-butylamine (1.81 g, 0.01824 moles) were added. This mixture was allowed to stir 16 hours. After the reaction period the mixture was filtered and the volatiles removed resulting in the isolation of the desired product as a yellow oil (5.55 g, 90.9 percent).

Preparation of [N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl]silanaminto(2-)-N]dilithium

N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl)silanamine (5.30 g, 0.01570 moles) was stirred in hexane (75 mL) as n-BuLi (0.03454 moles, 13.8 mL of 2.5 M solution in hexane) was added slowly. This mixture was then allowed to stir for 72 hours. After the reaction period the hexane was decanted away and the volatiles were removed resulting in the isolation of the desired product as an orange glassy solid which was used without further purification or analysis (5.56 g, 99.9 percent).

Preparation of dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl]silanaminto(2-)-N] titanium

[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5- η]-1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl]silanaminto(2-)-N]dilithium (0.500 g, 0.01428 moles) was slowly added as a solid to a slurry of $\text{TiCl}_3(\text{THF})_3$ (0.529 g, 0.001428 moles) in THF 50 mL. This mixture was allowed to stir for 2 hours. PbCl_2 (0.317 g, 0.001142 moles) was then added and the mixture allowed to stir for an additional hour. After the reaction period the volatiles were removed and the residue extracted and filtered using toluene. Removal of the toluene resulted in the isolation of a dark residue. This residue was then slurried in hexane and cooled in a refrigerator for 72 hours. The desired product was then isolated via filtration as a solid (0.259 g, 43.8 percent).


Example J

Synthesis of: dimethyl[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (also referred to as dimethylsilyl(2,3-dimethyl-s-indacenyl)(cyclohexylamido)TiMe₂

- 5 Dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2,3-dimethyl-s-indacen-1-yl]silanaminto(2-)-N] titanium (0.300 g, 0.0006588 moles) was stirred in diethylether (50 mL) as MeMgBr (0.001447 moles, 0.48 mL of 3.0 M solution in diethylether) was added slowly. This mixture was then stirred for 1 hour. After the reaction period the volatiles were removed and the residue extracted and filtered using hexane. Removal of the hexane resulted
10 in the isolation of the desired product as an orange solid (0.249 g, 91.2 percent).

Example K

Synthesis of: dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (also referred to as dimethylsilyl(2-methyl-3-phenyl-s-indacenyl)(cyclohexylamido)TiCl₂



15

Preparation of N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl) silanamine

- Chlorodimethyl(1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl) silane (9c) (5.5340 g, 0.01633 moles) was stirred in hexane (100 mL) as NEt₃ (2.9673 g, 0.02932 moles) and cyclohexylamine (1.6373 g, 0.01651 moles) were added. This mixture was allowed to stir
20 for 24 hours. After the reaction period the mixture was filtered and the volatiles removed resulting in the isolation of the desired product as a yellow oil (5.8969 g, 89.9 percent).

Preparation of [N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]dilithium


N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl)silamine (5.8969 g, 0.01468 moles) was stirred in hexane (100 mL) as nBuLi (0.032 moles, 16.00 mL of 2.0 M solution in cyclohexane) was added slowly. This mixture was then allowed to stir 16 hours during which time a sticky precipitate formed. The volatiles were then removed and the resulting pale yellow solid slurried in cold hexane. After the reaction period the solid was collected via suction filtration as a yellow powder which was used without further purification or analysis (5.3101 g, 87.5 percent).

Preparation of dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]titanium

[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]dilithium (5.3103 g, 0.01284 moles) in THF (50 mL) was added dropwise to a slurry of $\text{TiCl}_3(\text{THF})_3$ (4.7570 g, 0.01284 moles) in THF (100 mL). This mixture was allowed to stir for 2 hours. PbCl_2 (1.8896 g, 0.006795 moles) was then added and the mixture allowed to stir for an additional hour. After the reaction period the volatiles were removed and the residue extracted and filtered using toluene. Removal of the toluene resulted in the isolation of a dark residue. This residue was then slurried in hexane and cooled to -10°C . The desired product was then isolated via filtration as a red crystalline solid (3.0765 g, 46.2 percent).

Example L

Synthesis of: dimethyl[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (also referred to as dimethylsilyl(2-methyl-3-phenyl-s-indacenyl)(cyclohexylamido)TiMe₂)




Dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η)-1,5,6,7-tetrahydro-2-methyl-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (0.7164 g, 0.001382 moles) was stirred in diethylether (50 mL) as MeMgBr (0.002760 moles, 0.92 mL of 3.0 M solution in diethylether) was added

slowly. This mixture was then stirred for 1 hour. After the reaction period the volatiles were removed and the residue extracted and filtered using hexane. Removal of the hexane resulted in the isolation of the desired product as a sticky yellow-red residue (0.5102 g, 77.3 percent).

Example M

- 5 Synthesis of dichloro[N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η]-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]titanium (also referred to as dimethylsilyl(3-phenyl-s-indacen-1-yl)(cyclohexylamido)TiCl₂)



- 10 Preparation of N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl)silanamine

Chlorodimethyl(1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl) silane (3.8523 g, 0.01182 moles) was stirred in hexane (100 mL) as NEt₃ (1.5136 g, 0.01496 moles) and cyclohexylamine (1.2107 g, 0.01221 moles) were added. This mixture was allowed to stir for 24 hours. After the reaction period the mixture was filtered and the volatiles removed resulting in the isolation of the

15 desired product as a yellow oil (4.3313 g, 94.5 percent).

Preparation of [N-(cyclohexyl)-1,1-dimethyl-[1,2,3,4,5-η]-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl]silanaminto(2-)-N]dilithium

- N-(cyclohexyl)-1,1-dimethyl-1-(1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl)silanamine (4.3313 g, 0.01117 moles) was stirred in hexane (100 mL) as nBuLi (0.024 moles, 12.00 mL of
- 20 2.0 M solution in cyclohexane) was added slowly. This mixture was then allowed to stir 16 hours during which time a sticky precipitate formed. The volatiles were then removed and the resulting pale yellow solid slurried in cold hexane. After the reaction period the solid was collected via suction filtration as a red crystalline powder which was used without further purification or analysis (5.3101 g, 87.5 percent).

Preparation of dichloro[N-(cyclohexyl)-1,1-dimethyl-1-[(1,2,3,4,5- η)-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl]silanaminato(2-)-N]titanium

[N-(cyclohexyl)-1,1-dimethyl-1-[(1,2,3,4,5- η)-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl]silanaminato(2-)-N]dilithium (4.2135 g, 0.01055 moles) in THF (50 mL) was added dropwise to a slurry of $\text{TiCl}_3(\text{THF})_3$ (3.9085 g, 0.01055 moles) in THF (100 mL). This mixture was allowed to stir for 2 hours. PbCl_2 (1.5373 g, 0.005529 moles) was then added and the mixture allowed to stir for an additional hour. After the reaction period the volatiles were removed and the residue extracted and filtered using toluene. Removal of the toluene resulted in the isolation of a dark residue. This residue was then slurried in hexane and cooled to 0 °C. The desired product was then isolated via filtration as a red-brown crystalline solid (2.7655 g, 52.0 percent).

Example N

Synthesis of dimethyl[N-(cyclohexyl)-1,1-dimethyl-1-[(1,2,3,4,5- η)-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl]silanaminato(2-)-N]titanium (also referred to as dimethylsilyl(3-phenyl-s-indacen-1-yl)(cyclohexylamido) TiMe_2)

Dichloro[N-(cyclohexyl)-1,1-dimethyl-1-[(1,2,3,4,5- η)-1,5,6,7-tetrahydro-3-phenyl-s-indacen-1-yl]silanaminato(2-)-N]titanium (0.5581 g, 0.001106 moles) was stirred in diethylether (50 mL) as MeMgBr (0.0022 moles, 0.74 mL of 3.0 M solution in diethylether) was added slowly. This mixture was then stirred for 1 hour. After the reaction period the volatiles were removed and the residue extracted and filtered using hexane. Removal of the hexane resulted in the isolation of the desired product as a yellow-red residue (0.2118 g, 41.3 percent).

2-ethylene/1-octene copolymerization

A stirred 3.8 liter reactor was charged with 1440 g of Isopar-E™ mixed alkanes solvent (available from Exxon Chemicals Inc.) and 126 g of 1-octene comonomer. Hydrogen was added as a molecular weight control agent by differential pressure expansion from a 75 mL addition tank at 25 psid (2070 kPa). The reactor was heated to the polymerization temperature of 130 °C and saturated with ethylene at 450 psig (3.1 MPa). Approximately 2.0 μmol each of the Catalyst of Example H and tris(pentafluorophenyl)borane cocatalyst as 0.005 M solutions in toluene were premixed in a drybox, transferred to a catalyst addition tank and injected into the reactor over approximately a four minute period. The polymerization conditions were maintained for 10 minutes with ethylene on demand. The resulting solution was removed from the reactor, and a hindered phenol antioxidant (Irganox™ 1010 from Ciba Geigy Corporation) was added to the resulting solution. Polymers formed were dried in a vacuum oven set at 120

°C for about 20 hours. The catalyst efficiency was 700 kilograms polymer per gram Ti. The melt index (I₂) of the polymer was 0.43 g/10 min.

1. An olefin polymer produced by polymerizing at least one α -olefin in the presence of a catalyst further comprising a metal complex corresponding to the formula:



5 wherein:

M is titanium, zirconium or hafnium in the +2, +3 or +4 formal oxidation state;

A' is a substituted indenyl group substituted in at least the 2 or 3 position with a group selected from hydrocarbyl, fluoro-substituted hydrocarbyl, hydrocarbyloxy-substituted hydrocarbyl, dialkylamino-substituted hydrocarbyl, silyl, germyl and mixtures thereof, said
10 group containing up to 40 nonhydrogen atoms, and said A' further being covalently bonded to M by means of a divalent Z group;

Z is a divalent moiety bound to both A' and M via σ -bonds, said Z comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen or phosphorus, wherein an aliphatic or alicyclic hydrocarbyl group is covalently bonded to the
15 nitrogen or phosphorus via a primary or secondary carbon;


X is an anionic or dianionic ligand group having up to 60 atoms exclusive of the class of ligands that are cyclic, delocalized, π -bound ligand groups;

X' independently each occurrence is a neutral ligating compound, having up to 20 atoms;

20 p is 0, 1 or 2, and is two less than the formal oxidation state of M, with the proviso that when X is a dianionic ligand group, p is 1; and

q is 0, 1 or 2.

2. The polymer of Claim 1, wherein the metal complex corresponds to the formula:



25 wherein:

R_1 and R_2 , independently are groups selected from hydrogen, hydrocarbyl, perfluoro substituted hydrocarbyl, silyl, germyl and mixtures thereof, said group containing up to 20 nonhydrogen atoms, with the proviso that at least one of R_1 or R_2 is not hydrogen;

R_3 , R_4 , R_5 , and R_6 independently are groups selected from hydrogen, hydrocarbyl, perfluoro substituted hydrocarbyl, silyl, germyl and mixtures thereof, said group containing up to 20 nonhydrogen atoms;

M is titanium, zirconium or hafnium;

Z is a divalent moiety comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen or phosphorus, said moiety having up to 60 nonhydrogen atoms, wherein an aliphatic or alicyclic hydrocarbyl group is covalently bonded to the nitrogen or phosphorus via a primary or secondary carbon;

p is 0, 1 or 2;

q is zero or one;


with the proviso that:

when p is 2, q is zero, M is in the +4 formal oxidation state, and X is an anionic ligand selected from the group consisting of halide, hydrocarbyl, hydrocarbyloxy, di(hydrocarbyl)amido, di(hydrocarbyl)phosphido, hydrocarbylsulfido, and silyl groups, as well as halo-, di(hydrocarbyl)amino-, hydrocarbyloxy- and di(hydrocarbyl)phosphino-substituted derivatives thereof, said X group having up to 20 nonhydrogen atoms,

when p is 1, q is zero, M is in the +3 formal oxidation state, and X is a stabilizing anionic ligand group selected from the group consisting of allyl, 2-(N,N-dimethylaminomethyl)phenyl, and 2-(N,N-dimethyl)-aminobenzyl, or M is in the +4 formal oxidation state, and X is a divalent derivative of a conjugated diene, M and X together forming a metallocyclopentene group, and

when p is 0, q is 1, M is in the +2 formal oxidation state, and X' is a neutral, conjugated or nonconjugated diene, optionally substituted with one or more hydrocarbyl groups, said X' having up to 40 carbon atoms and forming a π -complex with M.

3. The olefin polymer of Claim 1, wherein the metal complex corresponds to the formula:



wherein:

R_1 and R_2 independently are hydrogen or C_{1-6} alkyl, with the proviso that both R_1 and R_2 are not hydrogen;

5 R_3 , R_4 , R_5 , and R_6 are independently hydrogen or C_{1-6} alkyl;

M is titanium;

Y is $-NR^{**}-$, or $-PR^{**}-$;

Z^* is SiR^{*}_2 , CR^{*}_2 , $SiR^{*}_2SiR^{*}_2$, $CR^{*}_2CR^{*}_2$, $CR^{*}=CR^{*}$, $CR^{*}_2SiR^{*}_2$, or GeR^{*}_2 ;

10 R^* each occurrence is independently hydrogen, or a member selected from hydrocarbyl, hydrocarbyloxy, silyl, halogenated alkyl, halogenated aryl, and combinations thereof, said R^* having up to 20 non-hydrogen atoms, and optionally, two R^* groups from Z (when R^* is not hydrogen), or an R^* group from Z and an R^* group from Y form a ring system, and wherein, when Y is $-NR^{*-}$ or $-PR^{*-}$, the R^* is covalently bonded to the N or P through a primary or secondary carbon;

15 R^{**} is a aliphatic or alicyclic hydrocarbyl group covalently bonded to the nitrogen or phosphorus of Y via a primary or secondary carbon;

p is 0, 1 or 2;

q is zero or one;


with the proviso that:

20 when p is 2, q is zero, M is in the +4 formal oxidation state, and X is independently each occurrence methyl or benzyl,

when p is 1, q is zero, M is in the +3 formal oxidation state, and X is 2-(N,N-dimethyl)aminobenzyl; or M is in the +4 formal oxidation state and X is 1,4-butadienyl, and

25 when p is 0, q is 1, M is in the +2 formal oxidation state, and X' is 1,4-diphenyl-1,3-butadiene or 1,3-pentadiene.

4. An olefin polymer produced by a process comprising reacting one or more α -olefins in the presence of a catalyst which in turn comprises a metal complex corresponding to the formula:



where M is titanium, zirconium or hafnium in the +2, +3 or +4 formal oxidation state;

R' and R'' are independently each occurrence hydride, hydrocarbyl, silyl, germyl, halide, hydrocarbyloxy, hydrocarbylsiloxy, hydrocarbylsilylamino, di(hydrocarbyl)amino,
 5 hydrocarbyleneamino, di(hydrocarbyl)phosphino, hydrocarbylene-phosphino, hydrocarbylsulfido, halo-substituted hydrocarbyl, hydrocarbyloxy-substituted hydrocarbyl, silyl-substituted hydrocarbyl, hydrocarbylsiloxy-substituted hydrocarbyl, hydrocarbylsilylamino-substituted hydrocarbyl, di(hydrocarbyl)amino-substituted hydrocarbyl, hydrocarbyleneamino-substituted hydrocarbyl, di(hydrocarbyl)phosphino-substituted hydrocarbyl, hydrocarbylene-phosphino-substituted hydrocarbyl, or hydrocarbylsulfido-substituted hydrocarbyl, said R' or R''
 10 group having up to 40 nonhydrogen atoms, and optionally two or more of the foregoing groups may together form a divalent derivative;

R''' is a divalent hydrocarbylene- or substituted hydrocarbylene group forming a fused system with the remainder of the metal complex, said R''' containing from 1 to 30 nonhydrogen
 15 atoms;

Z is a divalent moiety, or a moiety comprising one σ -bond and a neutral two electron pair able to form a coordinate-covalent bond to M, said Z comprising boron, or a member of Group 14 of the Periodic Table of the Elements, and also comprising nitrogen or phosphorus, wherein an aliphatic or alicyclic hydrocarbyl group is covalently bonded to the nitrogen or
 20 phosphorus via a primary or secondary carbon;

X is a monovalent anionic ligand group having up to 60 atoms exclusive of the class of ligands that are cyclic, delocalized, π -bound ligand groups;

X' independently each occurrence is a neutral ligating compound having up to 20 atoms;

25 X'' is a divalent anionic ligand group having up to 60 atoms;

p is zero, 1, 2, or 3;

q is zero, 1 or 2, and

r is zero or 1; and


2) an activating cocatalyst

the molar ratio of 1) to 2) being from 1:10,000 to 100:1, or

5 the reaction product formed by converting 1) to an active catalyst by use of an activating technique.

5. The olefin polymer of any of Claims 1 - 4, wherein the α -olefin is polymerized in the presence of the catalyst comprising the metal complex and an activating cocatalyst.

6. The olefin polymer of Claim 5 wherein the activating cocatalyst comprises
10 trispentafluorophenyl-borane or a cocatalyst corresponding to the formula:



wherein:


L^* is a neutral Lewis base;

$(L^*-H)^+$ is a Bronsted acid;

15 A^{d-} is a noncoordinating, compatible anion having charge d^- , and

d is an integer from 1 to 3.

7. The olefin polymer of Claim 6, wherein the anion A^{d-} is selected from the group consisting of: a) sterically shielded diboron anions corresponding to the formula:




20 wherein:

S is alkyl, fluoroalkyl, aryl, or fluoroaryl (and where two S groups are present additionally hydrogen),

Ar^f is fluoroaryl, and

X^1 is either hydrogen or halide, and

25 b) anions corresponding to the formula:



wherein:

k is an integer from 1 to 3;

n' is an integer from 2 to 6;

5 n'-k = d;

M' is an element selected from Group 13 of the Periodic Table of the Elements; and

Q independently each occurrence is selected from hydride, dialkylamido, halide, alkoxide, aryloxy, hydrocarbyl, and halosubstituted-hydrocarbyl radicals, said Q having up to 20 carbons with the proviso that in not more than one occurrence is Q halide.

10 8. The olefin polymer of Claim 6 wherein the activating cocatalyst comprises a borane or borate selected from the group consisting of trispentafluorophenylborane, i(octadecyl)methylammonium tetrakis(pentafluorophenyl)borate, and di(octadecyl)(n-butyl)ammonium tetrakis(pentafluorophenyl)borate.

15 9. The olefin polymer of Claim 6, wherein the activating cocatalyst further comprises an aluminum compound selected from the group consisting of tri(hydrocarbyl)aluminum compounds having from 1 to 10 carbons in each hydrocarbyl group, oligomeric or polymeric alumoxane compounds, di(hydrocarbyl)(hydrocarbyloxy)aluminum compounds having from 1 to 20 carbons in each hydrocarbyl or hydrocarbyloxy group, or a mixture of the foregoing compounds.

20 10. The olefin polymer of Claim 9, wherein the aluminum compound corresponds to the formula $T^1_2AlOT^2$, wherein T^1 is C_{3-6} secondary or tertiary alkyl and T^2 is a C_{12-30} alkaryl radical or aralkyl radical.

25 11. The olefin polymer of Claim 10, wherein the aluminum compound is 2,6-di(t-butyl)-4-methylphenyl, 2,6-di(t-butyl)-4-methyltolyl, 2,6-di(i-butyl)-4-methylphenyl, or 4-(3',5'-ditertiarybutyltolyl)-2,6-ditertiarybutylphenyl.

12. An olefin interpolymer characterized as satisfying at least four of the following criteria:

- a) an $I_2 \leq 100$ g/10 min,
- b) an M_w/M_n of from 1.5 to 3.0,
- 30 c) at least 0.03 vinyls/1000 carbons, as determined by FTIR, and
- d) a deconvoluted DSC melting curve which shows two distinct first and second DSC melting points, and

e) an ATREF curve which satisfies the following inequality:

$$\text{ATREF Shape Factor} \leq 0.90 - 0.00626 (\text{Average Elution Temperature})$$

13. The olefin polymer of Claim 12, wherein the ATREF curve satisfies the following inequality:

5 $\text{ATREF Shape Factor} \leq 0.75 - 0.00626 (\text{Average Elution Temperature}).$

14. An olefin interpolymer characterized as satisfying at least four of the following criteria:

a) an $I_2 \leq 100$ g/10 min,

b) an M_w/M_n of from 1.5 to 3.0,

10 c) at least 0.03 vinyls/1000 carbons, as determined by FTIR,

d) a deconvoluted DSC melting curve which shows two distinct first and second DSC melting points, and

15 e) a deconvoluted gel permeation chromatogram which shows two distinct first and second component fractions, wherein the first component fraction has a first density, a first I_2 , and is provided in a first weight percent, and wherein the second component fraction has a second density, a second I_2 , and is provided in a second weight percent.

15. The olefin interpolymer of Claim 14, wherein that the upper service temperature of the olefin interpolymer (UST (interpolymer)) is greater than the upper service temperature of a physical blend (UST (blend)) of a first homogeneous olefin polymer having a density equal to the first density, an I_2 equal to the first I_2 , and which is provided in the first weight percent, and a second homogeneous olefin polymer having a density equal to the second density, an I_2 equal to the second I_2 , and which is provided in the second weight percent, in accordance with the following inequality:

$$\text{UST (interpolymer)} - \text{UST (blend)} \geq 256 - 275 (\text{density of olefin interpolymer}).$$

25 16. The olefin interpolymer of any of Claims 12 - 15, which is further characterized as being an interpolymer of ethylene and at least one C_3 - C_{20} α -olefin.

17. The olefin interpolymer of any of Claims 12 - 16, which is further characterized as having an I_{10}/I_2 of at least 10.

30 18. The olefin interpolymer of any of Claims 12 - 16, which is further characterized as having from 0.01 to 3 long chain branches/1000 carbons.

19. The olefin interpolymers of any of Claims 12 - 16, which is further characterized as exhibiting a critical shear rate at the onset of surface melt fracture which is at least 50 percent greater than the critical shear rate at the onset of surface melt fracture for a linear interpolymers, wherein the olefin interpolymers and the linear interpolymers comprise the same comonomer or comonomers, the linear interpolymers has an I_2 and density within ten percent of that of the olefin interpolymers, and wherein the respective critical shear rates of the olefin interpolymers and the linear interpolymers are measured at the same melt temperature using a gas extrusion rheometer.

20. The olefin interpolymers of any of Claims 12 - 19 which is further characterized as having a density of no more than 0.915 g/cm^3 .

21. A method for improving the upper service temperature of an article or a formulation, comprising incorporating into the same an olefin interpolymers characterized as having:

- a) an $I_2 \leq 100 \text{ g/10 min}$,
- b) an M_w/M_n of from 1.5 to 3.0,
- c) at least 0.03 vinyls/1000 carbons, as determined by FTIR,
- d) at least two distinct DSC melting points, and
- e) a deconvoluted gel permeation chromatogram which shows two distinct first and second component fractions, wherein the first component fraction has a first density, a first I_2 , and is provided in a first weight percent, and wherein the second component fraction has a second density, a second I_2 , and is provided in a second weight percent.

22. The olefin polymer of Claim 3, wherein the metal complex is (cyclohexylamido)dimethyl(η 5-2,3,4,6-tetramethylindenyl)silane-titanium (IV) dimethyl or (isopropylamido)dimethyl(η 5-2,3,4,6-tetramethylindenyl)silane-titanium (IV) dimethyl.

23. The olefin polymer of any of Claims 12 - 16, wherein the olefin polymer is an interpolymers of ethylene, a C_3 - C_{20} α -olefin, and an optional diene.


24. The olefin polymer of Claim 23, wherein the olefin polymer is an interpolymers of ethylene, propylene and a diene.

25. The olefin polymer of Claim 12, which satisfies each of the criteria (a) - (e).

26. The olefin polymer of Claim 14, which satisfies each of the criteria (a) - (e).

1 / 19

FIG. 1



2 / 19

FIG. 2






FIG. 3



SUBSTITUTE SHEET (RULE 26)

3 / 19

FIG. 4




4 / 19

FIG.5




SUBSTITUTE SHEET (RULE 26)

FIG. 6




6 / 19

FIG. 7A




7 / 19

FIG. 7B




8 / 19

FIG. 7C



9 / 19

FIG. 7D



SUBSTITUTE SHEET (RULE 26)

FIG. 8A






FIG. 8B



SUBSTITUTE SHEET (RULE 26)

11 / 19


FIG. 9A



SUBSTITUTE SHEET (RULE 26)

12 / 19


FIG. 9B



SUBSTITUTE SHEET (RULE 28)

13 / 19


FIG. 10



SUBSTITUTE SHEET (RULE 28)

14 / 19


FIG. 11



SUBSTITUTE SHEET (RULE 26)

15 / 19


FIG. 12



SUBSTITUTE SHEET (RULE 26)

16 / 19

FIG. 13




— Viscosity 2a Continuous
..... Viscosity c- 2a Batch
- - - Tan δ 2a Continuous
- . - Tan δ c- 2a Batch

SUBSTITUTE SHEET (RULE 26)


17 / 19

FIG. 14




18 / 19

FIG. 15



SUBSTITUTE SHEET (RULE 28)

FIG. 16



In. **Patent Application No**
PCT/US 98/08859

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 749 975 A (HOECHST AG) 27 December 1996	1,5,6,
Y	see page 5, line 58 - line 59	8-11
	see page 11, line 5 - page 12, line 5; claims	1,5-11
Y	US 5 447 895 A (MARKS TOBIN J ET AL) 5 September 1995 see claims	1,5-11
X	EP 0 298 700 A (MITSUI PETROCHEMICAL IND) 11 January 1989 see the whole document	12-17, 20,21
X	EP 0 286 177 A (STAMICARBON) 12 October 1988 see claims	12-17, 20,21
	-/--	

☒ Further documents are listed in the continuation of box C.

X Patent family members are listed in annex.

* Special categories of cited documents :

P document published prior to the international filing date but later than the priority date claimed

"&" document member of the same patent family

Date of the actual completion of the international search

13 July 1998

Date of mailing of the international search report

03/08/1998

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kaumann, E

INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/US 98/08859

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 00526 A (DOW CHEMICAL CO) 5 January 1995	1,5
A	cited in the application see page 2, line 1 - page 4, line 22 see page 6, line 22 - page 24, line 8 see claims; example 22	2-4,6-26
A	WO 93 08221 A (DOW CHEMICAL CO) 29 April 1993	1-26
A	see the whole document & US 5 272 236 A cited in the application	1-26
A	EP 0 416 815 A (DOW CHEMICAL CO) 13 March 1991	1-11
	cited in the application see claims; example 96	
P,X	WO 97 15583 A (DOW CHEMICAL CO ;NICKIAS PETER N (US); MCADON MARK H (US); PATTON) 1 May 1997 see the whole document	1-3,5,6, 8-11

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. al Application No
PCT/US 98/08859

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0749975 A	27-12-1996	DE 19522013 A CN 1146994 A JP 9003086 A US 5750752 A	02-01-1997 09-04-1997 07-01-1997 12-05-1998
US 5447895 A	05-09-1995	CA 2185111 A WO 9524269 A	14-09-1995 14-09-1995
EP 0298700 A	11-01-1989	JP 1014018 A JP 2041658 C JP 7077754 B CA 1309800 A CN 1030592 A CN 1146399 A DE 3870733 A US 5296580 A	18-01-1989 09-04-1996 23-08-1995 03-11-1992 25-01-1989 02-04-1997 11-06-1992 22-03-1994
EP 0286177 A	12-10-1988	NL 8700797 A NL 8702902 A DE 3868664 A ES 2063753 T JP 1085205 A	01-11-1988 01-11-1988 09-04-1992 16-01-1995 30-03-1989
WO 9500526 A	05-01-1995	US 5470993 A AT 147748 T AU 681678 B AU 7111194 A BR 9407034 A CN 1125951 A CZ 9503438 A DE 69401509 D DE 69401509 T DK 705269 T EP 0705269 A ES 2096475 T FI 956244 A HU 74312 A JP 2736938 B JP 8511804 T NO 955290 A	28-11-1995 15-02-1997 04-09-1997 17-01-1995 19-03-1996 03-07-1996 12-06-1996 27-02-1997 17-07-1997 28-07-1997 10-04-1996 01-03-1997 15-02-1996 30-12-1996 08-04-1998 10-12-1996 23-02-1996

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/08859

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9500526 A		PL 312274 A	15-04-1996
		US 5624878 A	29-04-1997
		US 5556928 A	17-09-1996
		ZA 9404510 A	27-12-1995
WO 9308221 A	29-04-1993	US 5272236 A	21-12-1993
		US 5278272 A	11-01-1994
		CA 2120766 A	29-04-1993
		DE 9219090 U	25-09-1997
		DE 69220077 D	03-07-1997
		DE 69220077 T	20-11-1997
		EP 0608369 A	03-08-1994
		EP 0783006 A	09-07-1997
		ES 2103976 T	01-10-1997
		FI 941727 A	31-05-1994
		JP 7500622 T	19-01-1995
		US 5380810 A	10-01-1995
		US 5427807 A	27-06-1995
		US 5562958 A	08-10-1996
		US 5395471 A	07-03-1995
		US 5582923 A	10-12-1996
		US 5525695 A	11-06-1996
		US 5674342 A	07-10-1997
		US 5685128 A	11-11-1997
		US 5591390 A	07-01-1997
		US 5773155 A	30-06-1998
		US 5595705 A	21-01-1997
		US 5677383 A	14-10-1997
		US 5665800 A	09-09-1997
EP 0416815 A	13-03-1991	AT 156827 T	15-08-1997
		AU 645519 B	20-01-1994
		AU 6203990 A	07-03-1991
		CA 2024333 A	01-03-1991
		DE 69031255 D	18-09-1997
		DE 69031255 T	05-03-1998
		EP 0764653 A	26-03-1997
		EP 0764664 A	26-03-1997
		EP 0764654 A	26-03-1997
		EP 0774468 A	21-05-1997

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Application No

PCT/US 98/08859

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0416815 A		EP 0765888 A	02-04-1997
		ES 2106020 T	01-11-1997
		HU 209316 B	28-04-1994
		JP 2684154 B	03-12-1997
		JP 7053618 A	28-02-1995
		JP 2623070 B	25-06-1997
		JP 7070223 A	14-03-1995
		JP 2535249 B	18-09-1996
		JP 3163088 A	15-07-1991
		NO 176964 B	20-03-1995
		NO 179043 B	15-04-1996
		NO 301376 B	20-10-1997
		NO 954469 A	01-03-1991
		RU 2073018 C	10-02-1997
		US 5703187 A	30-12-1997
		CN 1049849 A,B	13-03-1991
		PL 166689 B	30-06-1995
WO 9715583 A	01-05-1997	AU 7392996 A	15-05-1997

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.